

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicants: B.D. Ratner et al. Attorney Docket No.: UWOTL121535  
Application No.: 10/630,235 Art Unit: 1641 / Confirmation No: 8280  
Filed: July 29, 2003 Examiner: A.Y. Lam  
Title: APPARATUS AND METHODS FOR BINDING  
MOLECULES AND CELLS

DECLARATION OF BUDDY D. RATNER

Seattle, Washington 98101

March 31, 2008

TO THE COMMISSIONER FOR PATENTS:

I, Buddy D. Ratner, declare as follows:

1. I am a professor in the Department of Bioengineering and the Department of Chemical Engineering at the University of Washington. I am the co-editor of Surface Modification of Polymeric Biomaterials, Springer (1997), a text that deals extensively with the deposition and characterization of plasma-deposited polymers. I am an inventor of the invention claimed in the above-captioned application and am familiar with the subject matter disclosed and claimed therein. A copy of my CV is attached hereto.

2. I have read and understand the Takei et al. (*Macromolecules*, 1994) reference. The Takei et al reference teaches solution-deposited polymerized (*N*-isopropylacrylamide) (NIPAM) having end-group and/or mid-chain carboxyl functionality that facilitates covalently bonding of the polymers to an amino-functionalized substrate.

3. Plasma is an ionized gas phase with a high energy state and a monomer subjected to a plasma will typically result in several species being formed at several locations in the plasma chamber. Because monomers in the plasma state are highly active, they can combine with each other to form oligomers and polymers in the gas phase. The monomers can also react with a

LAW OFFICES OF  
CHRISTENSEN O'CONNOR JOHNSON KINDNESS<sup>LLC</sup>  
1420 Fifth Avenue  
Suite 2800  
Seattle, Washington 98101  
206.682.8100

substrate, which initiates polymerization on the substrate surface, thus forming covalent bonds between the polymerized monomer and the substrate. The oligomers and polymers formed in gas phase can also react (and bond) with the substrate. In the plasma, monomers can also become fragmented through collision with the substrate or with each other. These fragments will also deposit on the substrate.

4. Plasma-deposited monomers that form polymers on a substrate form films that are distinct in structure and properties from traditionally (solution-based) polymerized materials that are covalently bound to a substrate. In particular, plasma-deposited NIPAM, as described and claimed in the above-captioned application, is distinct from the covalently-coupled NIPAM polymers taught by Takei et al., as cited by the Examiner in the pending Office Action. One significant distinction between the plasma-deposited polymer of the application and the solvent-deposited polymers of Takei et al. is that the plasma-deposited polymer film is a crosslinked polymer—so not only do the polymer chains anchor on the substrate, they also are linked to each other through the plasma deposition process, resulting in a robust film. Another significant distinction relates to surface coverage by the polymer. Because plasma deposition is a gas-based process, it fills all surface space, yielding a pinhole-free coating. Immobilizing a polymer on a chemically functionalized substrate, as taught by Takei et al., yields low coverage density due to steric hindrance of the polymer molecules in the deposition process. When considering applications such as protein and cell binding on the deposited polymer film, any pinholes will lead to non-specific binding (high background) and the loss of reversible binding due to non-specific interactions at the pinhole sites. Thirdly, plasma coating is a universal deposition method that has few, if any, substrate surface chemistry requirements, whereas the deposition process taught by Takei et al requires a particular chemical functionalization (carboxyl) at the surface of the substrate to facilitate polymer bonding.

LAW OFFICES OF  
CHRISTENSEN O'CONNOR JOHNSON KINDNESS<sup>SM</sup>  
1420 Fifth Avenue  
Suite 2800  
Seattle, Washington 98101  
206.682.8100

5. The solvent-free nature of plasma-deposited films of the invention exhibit several advantages over the solution-deposited films taught by Takei et al. Plasma deposition is a dry coating process that creates conformal, pinhole-free and thin (from a few nanometers up to one micrometer) films crosslinked to a substrate. Almost any substrate can be functionalized using the plasma deposition process, in contrast to the substrate-specific wet-functionalization process necessary to create the films taught by Takei et al. Most chemicals that have a low melting point (up to about 200°C) or high vapor pressure can be vaporized and immobilized on a substrate by plasma deposition. There is no functional head group requirement for plasma-deposited monomers, as there is for the polymers taught by Takei et al. Finally, because no solvent is used in the plasma deposition process of the invention described and claimed in the present invention, it is compatible with biological systems.

6. Due to the high energy of plasma and the resulting fragmentation of a deposited monomer, conventional plasma deposition yields a highly crosslinked film with little chemical resemblance to the monomer. In the case of NIPAM deposition, however, maintenance of the side-chain structure on the surface of a coated substrate or device is critical to the thermal responsive function of the deposited film. Thus, a conventional single-step deposition will not produce a film that retains a significant temperature-responsive effect when compared with monomer NIPAM. This deficiency of the plasma deposition process is overcome in the invention by depositing NIPAM in at least two steps, including a high-power plasma and a subsequent lower-power plasma. The high-power deposition step activates the substrate and promotes adhesion of the polymer on a surface or device. The lower-power deposition provides additional polymer to the surface, which crosslinks with and is retained on the high-power deposited polymers, while retaining polymer functionality to exist in a first state to bind

LAW OFFICES OF  
CHRISTENSEN O'CONNOR JOHNSON KINDNESS<sup>SM</sup>  
1420 Fifth Avenue  
Suite 2800  
Seattle, Washington 98101  
206.682.8100

molecules or living cells, and a second state that binds substantially less molecules or living cells, as described in the application and further in paragraph 7 and Figure 1.

7. An experiment was performed under my direct supervision wherein films of plasma-deposited NIPAM were analyzed by electron spectroscopy for chemical analysis (ESCA), the results of which are presented in Figure 1. The theoretical composition of NIPAM is compared to ESCA results for a multistep-deposited film, deposited at a high power followed by at least one lower power, and a high-power-only deposited film. The multistep film was deposited using the experimental procedure described in the present application at page 25, lines 5-19: initial deposition at a plasma power of 80 W and then decreasing the power to 1 W. The high-power film was deposited at 80 W.

Figure 1. ESCA analysis of plasma-deposited NIPAM films.





Figure 1(a) illustrates elemental composition of the two films compared to stoichiometric values.

Figure 1(b) illustrates chemical bonding of the two films compared to stoichiometric values. In

both analyses, it is clearly demonstrated (by the similarity of the stepwise film to the stoichiometric theoretical value) that the stepwise plasma is critical to maintaining the side chain integrity of NIPAM (responsible for the temperature-sensitive properties of NIPAM), while high power alone yields a surface coating dramatically different from an intact polymer. Thus, high-power-deposited NIPAM films will have little or no temperature-responsive properties, while stepwise-deposited films benefit from both strong crosslinking to the substrate surface (high-power deposition) and maintenance of monomer functionality (low-power deposition).

8. All statements made herein and of my own knowledge are true, and all statements made on information and belief are believed to be true; and, further, these statements were made with the knowledge that willful, false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful, false statements may jeopardize the validity of the above-identified application or any patent issued thereon.

Respectfully submitted,

  
Buddy D. Ratner

4/03/08

Date

LRL:pg

LAW OFFICES OF  
CHRISTENSEN O'CONNOR JOHNSON KINDNESS<sup>PC</sup>  
1420 Fifth Avenue  
Suite 2800  
Seattle, Washington 98101  
206.682.8100

## CURRICULUM VITAE

Name: **Buddy D. Ratner**

Birth Date: January 19, 1947

Birthplace: Brooklyn, New York

University Address: Department of Bioengineering, Box 355061  
University of Washington  
Seattle, Washington 98195

Home Address: 1612 Bigelow Avenue N.  
Seattle, Washington 98109

Telephones: Office: (206) 685-1005  
Department: (206) 685-2000  
Home: (206) 286-0969

E-mail: ratner@uweb.engr.washington.edu

Current Position: Michael L. and Myrna Darland Endowed Chair in Technology Commercialization  
Professor, Department of Bioengineering, University of Washington  
Professor, Department of Chemical Engineering, University of Washington  
Adjunct Professor, Department of Materials Science and Engineering, University of Washington

Education: Brooklyn College (Brooklyn, NY), B.S. in Chemistry, 1967  
Polytechnic Institute of Brooklyn (Brooklyn, NY), Ph.D. in Polymer Chemistry, 1972

### Appointments

1970-1972	National Institutes of Health Traineeship
1972-1973	Postdoctoral Fellow, Dept. of Chemical Engineering, University of Washington
1973-1975	Research Associate, Dept. of Chemical Engineering, University of Washington
1975-1979	Research Assistant Professor, Dept. of Chemical Engineering, University of Washington
1979-1984	Research Associate Professor, Dept. of Chemical Engineering, University of Washington
1984-1986	Associate Professor, Center for Bioengineering and Dept. of Chemical Engineering University of Washington
1986-present	Professor, Dept. of Bioengineering and Dept. of Chemical Engineering University of Washington
1996-present	Director, University of Washington Engineered Biomaterials (UWEB) University of Washington
2001-2004	Washington Research Foundation Endowed Professor of Bioengineering University of Washington
2002-present	Nanyang Professor, School of Mechanical & Production Engineering, Nanyang Technological University, Singapore
2004-2005	Robert F. Rushmer Professor of Bioengineering University of Washington
2004-present	Adjunct Professor, Dept. of Materials Science and Engineering University of Washington
2005-present	Michael L. and Myrna Darland Endowed Chair in Technology Commercialization

## Honors and Awards

1988	Clemson Award for Contributions to the Literature
1990	Burlington Resources Foundation Faculty Achievement Award for Outstanding Research
1991	Perkin Elmer Physical Electronics Award for Excellence in Surface Science
1993	Founding Fellow of the American Institute of Medical and Biological Engineering (AIMBE)
1993	Fellow, American Vacuum Society
1993	Fellow, Society for Biomaterials
1995	Chair, Gordon Research Conference on Biocompatibility & Biomaterials, July 23-28
1996	Van Ness Lecturer, Rensselaer Polytechnic Institute
1999	American Vacuum Society Distinguished Lecturer
1999	C.M.A. Stine Award for Materials Science, AIChE
2000	Science In Medicine Lecturer, University of Washington
2000	Joe Smith Distinguished Lecturer, University of California, Davis
2002	Elected to the National Academy of Engineering of the United States of America
2002	Medard W. Welch Award, American Vacuum Society
2004	Founders Award, Society for Biomaterials
2004	Distinguished Lecturer, University of Utah
2006	C. William Hall Award, Society for Biomaterials
2007	Bayer Lectureship, University of Akron
2008	BMES Pritzker Distinguished Lecturer Award

## Professional Organizations

American Association for the Advancement of Science (Fellow)  
American Chemical Society  
American Institute of Chemical Engineers (AIChE)  
    Director, Materials Engineering and Science Division (2005- )  
American Institute of Medical and Biological Engineering (Fellow, President 2002-2003)  
AVS The Science and Technology Society (Fellow)  
    Trustee of the AVS (elected) (2006- )  
Biomedical Engineering Society  
Controlled Release Society  
European Society For Biomaterials  
International Academy for Medical and Biological Engineering (Fellow)  
International Society for Contact Lens Research (Member of Council)  
Materials Research Society  
Society for Biomaterials (Fellow)  
    President 1990-1991  
The National Academies, Roundtable on Biomedical Engineering Materials and Applications (Chair 2003-present)  
Tissue Engineering and Regenerative Medicine International Society - North America Council (2005-2008)  
Tissue Engineering Society International (Vice President 2003-2005)  
Tissue Engineering Society of North America (President 2003-2005)

## Editorial Boards

American Journal of Drug Delivery  
BioInterphases (Editorial Advisory board) (2005- )  
Biomacromolecules (2000-2004)  
Biomaterials  
Biomedical Materials: Materials for Tissue Engineering and Regenerative Medicine (2005- )  
Colloids and Surfaces B: Biointerfaces  
Critical Reviews in Solid State and Materials Science  
Journal of Applied Biomaterials and Biomechanics (2003- )  
Journal of Biomaterials Science: Polymer Edition  
Journal of Biomedical Materials Research A - Associate Editor  
Journal of Biopharmaceutics and Biotechnology (2005- )  
JURIBE (Journal of Undergraduate Research In Bioengineering) - Editor

Nanobiotechnology (IEE)  
Nanomedicine  
Plasmas and Polymers - Founding Editor (journal ceased publication in 2004)  
Science and Technology of Advanced Materials (1996-2002)  
Surface Science  
Tissue Engineering and Regenerative Medicine (2006- )

### **Advisory Boards**

Asemblon, Inc. 2003-  
Bioengineering Program, Cornell University, 1999-  
Biomimetic MicroElectronic Systems (BMES) Engineering Research Center (USC), 2004-  
Center on Polymer Interfaces and Macromolecular Assemblies (CPIMA), Stanford U., 2000-  
Center for NanoBio Integration (CNBI) , International Advisory Committee, 2007-  
DexCom, Inc Science Advisory Board, 2003-  
Eli Lilly Ventures Scientific Advisory Board 2004-2006  
Genzyme Pharmaceuticals Science, 2001-2003  
Hope Heart Institute Board of Directors  
Institute of Materials Research and Engineering (IMRE), Singapore, 2002-2004  
Institute for Molecular Biophysics (Bar Harbor, Maine), 2004-  
Institute for Soldier Nanotechnologies, MIT, 2005-  
Lilly Venture Fund, 2004-  
NIBIB Intramural Research Program Scientific Director Search Committee, 2005  
Ratner Biomedical Group LLC 2006-  
Regentis Biomaterials Ltd. 2006-  
SageCliffe Foundation 2006-  
Tengion, Inc, 2004-

## PUBLICATIONS

### Refereed Papers

1. "Interaction of Urea with Poly(2-hydroxyethyl methacrylate) Hydrogels," B.D. Ratner and I.F. Miller, J. Polym. Sci., A-1, **10**, 2425-45, 1972.
2. "Transport Through Crosslinked Poly(2-hydroxyethyl methacrylate) Hydrogel Membranes," B.D. Ratner and I.F. Miller, J. Biomed. Mater. Res., **7**, 353-367, 1973.
3. "The Effect of Cupric Ion on the Radiation Grafting of N-vinyl-2-pyrrolidone and Other Hydrophilic Monomers to Silicone Rubber," B.D. Ratner and A.S. Hoffman, J. Appl. Polym. Sci., **18**, 3183-3204, 1974.
4. "Blood Compatibility of Radiation-Grafted Hydrogels," B.D. Ratner, A.S. Hoffman and J.D. Whiffen, Biomater. Med. Dev., Art. Org., **3**, 115-120, 1975.
5. "Cell Adhesion to Polymeric Materials: Implications with Respect to Biocompatibility," B.D. Ratner, T.A. Horbett, A.S. Hoffman and S. Hauschka, J. Biomed. Mater. Res., **9**, 407-422, 1975.
6. "Synthetic Hydrogels for Biomedical Applications," B.D. Ratner and A.S. Hoffman, in Hydrogels for Medical and Related Applications, ACS Symposium Series, No. **31**, J.D. Andrade, ed., American Chemical Society, Washington, D.C., 1-36, 1976.
7. "Radiation-Induced Co-Graft Polymerization of 2-Hydroxyethyl Methacrylate and Ethyl Methacrylate onto Silicone Rubber Films," T. Sasaki, B.D. Ratner and A.S. Hoffman, in Hydrogels for Medical and Related Applications, ACS Symposium Series, No. **31**, J.D. Andrade, ed., American Chemical Society, Washington, D.C., 283-294, 1976.
8. "The Thermodynamics of Water Sorption in Radiation-Grafted Hydrogels," B.N.L. Khaw, B.D. Ratner and A.S. Hoffman, in Hydrogels for Medical and Related Applications, ACS Symposium Series No. **31**, J.D. Andrade, ed., American Chemical Society, Washington, D.C., 295-304, 1976.
9. "A Flow Grafting Apparatus for Chemically Modifying the Luminal Surface of Polymeric Tubing," B.D. Ratner, T. Balisky and A.S. Hoffman, J. Bioeng., **1**, 115-120, 1977 (Communication).
10. "Radiation-Grafted Hydrogels for Biomaterial Applications as Studied by the ESCA Technique," B.D. Ratner, P.K. Weathersby, A.S. Hoffman, M.A. Kelly and L.H. Scharpen, J. Appl. Polym. Sci., **22**, 643-664, 1978.
11. "The Thrombogenicity of Radiation-Grafted Polymers as Measured by the *Vena Cava* Ring Test," B.D. Ratner, A.S. Hoffman and J.D. Whiffen, J. Bioeng., **2**, 313-323, 1978.
12. "Factors Influencing Platelet Consumption by Polyacrylamide Hydrogels," S.R. Hanson, L.A. Harker, B.D. Ratner and A.S. Hoffman, Ann. Biomed. Eng., **7**, 357-367, 1979.
13. "Blood Compatibility-Water Content Relationships for Radiation-Grafted Hydrogels," B.D. Ratner, A.S. Hoffman, S.R. Hanson, L.A. Harker and J.D. Whiffen, J. Polym. Sci. Polym. Symp., **66**, 363-375, 1979.
14. "An ESCA Study of Surface Contaminants on Glass Substrates for Cell Adhesion," B.D. Ratner, J.J. Rosen, A.S. Hoffman and L.H. Scharpen, in Surface Contamination: Genesis, Detection and Control, Vol. **2**, K.L. Mittal, ed., Plenum Press, New York, 669-686, 1979.
15. "The Radiation Grafting of Acrylamide to Polymer Substrates in the Presence of Cupric Ion. I. A Preliminary Study," A.S. Hoffman and B.D. Ratner, Radiat. Phys. Chem., **14**, 831-840, 1979.
16. "*In Vivo* Evaluation of Artificial Surfaces with a Nonhuman Primate Model of Arterial Thrombosis," S.R. Hanson, L.A. Harker, B.D. Ratner and A.S. Hoffman, J. Lab. Clin. Med., **95**, 289-304, 1980.

17. "Characterization of Graft Polymers for Biomedical Applications," B.D. Ratner, *J. Biomed. Mater. Res.*, **14**, 665-687, 1980.
18. "ESCA and SEM Studies on Polyurethanes for Biomedical Applications," B.D. Ratner, in Photon, Electron and Ion Probes of Polymer Structure and Properties, *ACS Symposium Series*, No. 162, D.W. Dwight, T.J. Fabish and H.R. Thomas, eds., American Chemical Society, Washington, D.C., 371-382, 1981.
19. "Characterization of Hydrophilic-Hydrophobic Polymeric Surfaces by Contact Angle Measurements," Y.C. Ko, B.D. Ratner and A.S. Hoffman, *J. Coll. Interf. Sci.*, **82**, 25-37, 1981.
20. "Analysis of the Organization of Protein Films on Solid Surfaces by ESCA," B.D. Ratner, T.A. Horbett, D. Shuttleworth and H.R. Thomas, *J. Coll. Interf. Sci.*, **83**, 630-642, 1981.
21. "Thrombotic Events on Grafted Polyacrylamide-Silastic Surfaces as Studied in a Baboon," A.S. Hoffman, T.A. Horbett, B.D. Ratner, S.R. Hanson, L.A. Harker and L.O. Reynolds, in Biomaterials: Interfacial Phenomena and Applications, *Advances in Chemistry Series* No. 199, S.L. Cooper and N.A. Peppas, eds., American Chemical Society, Washington, D.C., 59-80, 1982.
22. "Surface Characterization of Materials for Blood Contact Applications," B.D. Ratner, in Biomaterials: Interfacial Phenomena and Applications, *Advances in Chemistry Series* No. 199, S.L. Cooper and N.A. Peppas, eds., American Chemical Society, Washington, D.C., 9-23, 1982.
23. "Adsorption of Proteins from Artificial Tear Solutions to Poly(methyl methacrylate-2-hydroxyethyl methacrylate) Copolymers," F.H. Royce, Jr., B.D. Ratner and T.A. Horbett, in Biomaterials: Interfacial Phenomena and Applications, *Advances in Chemistry Series* No. 199, S.L. Cooper and N.A. Peppas, eds., American Chemical Society, Washington, D.C., 453-462, 1982.
24. "Analysis of Surface Contaminants on Intraocular Lenses," B.D. Ratner, *Arch. Ophthalmol.*, **101**, 1434-1438, 1983.
25. "ESCA Studies of Extracted Polyurethanes and Polyurethane Extracts: Biomedical Implications," B.D. Ratner, in Physicochemical Aspects of Polymer Surfaces, Vol. II, K.L. Mittal, ed., Plenum Press, New York, 969-983, 1983.
26. "Chemical Modification of Kevlar Surfaces for Improved Adhesion to Epoxy Matrices: I. Surface Characterization," T.S. Keller, A.S. Hoffman, B.D. Ratner and B.J. McElroy, in Physicochemical Aspects of Polymer Surfaces, Vol. II, K.L. Mittal, ed., Plenum Press, New York, 861-879, 1983.
27. "Surface Characterization of Biomaterials by Electron Spectroscopy for Chemical Analysis," B.D. Ratner, *Ann. Biomed. Eng.*, **11**, 313-336, 1983.
28. "Evaluation of the Blood Compatibility of Synthetic Polymers: Consensus and Significance," B.D. Ratner, in Contemporary Biomaterials: Materials and Host Response, Clinical Applications, New Technology and Legal Aspects, J.W. Boretos and M. Eden, eds., Noyes Publications, Park Ridge, NJ, 193-204, 1984.
29. "Analysis of Polymer Surfaces by SIMS. 4. A Study of Some Acrylic Homo- and Co-Polymers," D. Briggs, M.J. Hearn and B.D. Ratner, *Surf. Interf. Anal.*, **6**, 184-192, 1984.
30. "Radiation-Grafted Polymers for Biomedical Applications. I. 2-Hydroxyethyl Methacrylate: Ethyl Methacrylate Grafting onto Low Density Polyethylene Films," D. Cohn, A.S. Hoffman and B.D. Ratner, *J. Appl. Polym. Sci.*, **29**, 2645-2663, 1984.
31. "XPS Studies on the Organization of Adsorbed Protein Films on Fluoropolymers," R.W. Paynter, B.D. Ratner, T.A. Horbett and H.R. Thomas, *J. Coll. Interf. Sci.*, **101**, 233-245, 1984.
32. "Glucose Sensitive Membranes for Controlled Delivery of Insulin," G. Albin, T.A. Horbett and B.D. Ratner, *J. Controlled Release*, **2**, 153-164, 1985.
33. "Hydrophilic-Hydrophobic Copolymers as Cell Substrates: Effect on 3T3 Cell Growth Rates," T.A. Horbett, M.B. Schway and B.D. Ratner, *J. Coll. Interf. Sci.*, **104**, 28-39, 1985.

34. "Glucose-sensitive Membranes Containing Glucose Oxidase: Activity, Swelling and Permeability Studies," J. Kost, T.A. Horbett, B.D. Ratner and M. Singh, J. Biomed. Mater. Res., 19, 1117-1133, 1985.
35. "Rat Peritoneal Macrophage Adhesion to Hydroxyethyl Methacrylate-Ethyl Methacrylate Copolymers and Hydroxystyrene-Styrene Copolymers," A.J. Lentz, T.A. Horbett, L. Hsu, B.D. Ratner and A.S. Hoffman, J. Biomed. Mater. Res., 19, 1101-1115, 1985.
36. "The Kinetics of Baboon Fibrinogen Adsorption to Polymers: *In Vitro* and *In Vivo* Studies," T.A. Horbett, C.M. Cheng, B.D. Ratner, A.S. Hoffman and S.R. Hanson, J. Biomed. Mater. Res., 20, 739-772, 1986.
37. "The Biocompatibility of Solution Cast and Acetone Extracted Cast Biomer™," R.E. Marchant, J.M. Anderson, A. Hiltner, E.J. Castillo, J. Gleit and B.D. Ratner, J. Biomed. Mater. Res., 20, 799-815, 1986.
38. "Surface Structure of Segmented Poly(ether urethanes) and Poly(ether urethane ureas) with Various Perfluoro Chain Extenders. An X-ray Photoelectron Spectroscopic Investigation," S.C. Yoon and B.D. Ratner, Macromolecules, 19, 1068-1079, 1986.
39. "Preparation and Properties of Plasma-Deposited Films with Surface Energies Varying over a Wide Range," Y. Haque and B.D. Ratner, J. Appl. Polym. Sci., 32, 4369-4381, 1986.
40. "Radiation-Grafted Polymers for Biomaterial Applications. II. The Morphology and Structure of 2-Hydroxyethyl Methacrylate and Ethyl Methacrylate Homopolymer Grafts," D. Cohn, A.S. Hoffman and B.D. Ratner, J. Appl. Polym. Sci., 33, 1-20, 1987.
41. "A Comparison of Two Angular Dependent ESCA Algorithms Useful for Constructing Depth Profiles of Surfaces," R.S. Yih and B.D. Ratner, J. Electron Spectrosc. Relat. Phenom., 43, 61-82, 1987.
42. "SIMS and XPS Studies of Polyurethane Surfaces. 2. Polyurethanes with Fluorinated Chain Extenders," M.J. Hearn, D. Briggs, S.C. Yoon and B.D. Ratner, Surf. Interface. Anal., 10, 384-391, 1987.
43. "Adsorption of Proteins from Artificial Tear Solutions to Contact Lens Materials," J.L. Bohnert, T.A. Horbett, B.D. Ratner and F.H. Royce, Jr., Invest. Ophthalmol. Visual Sci., 29, 362-373, 1988.
44. "A Semi-quantitative SIMS analysis of the surfaces of random ethyl methacrylate: hydroxyethyl methacrylate copolymer films", D. Briggs and B.D. Ratner, Polymer Communications, 29, 6-8, 1988.
45. "Cell Adhesion to a Series of Hydrophilic-Hydrophobic Copolymers Studied with a Spinning Disc Apparatus," T.A. Horbett, J.J. Waldburger, B.D. Ratner and A.S. Hoffman, J. Biomed. Mater. Res., 22, 383-404, 1988.
46. "Enzymatic and Oxidative Degradation of Polyurethanes," B.D. Ratner, K.W. Gladhill, and T.A. Horbett, J. Biomed. Mater. Res., 22, 509-527, 1988.
47. "Surface and Bulk Structure of Segmented Poly(ether urethanes) with Perfluoro Chain Extenders. 2. FTIR, DSC and X-ray Photoelectron Spectroscopic Studies," S.C. Yoon and B.D. Ratner, Macromolecules, 21, 2392-2400, 1988.
48. "Surface and Bulk Structure of Segmented Poly(ether urethanes) with Perfluoro Chain Extenders. 3. Effects of Annealing, Casting Solvent and Casting Conditions," S.C. Yoon and B.D. Ratner, Macromolecules, 21, 2401-2404, 1988.
49. "The Synthesis, Bulk Characterization and Surface Characterization of p-Hydroxystyrene/Styrene Copolymers," D. Majumdar and B.D. Ratner, J. Polym. Sci.: Part A: Polym. Chem., 26, 1991-2002, 1988.
50. "Role of Negative Ions in the RF Plasma Deposition of Fluoropolymer Films from Perfluoropropane," Y. Haque and B.D. Ratner, J. Polym. Sci.: Part B: Polym. Phys., 26, 1237-1249, 1988.
51. "Interaction of Blood with Gas Discharge Treated Vascular Grafts", D. Kiaei, A.S. Hoffman, B.D. Ratner, T.A. Horbett, and L.O. Reynolds, J., Appl. Poly. Sci.: Appl. Poly. Symp., 42, 269, 1988.

52. "X-ray Photoelectron Spectroscopy Characterization of Polymers for Biomedical Applications," D.G. Castner and B.D. Ratner, J. Vac. Sci. Technol. A, **6**, 964-965, 1988.
53. "SIMS and XPS Studies of Polyurethane Surfaces. 1. Preliminary Studies," M.J. Hearn, B.D. Ratner and D. Briggs, Macromolecules, **21**, 2950-2959, 1988.
54. "Enhancement of Serum Fibronectin Adsorption and the Clonal Plating Efficiencies of Swiss Mouse 3T3 Fibroblast and MM14 Mouse Myoblast Cells on Polymer Substrates Modified by Radio Frequency Plasma Deposition," J.A. Chinn, T.A. Horbett, B.D. Ratner, M.B. Schway, Y. Haque and S.D. Hauschka, J. Coll. Interf. Sci., **127**, 67-87, 1989.
55. "Relating the Surface Properties of Intraocular Lens Materials to Endothelial Cell Adhesion Damage," N.B. Mateo and B.D. Ratner, Inv. Ophthalmol. Vis. Sci., **30**, 853-860, 1989.
56. "IR Spectral Changes of Bovine Serum Albumin Upon Surface Adsorption," T.J. Lenk, B.D. Ratner, R.M. Gendreau and K.K. Chittur, J. Biomed. Mat. Res., **23**, 549-569, 1989.
57. "Synthesis and ESCA Surface Studies of Octadecyl Chain-Extended Polyurethanes," R. Rahman and B.D. Ratner, J. Polym. Sci., Part A: Polymer Chemistry, **27**, 2673-2683, 1989.
58. "Determining Depth Profiles from Angle Dependent X-ray Photoelectron Spectroscopy: The Effects of Analyzer Lens Aperture Size and Geometry", B.J. Tyler, D.G. Castner, B.D. Ratner, J. Vac. Sci. Technol. A, **7**, 1646-1654, 1989.
59. "Regularization: A Stable and Accurate Method for Generating Depth Profiles from Angle Dependent XPS Data," B.J. Tyler, D.G. Castner, and B.D. Ratner, Surf. Interface. Anal., **14**, 443-450, 1989.
60. "Adhesion and Aggregation of Thrombin Prestimulated Human Platelets: Evaluation of a Series of Biomaterials Characterized by ESCA," I.A. Feuerstein and B.D. Ratner, Biomaterials, **11**, 127-132, 1990.
61. "Surface Characterization of a Series of Polyurethanes by X-ray Photoelectron Spectroscopy and Contact Angle Methods," D.G. Castner, B.D. Ratner and A.S. Hoffman, J. Biomat. Sci., Polymer Edn. **1**, 191-206, 1990.
62. "Near-infrared Spectroscopic Analyses of Poly(ether urethane urea) Block Copolymers, I. Bulk Composition," C.E. Miller, P.G. Edelman, B.D. Ratner, Applied Spectroscopy, **44**, 576-580, 1990.
63. "Near-infrared Spectroscopic Analyses of Poly(ether urethane urea) Block Copolymers, II. Bulk Composition," C.E. Miller, P.G. Edelman, B.D. Ratner, Applied Spectroscopy, **44**, 581-586, 1990.
64. "Surface Characterization of a Poly(styrene/p-hydroxystyrene) Copolymer Series using XPS, Static SIMS, and Chemical Derivatization Techniques," A. Chilkoti, D.G. Castner, B.D. Ratner and D. Briggs, J. Vac. Sci. Technol. A, **8**, 2274-2282, 1990.
65. "Poly(dimethylsiloxane)-Poly(ethylene oxide)-Heparin Block Copolymers III: Surface and Bulk compositional Differences," D.W. Grainger, T. Okano, S.W. Kim, D.G. Castner, B.D. Ratner, D. Briggs and Y.K. Sung, Biomed. Mater. Res. **24**, 547-571, 1990.
66. "Biomolecules and Surfaces," B. D. Ratner, D.G. Castner, T.A. Horbett, T.J. Lenk, K.B. Lewis and R.J. Rapoza, J. of Vac. Sci. and Tech. A, **8**, 2306-2317, 1990.
67. "Surface Characterization of Butyl Methacrylate Polymers with XPS and Static SIMS," D.G. Castner and B.D. Ratner, Surf. Interf. Anal. **15**, 479-486, 1990.
68. "Characterization of Alkyl Grafted Polyurethane Block Copolymers by Variable Takeoff Angle X-ray Photoelectron Spectroscopy," T.G. Grasel, D.G. Castner, B.D. Ratner, and S.L. Cooper, J. Biomed. Mater. Res. **24**, 605-620, 1990.

69. "Radiofrequency Plasma Deposition of Oxygen-containing Films on Polystyrene and Poly(ethylene terephthalate) Substrates Improves Endothelial Cell Growth," S.I. Ertel, B.D. Ratner, and T.A. Horbett, *J. Biomed. Mater. Res.*, 24, 1637-1659, 1990.
70. "The Use of Cryogenic Substrate Temperatures to Control Film Chemistry in Plasma Deposition of Organic Thin Films," G.P. Lopez and B.D. Ratner, *J. Appl. Polym. Sci. Appl. Polym. Symp.*, 46, 493-510, 1990.
71. "Characterization of the Poly(ether ether ketone)-Copper Interface: Preliminary Electron Spectroscopy for Chemical Analysis," R.D. McElhaney, D.G. Castner, and B.D. Ratner, in *Metallization of Polymers*, ACS Symposium Series, No. 440, E. Sacher, J. Pireaux, S.P. Kowalczyk, eds., American Chemical Society, Washington, D.C., 370-378, 1990.
72. "Surface and Bulk Structure of Segmented Poly(ether urethanes) with Perfluoro Chain Extenders. 4. Role of Hydrogen Bonding on Thermal Transitions," S.C. Yoon, Y.K. Sung, and B.D. Ratner, *Macromolecules*, 23, 4351-4356, 1990.
73. "Static Secondary Ion Mass Spectrometry and X-ray Photoelectron Spectroscopy of Deuterium and Methyl Substituted Polystyrene," A. Chilkoti, D.G. Castner and B.D. Ratner, *Applied Spectroscopy*, 45, 209-217, 1991.
74. "Post-adsorptive Transitions in Fibrinogen Adsorbed to Biomer: Changes in Baboon Platelet Adhesion, Antibody Binding, and Sodium Dodecyl Sulfate Elutability," J.A. Chinn, S.E. Posso, T.A. Horbett and B.D. Ratner, *J. Biomed. Mater. Res.*, 25, 535-555, 1991.
75. "Baboon Fibrinogen Adsorption and Platelet Adhesion to Polymeric Materials," J.A. Chinn, T.A. Horbett and B.D. Ratner, *Thrombosis and Hemostasis*, 65, 608-617, 1991.
76. "Plasma-deposited Polymeric Films Prepared from Carbonyl-containing Volatile Precursors: XPS Chemical Derivatization and Static SIMS Surface Characterization," A. Chilkoti, B.D. Ratner, and D. Briggs, *Chem. Mater.*, 3, 51-61, 1991.
77. "Infrared Spectroscopic Studies of Time-Dependent Changes in Fibrinogen Adsorbed to Polyurethanes," T.J. Lenk, T.A. Horbett, B.D. Ratner, and K.K. Chittur, *Langmuir*, 7, 1755-1764, 1991.
78. "XPS O1s Binding Energies for Polymers Containing Hydroxyl, Ether, Ketone and Ester Groups," G. P. Lopez, D. G. Castner, and B.D. Ratner, *Surf. Interface. Anal.*, 17, 267-272, 1991.
79. "Substrate Temperature Effects on Film Chemistry in Plasma Deposition of Organics. 1. Nonpolymerizable Precursors," G.P. Lopez and B.D. Ratner, *Langmuir*, 7, 766-773, 1991.
80. "An X-ray Photoelectron Spectroscopic Investigation of the Selectivity of Hydroxyl Derivatization Reactions," A. Chilkoti and B.D. Ratner, *Surf. Interf. Anal.*, 17, 567-574, 1991.
81. "Direct Emission of Molecular Fragments during the Sputtering of Poly (4-hydroxystyrene) and Determination of Ion Structures Using Tandem-SIMS," G.J. Leggett, A. Chilkoti, D.G. Castner, B.D. Ratner, and J.C. Vickerman, *Inter. J. Mass Spectrom. Ion Proc.*, 108, 29-39, 1991.
82. "Endothelial Cell Growth on Oxygen-containing Films Deposited by Radio-frequency Plasmas: The Role of Surface Carbonyl Groups," S.I. Ertel, A. Chilkoti, T.A. Horbett, and B.D. Ratner, *J. Biomat. Sci., Polym. Ed.*, 3, 163-183, 1991.
83. "Static Secondary Ion Mass Spectrometric Investigation Of the Surface Structure of Organic Plasma-Deposited Films Prepared from Stable Isotope-Labeled Precursors Part I. Carbonyl Precursors," A. Chilkoti, B.D. Ratner, and D. Briggs, *Anal. Chem.*, 63, 1612-1620, 1991.
84. "Photoenhancement of Platelet Adhesion to Biomaterial Surfaces Observed with Epi-Fluorescent Video Microscopy (EVM)", C.L. Haycox, B.D. Ratner, and T.A. Horbett, *J. Biomed. Mater. Res.*, 25, 1317-1320, 1991.
85. "The Adsorption and Elutability of Albumin, IgG and Fibronectin on Radio-Frequency Plasma Deposited Polystyrene," S.I. Ertel, B.D. Ratner, and T.A. Horbett, *J. Coll. Interf. Sci.*, 147, 433-442, 1991.

86. "TFE-Plasma Polymerized Dermal Sheep Collagen for the Repair of Abdominal Wall Defects," J.S. van der Laan, G.P. Lopez, P.B. van Wachem, P. Nieuwenhuis, B.D. Ratner, R.P. Bleichrodt, and J.M. Schakenraad, Int. J. Artif. Org., **14**(10), 661-666, 1991.
87. "Variations between Biomer™ Lots: 1. Significant Differences in Surface Chemistry of Two Lots of a Commercial Polyetherurethane," B.J. Tyler, B.D. Ratner, D.G. Castner, and D. Briggs, J. Biomed. Mater. Res., **26**, 273-289, 1992.
88. "Glow Discharge Plasma Deposition of Tetraethylene Glycol Dimethyl Ether for Fouling-resistant Biomaterial Surfaces," G.P. Lopez, B.D. Ratner, C.D. Tidwell, C.L. Haycox, R. J. Rapoza, T.A. Horbett, J. Biomed. Mater. Res., **26**(4), 415-439, 1992.
89. "A Tandem SIMS Study of Poly(vinyl methyl ether)," G.J. Leggett, A. Chilkoti, B.D. Ratner, J.C. Vickerman, Surf. Interf. Anal., **18**, 210-216, 1992.
90. "Post-adsorptive Transitions in Fibrinogen Adsorbed to Polyurethanes: Changes in Antibody Binding and Sodium Dodecyl Sulfate Elutability," J.A. Chinn, S.E. Posso, T.A. Horbett and B.D. Ratner, J. Biomed. Mater. Res., **26**(6), 757-778, 1992.
91. "The Adsorption of Baboon Fibrinogen and the Adhesion of Platelets to a Thin Film Polymer Deposited by Radio-Frequency Glow Discharge of Allylamine," J.A. Chinn, B.D. Ratner and T.A. Horbett, Biomaterials, **13**(5), 322-332, 1992.
92. "Static Secondary Ion Mass Spectrometry of Organic Plasma Deposited Films Created from Stable Isotope-Labeled Precursors. Part II. Mixtures of Acetone and Oxygen," A. Chilkoti, B.D. Ratner, D. Briggs and F. Reich, J. Polym. Sci.: Part A: Polym. Chem., **30**, 1261-1278, 1992.
93. "Spin Cast Poly (vinyl isobutyl ether) Film on Glass Substrate by XPS," M. Ackert and B.D. Ratner, Surface Sci. Spectra, **1**(1), 96-99, 1992.
94. "Spin Cast Poly (*t*-butyl methacrylate) Film on Glass Substrate by XPS," M. Ackert and B.D. Ratner, Surface Sci. Spectra, **1**(1), 104-107, 1992.
95. "Spin Cast Polycarbonate Film on Glass Substrate by XPS," M. Ackert and B.D. Ratner, Surface Sci. Spectra, **1**(1), 108-111, 1992.
96. "Substrate Temperature Effects on Film Chemistry in Plasma Depositions of Organics. II: Polymerizable Precursors," G.P. Lopez and B.D. Ratner, J. Polym. Sci.: Part A: Polym. Chem., **A30**, 2415-2425, 1992.
97. "Substrate Temperature Effects on Film Chemistry in Plasma Deposition of Organics. III: Analysis by Static Secondary Ion Mass Spectrometry," G.P. Lopez, A. Chilkoti, D. Briggs, B.D. Ratner, J. Polym. Sci.: Part A: Polym. Chem., **30**, 2427-2441, 1992.
98. "Analysis of Polymer Surfaces by SIMS: Part 15. Oxygen-Functionalized Aliphatic Homopolymers," A. Chilkoti, B.D. Ratner and D. Briggs, Surf. Interf. Anal., **18**, 604-618, 1992.
99. "Surface Characterization of 2-Hydroxyethyl Methacrylate/Styrene Copolymers by Angular Dependent X-ray Photoelectron Spectroscopy and Secondary Ion Mass Spectrometry," D.G. Castner, B.D. Ratner, D.W. Grainger, S.W. Kim, D. Briggs, T. Okano, K. Suzuki, and S. Nakahama, J. Biomat. Sci., Polymer Edn, **3**(6), 463-480, 1992.
100. "Plasma-Deposited Polymer Coatings for Scanning Tunneling Microscope Tips," K.B. Lewis, B.D. Ratner, J. Vac. Sci. Technol., **B 10**(5), 2331-2332, 1992.
101. "Contemporary Methods for Characterizing Complex Biomaterial Surfaces," B.D. Ratner, A. Chilkoti, and D.G. Castner, Clinical Materials, **11**, 25-36, 1992.
102. "Angular-Resolved ESCA Studies of Cadmium Arachidate Monolayers on Si (100): Inelastic Mean-Free Path and Depth Profile Analysis," S.R. Letellier, V. Vogel, B.D. Ratner, D. Leach-Scampavia, in Biomolecular Materials,

MRS Symposium Proceedings, Vol. 292, C. Viney, S.T. Case, and J.H. Waite, Materials Research Society, Pittsburgh, PA, pp. 115-120, 1993.

103. "Variations between Biomer™ Lots: 2. The Effect of Differences Between Lots on *In Vitro* Enzymatic and Oxidative Degradation of a Commercial Polyurethane", B.J. Tyler and B.D. Ratner, J. Biomed. Mater. Res., 27(3), 327-334, 1993.
104. "ESCA Surface Characterization of Four IUPAC Reference Polymers," B.D. Ratner, D. Leach-Scampavia, and D.G. Castner, Biomaterials, 14(2), 148-152, 1993.
105. "Determination of Surface Structure and Orientation of Polymerized Tetrafluoroethylene Films by Near-Edge X-ray Absorption Fine Structure, X-ray Photoelectron Spectroscopy, and Static Secondary Ion Mass Spectrometry," D.G. Castner, K.B. Lewis, D.A. Fischer, B.D. Ratner, J.L. Gland, Langmuir, 9(2), 537-542, 1993.
106. "Static Secondary Ion Mass Spectrometry of Adsorbed Proteins," D.S. Mantus, B.D. Ratner, B.A. Carlson, and J.F. Moulder, Anal. Chem., 65, 1431-1438, 1993.
107. "Effect of Polyol Type on the Surface Structure of Sulfonate-Containing Polyurethanes," J.H. Silver, K.B. Lewis, B.D. Ratner, S.L. Cooper, Biomed. Mater. Res. 27, 735-745, 1993.
108. "Surface Analysis of Hydrogel Contact Lenses by ESCA," D.E. Hart, M. DePaolis, B.D. Ratner and N.B. Mateo, CLAO Journal, 19(3), 169-173, 1993.
109. "Plasma Deposition of Ultrathin Films of Poly(2-hydroxyethyl methacrylate): Surface Analysis and Protein Adsorption Measurements." G.P. Lopez, B.D. Ratner, R.J. Rapoza and T.A. Horbett, Macromolecules, 26, 3247-3253, 1993.
110. "Characterization of Biomaterial Surfaces," B.D. Ratner, Cardiovascular Pathol., 2 Suppl. (3), 87S-100S, 1993.
111. "Observation of Surface Restructuring of Polymers Using ESCA," K.B. Lewis and B.D. Ratner, J. Coll. Interf. Sci. 158, 77-85, 1993.
112. "*In Vitro* Platelet Interactions in Whole Human Blood Exposed to Biomaterial Surfaces: Insights on Blood Compatibility," C.L. Haycox and B.D. Ratner, J. Biomed. Mater. Res., 27, 1181-1193, 1993.
113. "Static Secondary Ion Mass Spectrometric Investigation of the Surface Chemistry of Organic Plasma-Deposited Films Created from Oxygen-Containing Precursors. 3. Multivariate Statistical Modeling," A. Chilkoti, B.D. Ratner, and D. Briggs, Anal. Chem., 65, 1736-1745, 1993.
114. "Analysis of Polymer Surfaces by SIMS: 16. Investigation of Surface Crosslinking in Polymer Gels of 2-Hydroxyethyl Methacrylate," A. Chilkoti, G.P. Lopez, B.D. Ratner, M.J. Hearn, and D. Briggs, Macromolecules, 26, 4825-4832, 1993.
115. "X-ray Photoelectron Spectroscopy of Iodine-Doped Nonconjugated Polymers," A. Chilkoti and B.D. Ratner, Chem. Mater., 5, 786-792, 1993.
116. "Surface Properties of RGD-Peptide Grafted Polyurethane Block Copolymers: Variable Take-off Angle and Cold-Stage ESCA Studies," H.-B. Lin, K.B. Lewis, D. Leach-Scampavia, B.D. Ratner, and S.L. Cooper, J. Biomat. Sci.: Polym. Ed. 4(3), 183-198, 1993.
117. "Immobilization of Polyethylene Oxide Surfactants for Non-fouling Biomaterial Surfaces Using an Argon Glow Discharge Treatment," M.-S. Sheu, A.S. Hoffman, B.D. Ratner, J. Feijen, and J.M. Harris, J. Adhesion Sci. Technol. 7, 1065-1076, 1993.
118. "Advances in X-ray Photoelectron Spectroscopy Instrumentation and Methodology: Instrument Evaluation and New Techniques with Special Reference to Biomedical Studies," B.D. Ratner and D.G. Castner, Colloids and Surfaces B: Biointerfaces 2, 333-346, 1994.

119. "In Vitro Study of the Intrinsic Toxicity of Synthetic Surfaces to Cells," S.I. Ertel, B.D. Ratner, A. Kaul, M.B. Schway, and T.A. Horbett, J. Biomed. Mater. Res. **28**, 667-675, 1994.
120. "Surface and Bulk Structure of Segmented Poly(Ether Urethanes) with Perfluoro Chain Extenders. 5. Incorporation of Polydimethylsiloxane and Polyisobutylene Macroglycols," S.C. Yoon, B.D. Ratner, B. Ivan, and J.P. Kennedy, Macromolecules, **27**, 1548-1554, 1994.
121. "Developing Correlations between Fibrinogen Adsorption and Surface Properties Using Multivariate Statistics," V.H. Perez-Luna, T.A. Horbett, and B.D. Ratner, J. Biomed. Mater. Res. **28**, 1111-1126, 1994.
122. "Two-Dimensional Assembly of Purines and Pyrimidines on Au(111)," T. Boland and B.D. Ratner, Langmuir, **10**, 3845-3852, 1994.
123. "Oxidative Degradation of Biomer<sup>TM</sup> Fractions Prepared By Using Preparative-Scale Gel Permeation Chromatography," B.J. Tyler and B.D. Ratner, J. Biomat. Sci.: Polymer Edn., **6**, 359-373, 1994.
124. "Static Secondary Ion Mass Spectrometric Investigation of the Glow-Discharge-Treated Surfaces," M.-S. Sheu, A.S. Hoffman, B.D. Ratner, and J. Feijen, J. Appl. Polym. Sci.: Appl. Polym. Sympos., **54**, 29-40, 1994.
125. "Laboratory Preparation of Plasticware to Support Cell Culture: Surface Modification by Radio Frequency Glow Discharge Deposition of Organic Vapors," J.A. Chinn, T.A. Horbett, and B.D. Ratner, J. Tissue Culture Methods, **16**:155-159, 1994.
126. "Characterization of Plasma-Deposited Styrene Films by XPS and Static SIMS," G.J. Leggett, B.D. Ratner, J.C. Vickerman, Surf. Interface Anal., **23**, (1), 22-28, 1995.
127. "Investigating the Relationship Between Surface Chemistry and Endothelial Cell Growth: Partial Least Squares Regression of the Static Secondary Ion Mass Spectra of Oxygen-Containing Plasma-Deposited Films," A. Chilkoti, A.E. Schmierer, V.H. Perez-Luna, B.D. Ratner, Analytical Chemistry, **67**, (17) 2883-2891, 1995.
128. "Amphiphilic Networks: VIII. Surface Characterization," D.Park, B.Keszler, V.Galiatsatos, J.P. Kennedy, B.D. Ratner, Macromolecules, **28**(8), 2595-2601, 1995.
129. "Surface Modification of Polymers: Chemical, Biological & Surface Analytical Challenges," B.D. Ratner, Biosensors and Bioelectronics, **10**, 797-804, 1995.
130. "Direct Measurement by Hydrogen Bonding in DNA Nucleotide Bases by Atomic Force Microscopy," T. Boland and B.D. Ratner, Proceedings of the National Academy of Science, **92**, 5297-5301, 1995.
131. "Silicone Derivatives for Contact Lenses: Functionalization, Chemical Characterization and Cell Compatibility Assessment," V. Migonney, M.D. Lacroix, B.D. Ratner, M. Jozefowicz, J. Biomater. Sci. Polymer. Edn., Vol. 7, No. 3, 265-275, 1995.
132. "Surface Properties and Restructuring of a Crosslinked Polyurethane-Poly(amido-amine) Network,' A. Magnani, R.Barbucci, K.B. Lewis, D. Leach-Scampavia and B.D. Ratner, J. Mat. Chem., **5** (9) 1321-1330 1995.
133. "The Relationship Between Ligand-Binding Thermodynamics and Protein-Ligand Interaction Forces by Atomic Force Microscopy," A. Chilkoti, T. Boland, P. Stayton, B.D. Ratner, Biophysical Journal, **69**, 2125-2130, 1995.
134. "Glucose-Sensitive Membrane Coated Porous Filters for Control of Hydraulic Permeability and Insulin Delivery from a Pressurized Reservoir," S. Cartier, T.A. Horbett, B.D. Ratner, Journal of Membrane Science, **106**, 17-24, 1995.
135. "Imaging Fibrinogen Adsorbed on Noble Metal Surfaces with Scanning Tunneling Microscopy: Correlation of Images with Electron Spectroscopy for Chemical Analysis, Secondary Ion Mass Spectrometry, and Radiolabeling Studies," K.B. Lewis and B.D. Ratner, Colloids and Surfaces B: Biointerfaces, **7**, 259-269, 1996.
136. "Derivatization of Carboxylic Acid-Containing Polymers for Quantitative XPS Analysis," M.R. Alexander, P.V. Wright, B.D. Ratner, Surface Interface Analysis, Vol.24, 217-220, 1996.

137. "Molecular Adsorption and the Chemistry of Plasma-Deposited Thin Organic Films: Deposition of Oligomers of Ethylene Glycol," G.P. Lopez and B.D. Ratner, Plasma and Polymers, Vol. 1 (2), 127-152, 1996.
138. "Surface Characterization of Plasma Deposited Organic Thin Films," E. Johnston, B.D. Ratner, J. Elect. Spectrosc. Rel. Phenom., 81, 303-317, 1996.
139. "Pharmacology and Controlled Release of Hirudin for Cardiovascular Disorders," D.D. Kim, T.A. Horbett, M.M. Takeno, B.D. Ratner, Cardiovascular Pathology, Vol. 5, (6), 1996.
140. "Surface Chemical Composition and Fibrinogen Adsorption-Retention of Fluoropolymer Films Deposited from an RF Glow Discharge," P. Favia, V.H. Perez-Luna, T. Boland, D.G. Castner, B.D. Ratner, Plasmas and Polymers, Vol. 1, (4), 299-326, 1996.
141. "Surface Characterization of Tyrosine-Derived Polycarbonates," V.H. Perez-Luna, K.A. Hooper, J. Kohn, B.D. Ratner, Journal Applied Polymers Science, Vol. 63 (11), 1467-1479, 1997.
142. "A New Method for Straightening DNA Molecules for Optical Restriction Mapping," M.D. Garrison, B.D. Ratner, B.J. Trask and D. L. Miller, Nucleic Acids Research, Vol. 25 (5), 1064-1070, 1997.
143. "The Engineering of Biomaterials Exhibiting Recognition and Specificity," B.D. Ratner, Journal of Molecular Recognition, 9, 617-625, 1997.
144. "Endothelial Cell Growth and Protein Adsorption on Terminally Functionalized, Self-Assembled Monolayers of Alkanethiolates on Gold," C.D. Tidwell, S.I. Ertel, B.D. Ratner, S. Atre, B. Tarasevich, D. Allara, Langmuir, 13(13), 3404-3413, 1997.
145. "Characterization of Poly (2-Hydroxyethyl Methacrylate) (PHEMA) by XPS," D.G. Castner, B.D. Ratner, A. Hirao, S. Nakahama, Surface Science Spectra, 4(1), 14-20, 1997.
146. "An Investigation of Polyurethane Surface Chemistry Using XPS," S.C. Porter, B.D. Ratner, Surface Science Spectra, 4(1), 90-95, 1997.
147. "Scanning Probe Microscopy for the Characterization of Biomaterials and Biological Interactions," M.D. Garrison, B.D. Ratner, Annals of the New York Academy of Sciences, Vol. 831, 101-113, 1997.
148. "Glow Discharge Plasma Deposition (GDPD) Technique for the Local Controlled Delivery of Hirudin from Biomaterials," D-D. Kim, M. Takeno, B.D. Ratner, T.A. Horbett, Pharmaceutical Research, Vol. 15, (5), 1998.
149. "Multitechnique Surface Characterization of Derivatization Efficiencies for Hydroxyl-Terminated Self-Assembled Monolayers," S. Pan, D.G. Castner, B.D. Ratner, Langmuir, Vol. 14(13), 3545-3550, 1998.
150. "Template-Assisted Nano-Patterning of Solid Surfaces," M.S. Boechl, T. Baas, A. Fujita, K.-O. Hwang, A.L. Bramblett, B.D. Ratner, J.W. Rogers, T. Sasaki, Biopolymers, 47 (2), 185-193, 1998.
151. "Rapid Postadsorptive Changes in Fibrinogen Adsorbed from Plasma to Segmented Polyurethanes," T. A. Horbett, K.W. Cooper, K.R. Lew, B.D. Ratner, Journal of Biomaterials Science, Polymer Edition, Vol. 9, (10) 1071-1087, 1998.
152. "Chemical Modification of Atomic Force Microscope Cantilever Tips," R. Luginbühl, M.D. Garrison, R.M. Overney, B.D. Ratner, Scanning, 20, 160-161, 1998.
153. "An Intrinsically Protein-Resistant Surface Plasma Resonance Biosensor Based upon a RF-Plasma-Deposited Thin Film," M.N. Mar, B.D. Ratner, S.S. Yee, Sensors and Actuators B 54 Chemical Sensors, 125-131, 1999.
154. "Template-Imprinted Nanostructured Surfaces for Protein Recognition, H. Shi, W-B. Tsai, M.D. Garrison, S. Ferrari, B.D. Ratner, Nature, 398, 593-597, 1999.

155. "Mice That Lack the Angiogenesis Inhibitor, Thrombospondin 2, Mount an Altered Foreign Body Reaction Characterized by Increased Vascularity," T.R. Kyriakides, K.J. Leach, A.S. Hoffman, B.D. Ratner, P. Bornstein, Proceedings of the National Academy of Science, Vol. 96, 4449-4454, 1999.
156. "Self Assembly of 16-Mercapto-1-Hexadecanol on Gold: Surface Characterization and Kinetics," S. Pan, A.M. Belu, B.D. Ratner, abstract submitted to Materials Science and Engineering C, 7, 51-58, 1999.
157. "Glow Discharge Plasma Deposited Hexafluoropropylene Films: Surface Chemistry and Interfacial Materials Properties," M.D. Garrison, R. Luginbuhl, R.M. Overney, B.D. Ratner, Thin Solid Films, 352, 13-21, 1999.
158. "Template Recognition of Protein Imprint Polymers Surfaces," H. Shi, B.D. Ratner, Journal of Biomedical Materials Research, 50, 1-11, 1999.
159. "Design of Infection-resistant Antibiotic-releasing Polymers: I. Fabrication and Formulation," C.S. Kwok, C. Wan, S. Hendricks and J.D. Bryers, T.A. Horbett, B.D. Ratner, Journal of Controlled Release, 62, 289-299, 1999.
160. "Design of Infection-resistant Antibiotic-releasing Polymers: II. Controlled Release of Antibiotics through a Plasma-deposited Thin Film Barrier," C.S. Kwok, T.A. Horbett, B.D. Ratner, Journal of Controlled Release, 62, 301-311, 1999.
161. "An Intrinsically Protein-Resistant Surface Plasma Resonance Biosensor Based upon a RF-Plasma-Deposited Thin Film," M.N. Mar, B.D. Ratner, S.S. Yee, Sensors and Actuators B Chemical Sensors, 54, 125-131, 1999.
162. "Plasma-Deposited Membranes for Controlled Release of Antibiotic to Prevent Bacterial Adhesion and Biofilm Formulation," S.K. Hendricks, C. Kwok, T. A. Horbett, B. D. Ratner, J. D. Bryers, Journal of Biomedical Materials Research, 50, 160-170, 2000.
163. "Surface Modification of Polymers with Self-assembled Monolayers: Multi technique Surface characterization," C.S. Kwok, P.D. Mourad, L.A. Crum, B.D. Ratner, Biomacromolecules, 1 139-148, 2000.
164. "Self Assembly of Tetraphenylporphyrin Monolayers of Gold Substrates," M.S. Boeckl, A.L. Bramblett, K.D. Hauch, T. Sasaki, B.D. Ratner, and J.W. Rogers, Jr., Langmuir, 16(13), 5644-5653, 2000.
165. "New Substrates for Polymer Cationization with Time-of-Flight Secondary Ion Mass Spectrometry," R. Michel, R. Luginbühl, D.J. Graham, B.D. Ratner, Langmuir, Vol. 16(16), 6503-6509, 2000.
166. "Self-assembled monolayers for polymer and protein cationization with ToF-SIMS," R. Michel, R. Luginbühl, D.J. Graham, B.D. Ratner, Journal of Vacuum Science and Technology, A 18(4), 1114-1118, 2000.
167. "Comprehensive Surface Analysis of Hydrophobically Functionalized SFM Tips," R. Luginbuhl, A. Szuchmacher, M.D. Garrison, J-B. Lhoest, R.M. Overney, B.D. Ratner, Ultramicroscopy, 82 171-179, 2000.
168. "Quantitative Interrogation of Micropatterned Biomolecules by Surface Force Microscopy", M.D. Garrison, T.C. McDevitt, R. Luginbuhl, C.M. Giachelli, P. Stayton, B.D. Ratner, Ultramicroscopy, 82, 193-202, 2000.
169. "Characterization of Combinatorially Designed Polyarylates by Time-Of-Flight Secondary Ion Mass Spectrometry," A.M. Belu, S. Brocchini, J. Kohn, B.D. Ratner, Rapid Communications In Mass Spectrometry, 14, 564-571, 2000.
170. "Surface Characterization of Hydroxyapatite and Related Calcium Phosphates by XPS and TOF-SIMS," H.B. Lu, C.T. Campbell, B.D. Ratner, Analytical Chemistry, 72, (13), 2886-2894, 2000.
171. "ToF-SIMS quantification of albumin adsorbed on plasma-deposited fluoropolymers by partial least square regression," S. Ferrari, B.D. Ratner, Surface and Interface Analysis, 29, 837-844, 2000.
172. "Plasma Polymerized N-isopropylacrylamide: Synthesis and Characterization of a Smart Thermally Responsive Coating," Y.V. Pan, R.A. Wesley, R. Luginbuhl, D.D. Denton, B.D. Ratner, Biomacromolecules, 2(1) 32-36, 2001.

173. "A Precision Technology for Controlling Protein Adsorption and Cell Adhesion in BioMEMS," Y.V. Pan, Y. Hanein, D. Leach-Scampavia, K.F. Bohringer, B.D. Ratner, D.D. Denton, IEEE International Conference on Mechanical Systems (MEMS) 2001, Interlaken, Switzerland, 435-348, 2001.
174. "Self-assembled Molecular Structures as Ultrasonically-responsive Barrier Membranes for Pulsatile Drug Delivery," C.S. Kwok, P.D. Mourad, L.A. Crum, B.D. Ratner, Journal of Biomedical Materials Research, 57, 151-164, 2001.
175. "Replacing and Renewing: Synthetic Materials, Biomimetics, and Tissue Engineering in Implant Dentistry," B.D. Ratner, Journal of Dental Education, Vol. 65, No. 12. 1340-1347, 2001.
176. "Static Time-of-flight Secondary Ion Mass Spectrometry and X-ray Photoelectron Spectroscopy Characterization of Adsorbed Albumin and Fibronectin Films," C.D. Tidwell, D. G. Castner, S.L. Goledge, B. D. Ratner, K. Meyer, B. Hagenhoff, and A. Benninghoven, Surface and Interface Analysis, 31, 8, 724-733, 2001.
177. "Micromachining of non-fouling Coatings For Bio-MEMS Applications," Y. Hanein, Y.V. Pan, B.D. Ratner, D.D. Denton, K. Böhringer, Sensors and Actuators B, 81, 49-54, 2001.
178. "Inhibition of Monocyte Adhesion and Fibrinogen Adsorption on Glow Discharge Plasma Deposited Tetraethylene Glycol Dimethyl Ether," M. Shen, V. Pan, M.S. Wagner, K.D. Hauch, D.G. Castner, B.D. Ratner, and T.A. Horbett, J. Biomat. Sci., Polymer Edn. 12(9), 961-978, 2001.
179. "Protein Contact Printing for a Surface Plasmon Resonance Biosensor with On-chip Referencing," H. Lu, J. Homola, C.T. Campbell, G. G. Nenninger, S.S. Yee, B.D. Ratner, Sensors and Actuators B, 74, 91-99, 2001.
180. "Solution Assembled and Microcontact Printed Monolayers of Dodecanethiol on Gold: A Multivariate Exploration of Chemistry and Contamination," D.J. Graham, D.D. Price, and B.D. Ratner, Langmuir, 18(5), 1518-1527, 2002.
181. "Reducing Capsular Thickness and Enhancing Angiogenesis Around Implant Drug Release Systems," B.D. Ratner, Journal of Controlled Release, 78, 211-218, 2002.
182. "Micro-Scale Cell Patterning on Non-fouling Plasma Polymerized Tetraglyme Coatings by Protein Microcontact Printing," Y.V. Pan, T.C. McDevitt, T.K. Kim, D. Leach-Scampavia, P.S. Stayton, D.D. Denton, and B.D. Ratner, Plasma and Polymers, 7 (2), 171-183, 2002.
183. "Biomedical Surface Science: Foundations to Frontiers," D.G. Castner, B.D. Ratner, Surface Science 500, 28-60, 2002.
184. "Determination of Surface Coverage for Tetraphenylporphyrin Monolayers Using Ultraviolet-Visible Absorption and X-ray Photoelectron Spectroscopies," A. L Bramblett, M.S. Boeckl, K. D. Hauch, B.D. Ratner, T. Sasaki and J.W. Rogers Jr., Surface and Interface Analysis, 339(6), 506-515, 2002.
185. "PEO-like Plasma Polymerized Tetraglyme Surface Interactions with Leukocytes and Proteins: *in vitro* and *in vivo* Studies," M. Shen, L. Martinson, M.S. Wagner, D.G. Castner, B.D. Ratner, and T.A. Horbett, Journal of Biomaterials Science, Polymer Edition, 13(4), 367-390, 2002.
186. "Multivariate Analysis of ToF-SIMS Spectra from Dodecanethiol SAM Assembly on Gold: Spectral Interpretation and ToF-SIMS Fragmentation Processes," D.J. Graham and B.D. Ratner, Langmuir, 18(15), 5861-5868, 2002.
187. "Poly(Desaminotyrosyl-tyrosine Carbonate Ethyl Ester) Studied by XPS," V.H. Perez-Luna, J. Kohn, D.J. Graham, and B.D. Ratner, Surface Science Spectra, 9, 6-11, 2002.
188. "Compromised Production of Extracellular Matrix in Mice Lacking Secreted Protein, Acidic and Rich in Cysteine (SPARC) Leads to Reduced Foreign Body Reaction to Implanted Biomaterials," P. Puolakkainen, A.D. Bradshaw, T.R. Kyriakides, M. Reed, R. Brekken, T. Wight, P. Bornstein, B.D. Ratner, and E.H. Sage, American Journal of Pathology, Vol. 162 (2), 627-635, 2003.

189. "Relative Influence of Polymer Fiber Diameter and Surface Charge on Fibrous Capsule Thickness and Vessel Density for Single-Fiber Implants," J.E. Sanders, D.V. Cassisi, T. Neumann, S.L. Golledge, S.G. Zachariah, B.D. Ratner, and S.D. Bale, Journal of Biomedical Materials Research, 65(A), 462-467, 2003.
190. "Nacre surface transformation to hydroxyapatite in a phosphate buffer solution," M. Ni and B.D. Ratner, Biomaterials, 24, 4323-4331, 2003.
191. "Characterization and Analysis of Osteopontin-immobilized Poly(2-hydroxyethyl Methacrylate) Surfaces" S.M. Martin, R. Ganapathy, T.K. Kim, D. Leach-Scampavia, C.M. Giachelli and B.D. Ratner, Journal of Biomedical Materials Research, 67A(1), 334-343, 2003.
192. "Albumin adsorption on Cibacron Blue F3G-A immobilized onto oligo(ethylene glycol)-terminated self-assembled monolayers," M.C.L. Martins, E. Naeemi, B.D. Ratner<sup>3</sup> and M.A. Barbosa, Journal Of Materials Science Materials In Medicine, 14, 945-954, 2003.
193. "Albumin adsorption on alkanethiols self-assembled monolayers on gold electrodes studied by chronopotentiometry," C.L. Martins, C. Fonseca, B.D. Ratner, M.A. Barbosa, Biomaterials, 24(21) 3697-3706, 2003.
194. "Protein Adsorption on Mixtures of Hydroxyl- and Methyl-Terminated Alkanethiols Self-Assembled Monolayers," C.L. Martins, B.D. Ratner and M.A. Barbosa, Journal of Biomedical Materials Research, 67A (1), 158-171, 2003.
195. "Multivariate Surface Analysis of Plasma-deposited Tetraglyme for Reduction of Protein Adsorption and Monocyte Adhesion," M. Shen, M. Wagner, D.G. Castner, B.D. Ratner, T.A. Horbett, Langmuir, 19(5), 1692-1699, 2003.
196. "Calcium Phosphate—Chitosan Composite Scaffolds for Bone Tissue Engineering," Y. Zhang, M. Ni, M. Zhang, B.D. Ratner, Tissue Engineering, 9(2), 337-345, 2003.
197. "Development of an electrospray approach to deposit complex molecules on plasma modified surfaces," K.J. Kitching, H-N. Lee, W.T. Elam, E.E. Johnston, H. MacGregor, R.J. Miller, F. Turecek, and B.D. Ratner, Review of Scientific Instruments 74(11), 4832-4839, 2003.
198. "Generation of Porous Microcellular 85/15 poly (DL-Lactide-co-Glycolide) Foams for Biomedical Applications," L. Singh, V. Kumar, B.D. Ratner, Biomaterials, 25, 2611-2617, 2004.
199. "Maximizing Information Obtained from Secondary Ion Mass Spectra of Organic Thin Films Using Multivariate Analysis," M. Wagner, D. Graham, B.D. Ratner, and D.G. Castner, Surface Science, 570, 78-97, 2004.
200. "Probing the Orientation of Surface-Immobilized Immunoglobulin G by Time-of-Flight Secondary Ion Mass Spectrometry," H. Wang, D.G. Castner, B.D. Ratner, and S. Jiang, Langmuir, 20(5), 1877-1887, 2004.
201. "Methods for Generating Protein Molecular ions in ToF-SIMS," S.L. McArthur, M.C. Vendettuoli, B.D. Ratner, and D.G. Castner, Langmuir, 20, 3704-3709, 2004.
202. "Novel cell patterning using microheater-controlled thermoresponsive plasma films," X. Cheng, Y. Wang, Y. Hanein, K.F. Bohringer, B.D. Ratner, Journal of Biomedical Materials Research, 70(A), Issue 2, 159-168, 2004.
203. "Enhancing the Biological Activity of Immobilized Osteopontin Using a Type-1 Collagen Affinity Coating," S.M. Martin, J.L. Schwartz, C. M. Giachelli, B.D. Ratner, Journal of Biomedical Materials Research, 70A, 11-19, 2004.
204. "Biomaterials: Where We Have Been and Where We Are Going," B.D. Ratner and S.J. Bryant, Annual Reviews of Biomedical Engineering, Vol. 6:41-75, 2004.
205. "Surface Characterization of the Extracellular Matrix Remaining after Cell Detachment from a Thermoresponsive Polymer," H.E. Canavan, X. Cheng, D.J. Graham, B.D. Ratner, D.G. Castner, Langmuir 21(5), 1949-1955, 2005.
206. "Quantitative Characterization of Sphere-templated Porous Biomaterials," A.J. Marshall and B.D. Ratner, AIChE Journal, Vol. 51, No. 4, 1221-1232, 2005.

207. "Synthesis of Segmented Poly(ether urethanes) and Poly(ether urethane ureas) Incorporating Various Side-chain or Backbone Functionalities," F.I. Simonovsky, S.C. Porter, B.D. Ratner, Journal of Biomaterials Science: Polymer Edition, 16(2), 267-284, 2005.
208. "Controlling Osteopontin Orientation on Surfaces to Modulate Endothelial Cell Adhesion," L. Liu, S. Chen, C.M. Giachelli, B.D. Ratner and S. Jiang, J. Biomed. Mater. Res. A, 74(1):23-31, 2005.
209. "Cell Sheet Detachment Affects the Extracellular Matrix: A Surface Science Study Comparing Thermal Liftoff, Enzymatic and Mechanical Methods," H.E. Canavan, X. Cheng, D.J. Graham, B.D. Ratner, D.G. Castner, J. Biomed. Mater. Res. A, 75(1):1-13, 2005.
210. "Protein adsorption on 18-alkyl chains immobilized on hydroxyl-terminated self-assembled monolayers," I. Castro Goncalves, M. Cristina, L. Martins, M.A. Barbosa, and B.D. Ratner, Biomaterials, Vol. 26, Issue 18, 3891-3899, 2005.
211. "Plasma Deposition and Surface Characterization of Oligoglyme, Dioxane, and Crown Ether Non-fouling Films," E.E. Johnston, J.D. Bryers and B.D. Ratner, Langmuir, 21(3), 870-881, 2005.
212. "Protein Adsorption on Oligo(ethylene glycol)-Terminated Alkanethiolate Self-Assembled Monolayers: The Molecular Basis for Nonfouling Behavior," L. Li, S. Chen, J. Zheng, B.D. Ratner, and S. Jiang, J. Phys. Chem. B, 109(7), 2934-2941, 2005.
213. "A Model for Studying Epithelial Attachment and Morphology at the Interface between Skin and Percutaneous Devices," N.G. Knowles, Y. Miyashita, M.L. Usui, A.J. Marshall, A. Pirrone, K.D. Hauch, B.D. Ratner, R.A. Underwood, P. Fleckman and J.E. Olerud, J. Biomed. Mater. Res. A, 74(3): 482-488, 2005.
214. "The Role of Osteopontin in Foreign Body Giant Cell Formation," A. Tsai, J. Rice, M. Scatena, L. Liaw, B.D. Ratner, and C. Giachelli, Biomaterials, 26(29): 5835-5843, 2005.
215. "Poly(ether urethanes) Incorporating Long Alkyl Side-Chains with Terminal Carboxyl Groups as Fatty Acid Mimics: Synthesis, Structural Characterization and Protein Adsorption," F.I. Simonovsky, Y. Wu, S.L. Golledge, B.D. Ratner, and T.A. Horbett, Journal of Biomaterials Science, Polymer Edition, 16(12): 1463--1484, 2005.
216. "Esophageal Epithelial Cell Interaction with Synthetic and Natural Scaffolds for Tissue Engineering," B.L. Beckstead, S. Pan, A.D. Bhrany, A.M. Bratt-Leal, B.D. Ratner, and C.M. Giachelli, Biomaterials, 26(31):6217-6228, 2005.
217. "Fibro-porous meshes made from polyurethane micro-fibers: effects of surface charge on tissue response," J.E. Sanders, S.E. Lamont, A. Karchin, S.L. Golledge, and B.D. Ratner, Biomaterials, 26(7):813-818, 2005.
218. "Surface Chemical and Mechanical Properties of Plasma Polymerized *N*-isopropylacrylamide," X. Cheng, H.E. Canavan, M.J. Stein, J.R. Hull, S.J. Kveskin, M.S. Wagner, G.A. Somorjai, D.G. Castner, B.D. Ratner, Langmuir, Vol. 21, No. 17, 7833-7841, 2005.
219. "Preparative Soft and Reactive Landing of Gas-Phase Ions on Plasma-Treated Metal Surfaces," M. Volny, W.T. Elam, B.D. Ratner and F. Turecek, Analytical Chemistry, 77(15): 4846-4853, 2005.
220. "Preparative Soft and Reactive Landing of Multiply Charged Protein Ions on a Plasma-Treated Metal Surface," M. Volny, W.T. Elam, A. Branca, B.D. Ratner, F. Turecek, Analytical Chemistry, 77(15): 4890-4896, 2005.
221. "Identifying the SPARC binding sites on collagen I and procollagen I by atomic force microscopy," H. Wang, A. Fertala, B.D. Ratner, E.H. Sage and S. Jiang, Analytical Chemistry, 77(21): 6765-71, 2005.
222. "Ultrasonically Controlled Release of Ciprofloxacin from Self-Assembled Coatings on Poly(2-Hydroxyethyl Methacrylate) Hydrogels for *Pseudomonas Aeruginosa* Biofilm Prevention," P. Norris, M. Noble, I. Francolini, A.M. Vinogradov, P.S. Stewart, B.D. Ratner, J.W. Costerton, P. Stoodley, Antimicrob Agents Chemother., 49(10): 4272-4279, 2005.

223. "Protein bonding on biodegradable poly(L-lactide-*co*-caprolactone) membrane for esophageal tissue engineering," Y. Zhu, K.S. Chian, M.B. Chan-Park, P.S. Mhaisalkar, B.D. Ratner, Biomaterials, 27(1):68-78, 2006.
224. "Development of an Esophagus Acellular Matrix (EAM) Tissue Scaffold," A.D. Bhrany, B.L. Beckstead, T.C. Lang, D.G. Farwell, C.M. Giachelli, B.D. Ratner, Tissue Engineering, 12 (2): 319-330, 2006.
225. "Secreted protein acidic and rich in cysteine (SPARC/osteonectin/BM-40) binds to fibrinogen fragments D and E, but not to native fibrinogen," H. Wang, G. Workman, S. Chen, T.H. Barker, E.H. Sage, B.D. Ratner and S. Jiang, Matrix Biology, 25(1): 20-26, 2006.
226. "Characterization of an In Vitro Model for Evaluating the Interface between Skin and Percutaneous Biomaterials," Y. Fukano, N. G. Knowles, M. L. Usui, R. A. Underwood, K. D. Hauch, A. J. Marshall, B. D. Ratner, C. Giachelli, W. G. Carter, P. Fleckman, J. E. Olerud, Wound Repair and Regeneration, 14(4):484-491, 2006.
227. "Glow Discharge Plasma Treatment of Polyethylene Tubing with Tetraglyme Results in Ultralow Fibrinogen Adsorption and Greatly Reduced Platelet Adhesion," L. Cao, S. Sukavaneshvar, B.D. Ratner, T.A. Horbett, J. Biomed. Mater. Res. A, 79(4):788-803, 2006.
228. "Temperature Dependent Activity and Structure of Adsorbed Proteins on Plasma Polymerized N-Isopropyl Acrylamide," X. Cheng, H.E. Canavan, D.J. Graham, D.G. Castner, B.D. Ratner, Biointerphases, 1(1):61-72, 2006.
229. "Spatial Patterning of Thick Poly(2-Hydroxyethyl Methacrylate) Hydrogels," S. J. Bryant, K. D. Hauch, B.D. Ratner, Macromolecules 39(13):4395-4399, 2006.
230. "Modulating cell adhesion and spreading by control of Fn117-10 orientation on charged self-assembled monolayers (SAMs) of alkanethiolates," H. Wang, Y. He, B.D. Ratner, S. Jiang, J. Biomed. Mater. Res. A, 77(4): 672-678, 2006.
231. "A Plasma-Deposited Surface for Cell Sheet Engineering: Advantages over Mechanical Dissociation of Cells," H.D. Canavan, X. Cheng, D.J. Graham, B.D. Ratner, D.G. Castner, Plasma Process. Polym., 3(6-7):516-523, 2006.
232. "Fibrinogen Adsorption, Platelet Adhesion and Platelet Activation on Mixed Hydroxyl-/Methyl-Terminated Self-Assembled Monolayers," S.N. Rodrigues, I.C. Goncalves, M.C.L. Martins, M.A. Barbosa, B.D. Ratner, Biomaterials 27(31):5357-5367, 2006.
233. "Comparison of polyester scaffolds for bioengineered intestinal mucosa," D.C. Chen, J.R. Avansino, V.G. Agopian, V.D. Hoagland, J.D. Woolman, S. Pan, B.D. Ratner, M. Stelzner, Cells Tissues Organs, 184(3-4):154-165, 2006.
234. "Infrared Light Induced Patterning of Proteins on ppNIPAM Thermoresponsive Thin Films: A 'Protein Laser Printer,'" K.F. Bohringer, H. Bilge, X. Cheng, B. D. Ratner, S. Takeuchi, H. Fujita, IEEE Conference Proceedings on Micro Electro Mechanical Systems (MEMS), Istanbul, Turkey, January 22-26, 2006.
235. "Reversible Thermosensitive Glue for Retinal Implants," M. Tunc, X. Cheng, B.D. Ratner, E. Meng, M. Humayun, Retina, 27(7), 938-942, 2007.
236. "Controlling the Orientation of Bone Osteopontin via its Specific Binding with Collagen I to Modulate Osteoblast Adhesion," L. Liu, C. Qin, W.T. Butler, B.D. Ratner, S. Jiang, J. Biomed. Mater. Res. A, 80(1):102-110, 2007.
237. "Plasma Deposited Tetraglyme Surfaces Greatly Reduce Total Blood Protein Adsorption, Contact Activation, Platelet Adhesion, Platelet Procoagulant Activity, and In Vitro Thrombus Deposition," L. Cao, M. Chang, C-Y Lee, D.G. Castner, S. Sukavaneshvar, B.D. Ratner, T.A. Horbett, J. Biomed. Mater. Res. A, 81(4): 827-837, 2007.
238. "The influence of surface energy on competitive protein adsorption on oxidized NiTi surfaces," A. Michiardi, C. Aparicio, B.D. Ratner, J.A. Planell, J. Gil, Biomaterials 28(4):586-594, 2007.
239. "Plasma Deposition of Tetraglyme Inside Small Diameter Tubing: Optimization and Characterization," L. Cao, B.D. Ratner, T. A. Horbett, J. Biomed. Mater. Res. A, 81(1):12-23, 2007.

240. "Comparison of Native Extracellular Matrix with Adsorbed Protein Films Using Secondary Ion Mass Spectrometry," H.E. Canavan, D.J. Graham, X. Cheng, B.D. Ratner, D.G. Castner, Langmuir 23(1):50-56, 2007.
241. "Enhanced In-Vitro Blood Compatibility of 316L Stainless Steel Surfaces by Reactive Landing of Hyaluronan Ions," M. Volny, W.T. Elam, B.D. Ratner, F. Turecek, J. Biomed. Mater. Res. B, Applied Biomaterials 80(2):505-510, 2007.
242. "Photo-patterning of Porous Hydrogels for Tissue Engineering," S.J. Bryant, J.L. Cuy, K.D. Hauch, B.D. Ratner, Biomaterials, 28(19):2978-2986, 2007.
243. "Delivery of non-viral gene carriers from sphere-templated fibrin scaffolds for sustained transgene expression," J.M. Saul, M.P. Linnes, B.D. Ratner, C.M. Giachelli, S.H. Pun, Biomaterials 28(31):4705-4716, 2007.
244. "Dual requirements of extracellular matrix protein and chitosan for inducing adhesion contact evolution of esophageal epithelia," Z. Feng, K.S. Chian, W.F. Ong, P.S. Mhaisalka, V. Chan, B.D. Ratner, J. Biomed. Mater. Res. A, 82(4):788-801, 2007.
245. "Thermoresponsive MALDI Probe Surfaces as a Tool for Protein On-Probe Purification," M. Li, G. Fernando, L.G. Waasbergen, X. Cheng, B.D. Ratner, G.R. Kinsel, Anal. Chem., 79(17):6840-6844, 2007.
246. "A fibrinogen-based precision microporous scaffold for tissue engineering," M.P. Linnes, B.D. Ratner, C.M. Giachelli, Biomaterials 28:5298-5306, 2007.
247. "The Catastrophe Revisited: Blood Compatibility in the 21<sup>st</sup> Century," B.D. Ratner, Biomaterials 28:5144-5147, 2007.
248. "A Mouse Model to Evaluate the Interface between Skin and a Percutaneous Device," S.N. Isenath, Y. Fukano, M.L. Usui, R.A. Underwood, C.A. Irvin, A.J. Marshall, K.D. Hauch, B.D. Ratner, P. Fleckman, J.E. Olerud, J. Biomed. Mater. Research 83A:915-922, 2007.
249. "A Paradigm Shift: Biomaterials that Heal," B. Ratner, Polymer International, 56:1183-1185, 2007.
250. "Investigation of the Foreign Body Response with an Implanted Biosensor by In Situ Application of Electrical Impedance Spectroscopy," F.B. Karp, N.A. Bernotski, T.I. Valdes, K.F. Bohringer, B.D. Ratner, IEEE Sensors, 8(1):104-112, 2008.
251. "Surface modification of a perfluorinated ionomer using a glow discharge deposition method to control protein adsorption," T.I. Valdes, W. Ciridon, B.D. Ratner, J.D. Bryers, Biomaterials, 29(10):1356-1366, 2008.
252. "Effect of electrospun poly(D,L-lactide) (PLA) fibrous scaffold with nano-porous surface on attachment of porcine esophageal epithelial cells (PEECs) and protein adsorption," M.F. Leong, K.S. Chian, P.S. Mhaisalkar, W.F. Ong, B.D. Ratner, J. Biomed. Mater. Res. A 2008 (In Press).

## Nonrefereed Papers

1. "Radiation-Grafted Hydrogels on Silicone Rubber as New Biomaterials," B.D. Ratner and A.S. Hoffman, ACS Div. Org. Coat. Plast. Chem. Prepr., **33**, 386-392, 1973.
2. "pH Effects in the Covalent Coupling of Small Molecules and Proteins to Poly(2-hydroxyethyl methacrylate-methacrylic acid) Hydrogels," T.P. Mate, T.A. Horbett, A.S. Hoffman and B.D. Ratner, in Enzyme Engineering, Vol. 2, E.K. Pye and L.B. Wingard, Jr., eds., Plenum Press, New York, 137-139, 1974.
3. "Preparation and Application of Radiation-Grafted Hydrogels as Biomaterials," A.S. Hoffman, G. Schmer, T.A. Horbett, B.D. Ratner, L.N. Teng, C. Harris, W.G. Kraft, B.N.L. Khaw, T.T. Ling and T.P. Mate, in Permeability of Plastic Films and Coatings, H.B. Hopfenberg, ed., Plenum Press, New York, 441-451, 1975.
4. "Radiation-Grafted Hydrogels on Silicone Rubber as New Biomaterials," B.D. Ratner and A.S. Hoffman, in Biomedical Applications of Polymers, H.P. Gregor, ed., Plenum Press, New York, 159-171, 1975.
5. "Radiation-Induced Co-Graft Polymerization of 2-Hydroxyethyl Methacrylate and Ethyl Methacrylate onto Silicone Rubber Films," T. Sasaki, B.D. Ratner and A.S. Hoffman, ACS Polym. Prepr., **16**, 435-440, 1975.
6. "Synthetic Hydrogels for Biomedical Applications," A.S. Hoffman and B.D. Ratner, ACS Polym. Prepr., **16**, 272-275, 1975.
7. "The Thermodynamics of Water Sorption in Radiation-Grafted Hydrogels," B.N.L. Khaw, B.D. Ratner and A.S. Hoffman, ACS Polym. Prepr., **16**, 446-451, 1975.
8. "Interactions of Blood and Blood Components at Hydrogel Interfaces," A.S. Hoffman, T.A. Horbett and B.D. Ratner, Ann. N.Y. Acad. Sci., **283**, 372-382, 1977.
9. "Cleaning Glass Surfaces: The Effectiveness of Various Methods as Determined by the ESCA Technique," B.D. Ratner, L.H. Scharpen, J.J. Rosen and A.S. Hoffman, in Symposium on Surface Contamination, Washington, D.C., Sept. 10-14, 267-276, 1978.
10. "Some Unusual Effects in the Radiation Grafting of Acrylamide to Polymer Substrates," A.S. Hoffman and B.D. Ratner, ACS Polym. Prepr., **20**, 423-426, 1979.
11. "Surface Characterization of Hydrophilic-Hydrophobic Copolymer Model Systems," B.D. Ratner and A.S. Hoffman, ACS Div. Org. Coat. Plast. Chem. Prepr., **40**, 714-719, 1979.
12. "Estimation of Surface Energy Components and Their Potential Relevance to Biological Interactions," A.S. Hoffman, B.D. Ratner, Y.C. Ko and T.A. Horbett, in Proceedings NSF Interfacial Phenomena Workshop, J. Berg, ed., University of Washington, Feb. 15-16, 445-457, 1979.
13. "ESCA and SEM Studies on Polyurethanes for Biomedical Applications," B.D. Ratner, ACS Polym. Prepr., **21**, 152-153, 1980.
14. "The Interaction of Silastic and Poly(acrylamide-silastic) Surfaces with Blood," A.S. Hoffman, S.R. Hanson, L.A. Harker, T.A. Horbett, B.D. Ratner and L.O. Reynolds, in Proceedings of the 3rd Congress of International Society of Artificial Organs, Paris, July 8-10, 1981.
15. "Evaluation of Artificial Surfaces Using a Baboon Arteriovenous Shunt Model," S.R. Hanson, L.A. Harker, B.D. Ratner and A.S. Hoffman, in Biomaterials 1980, G.D. Winter, D.F. Gibbons and H. Plenck, Jr., eds., John Wiley and Sons, Ltd., London, 519-530, 1982.
16. "Application of Radiation-Grafted Hydrogels as Blood-contacting Biomaterials," A.S. Hoffman, D. Cohn, S.R. Hanson, L.A. Harker, T.A. Horbett, B.D. Ratner and L.O. Reynolds, Rad. Phys. Chem., **22**, 267-283, 1983.
17. "Polyurethane Surfaces - An XPS Study," R.W. Paynter, B.D. Ratner and H.R. Thomas, ACS Polym. Prepr., **24**, 13-14, 1983.

18. "Swelling Behavior of Glucose Sensitive Membranes," T.A. Horbett, J. Kost and B.D. Ratner, ACS Polym. Prepr., **24**, 34-35, 1983.
19. "An XPS and SEM Study of Polyurethane Surfaces: Experimental Conditions," R.W. Paynter, B.D. Ratner and H.R. Thomas, in Polymers as Biomaterials, S. Shalaby, A.S. Hoffman, B.D. Ratner and T.A. Horbett, eds., Plenum Press, New York, 121-133, 1984.
20. "Polyurethane Surfaces: The Importance of Molecular Weight Distribution, Bulk Chemistry and Casting Conditions," B.D. Ratner and R.W. Paynter, in Polyurethanes in Biomedical Engineering, Progress in Biomedical Engineering, Vol. 1, H. Planck, G. Eghers and I. Syre, eds., Elsevier, Amsterdam, 41-68, 1984.
21. "Unusual Biological Interactions at Radiation Graft Copolymer Interfaces," A.S. Hoffman, B.D. Ratner, T.A. Horbett, L.O. Reynolds, C.S. Cho, L.A. Harker and S.R. Hanson, in Progress in Artificial Organs - 1983, Vol. 2, K. Atsumi, M. Maekawa and K. Ota, eds., ISAO Press, Cleveland, OH, 819-824, 1984.
22. "A Bioresponsive Membrane for Insulin Delivery," T.A. Horbett, B.D. Ratner, J. Kost and M. Singh, in Recent Advances in Drug Delivery Systems, J.M. Anderson and S.W. Kim, eds., Plenum Press, New York, 209-220, 1984.
23. "Swelling Behavior of Glucose Sensitive Membranes," T.A. Horbett, J. Kost and B.D. Ratner, in Polymers as Biomaterials, S. Shalaby, A.S. Hoffman, B.D. Ratner and T.A. Horbett, eds., Plenum Press, New York, 193-207, 1984.
24. "Effects of a Tetrafluoroethylene Glow Discharge on Patency of Small Diameter Dacron Vascular Grafts," A.M. Garfinkle, A.S. Hoffman, B.D. Ratner and S.R. Hanson, Trans. Am. Soc. Artif. Intern. Org., **30**, 432-438, 1984.
25. "Enzymatically Controlled Drug Release Systems," B.D. Ratner and T.A. Horbett, in Drug and Enzyme Targeting, Methods in Enzymology, Vol. 112, K.J. Widder and R. Green, eds., Academic Press, New York, 484-495, 1985.
26. "The Importance of Vascular Graft Surface Composition as Demonstrated by a New Gas Discharge Treatment for Small Diameter Grafts," A.S. Hoffman, B.D. Ratner, A.M. Garfinkle, T.A. Horbett, L.O. Reynolds and S.R. Hanson, in Vascular Graft Update: Safety and Performance, Vol. STP #898, H.E. Kambic, A. Kantrowitz and P. Sung, eds., American Society for Testing and Materials, Philadelphia, 137-155, 1986.
27. "Characterization of Biomaterials Surfaces by Electron Spectroscopy for Chemical Analysis," B.D. Ratner, Proceedings of the 4th International Conference on Polymers in Medicine and Surgery, Plastics and Rubber Institute, Holland, Sept. 10-12, 1986.
28. "The Small Diameter Vascular Graft - A Challenging Biomaterials Problem," A.S. Hoffman, B.D. Ratner, A.M. Garfinkle, T.A. Horbett, L.O. Reynolds and S.R. Hanson, in Biomedical Materials, Vol. 55, J.M. Williams, M.F. Nichols and W. Zingg, eds., Materials Research Society, Pittsburgh, 3-17, 1986.
29. "ESCA for the Study of Biomaterial Surfaces," B.D. Ratner, in Polymers in Medicine II, E. Chiellini, P. Giusti, C. Migliaresi, and L. Nicolais, eds., Plenum Press, New York, 13-28, 1986.
30. "The Small Diameter Vascular Graft - A Biomaterials Challenge," A.S. Hoffman, B.D. Ratner, A.M. Garfinkle, L.O. Reynolds, T.A. Horbett and S.R. Hanson, in Polymers in Medicine II, E. Chiellini, P. Giusti, C. Migliaresi, and L. Nicolais, eds., Plenum Press, New York, 157-173, 1986.
31. "Biomaterial Surfaces," B.D. Ratner, A.B. Johnston and T.J. Lenk, J. Biomed. Mater. Res.: Appl. Biomat., **21**, 59-89, 1987.
32. "Surface Studies by ESCA of Polymers for Biomedical Applications," B.D. Ratner, S.C. Yoon and N.B. Mateo, in Polymer Surfaces and Interfaces, W.J. Feast and H.S. Munro, eds., John Wiley and Sons, Ltd., Chichester, 231-251, 1987.

33. "Control of Polyurethane Surface Structure by Synthesis and Additives: Implications for Blood Interactions," B.D. Ratner, S.C. Yoon, A. Kaul and R. Rahman, in Polyurethanes in Biomedical Engineering II, H. Planck, I. Syré, M. Dauner, and G. Egbers, eds., Elsevier, Amsterdam, 213-229, 1987.
34. "Interaction of Blood with Gas Discharge Treated Vascular Grafts," D. Kiaei, A.S. Hoffman, B.D. Ratner, T.A. Horbett and L.O. Reynolds, J. App. Polym. Sci.: App. Polym. Symp. **42**, 269, 1988.
35. "ESCA: Biomedical Studies," B.D. Ratner in Advances in Biomaterials, S.M. Lee, ed., Technomic Publishing Company, Lancaster, 28-33, 1987.
36. "Properties of the Plasma and Plasma-deposited Films of Perfluoropropane and Ethylene Oxide," B.D. Ratner and Y. Haque, ACS Polym. Mater. Sci. Eng., **56**, 500-504, 1987.
37. "Surface Contamination and Biomaterials," B.D. Ratner, in Treatise on Clean Surface Technology, Vol. 1, K.L. Mittal, ed., Plenum Press, New York, 247-259, 1987.
38. "Cell and Protein Interaction with Silicone Fluid and Silicone Elastomer," B.D. Ratner, J. Chinn and M.B. Schway, Afro-Asian J. Ophthalmol., in press.
39. "Surface Analysis of Biomedical Materials by ESCA and SIMS," B.D. Ratner, in Proceedings of the Third International Conference on Polymers in Medicine, Polymers in Medicine III, Biomedical and Pharmaceutical Applications, Porto Cervo, Sardinia, Italy, L. Nicolais and C. Migliaresi, eds., Elsevier, Amsterdam, 87-98, 1988.
40. "Surface Structure of Polymers for Biomedical Applications," B.D. Ratner, Die Makromolekulare Chemie, Macromolecular Symposium, **19**, 163-178, 1988.
41. "Prospects for Automatic Delivery of Insulin Using Glucose-Sensitive Membranes," T.A. Horbett and B.D. Ratner, Proc. Pharm. Tech. Conf. 356-569, 1988.
42. "Surface Properties of Polyurethanes with C18 Pendant Groups Attached to the Hard Segments by Two Different Routes," P.G. Edelman and B.D. Ratner, ACS Polymeric Mater. Science and Engineering, **59**, 253-257, 1988.
43. "Effect of Monomer Type on the Surface Chemistry of RF-Plasma Deposited Surfaces Prepared for Cell Culture," A. Chilkoti and B.D. Ratner, ACS Polymeric Mater. Science and Engineering, **59**, 258-263, 1988.
44. "Shear Stress Induced Platelet Refractoriness in Blood-Biomaterial Evaluations," J.A. Chinn, T.A. Horbett, and B.D. Ratner, ACS Polymeric Mater. Science and Engineering, **59**, 244-248, 1988.
45. "Surface Analysis of Biomedical Materials and Devices. Part I," B.D. Ratner and D.G. Castner, Biomedical Polymers, **4** (1), 1-4, 1988.
46. "Surface Analysis of Biomedical Materials and Devices. Part II," B.D. Ratner and D.G. Castner, Biomedical Polymers, **4** (2), 1-4, 1988.
47. "Biomaterials Science Refutes Surface Passivation," B.D. Ratner, Ocular Surgery News, **7**, 1989.
48. "Effect of Reduced Substrate Temperature on Film Chemistry in Plasma Deposition of Organics," G.P. Lopez, B.D. Ratner, R.J. Rapoza, and T.A. Horbett in Proceedings of the Ninth International IUPAC Symposium on Plasma Chemistry (Pugnochiuso, Italy), Vol. 2, R. D'Agostino, ed., 1178-1183, 1989.
49. "Perfluoropolyether Soft Segment Containing Polyurethanes: Synthesis, Characterization and Surface Properties," P.G. Edelman, D.G. Castner and B.D. Ratner, ACS Polymer Preprints, **31**, 314-315, 1990.
50. "Surface Analysis of Polyurethane-Poly(amide-amine)," B.D. Ratner and D.G. Castner, Biomaterials, **11**, 143-146, 1990.

51. "Static SIMS Investigation of the Surface Structure of Plasma Deposited Films Prepared from Stable Isotope-Labeled Carbonyl Precursors," A. Chilkoti, B.D. Ratner and D. Briggs, ACS Polym. Mat. Sci. and Eng., Vol. 62, 135-139, 1990.
52. "Interactions of Plasma-Deposited Films with Living Cells," B.D. Ratner, N.B. Mateo, S.I. Ertel, and T.A. Horbett, ACS Polym. Mat. Sci. and Eng., Vol. 62, 250-253, 1990.
53. "Cryogenic Control of Chemistry in Plasma Deposited Organic Films, G.P. Lopez and B.D. Ratner, ACS Polym. Mat. Sci. and Eng., Vol. 62, 14-18, 1990.
54. "Static SIMS Characterization of a Styrene/p-hydroxystyrene Copolymer Series, A. Chilkoti, D.G. Castner, B.D. Ratner and D. Briggs, in Proceedings of the Seventh International Conference on Secondary Ion Mass Spectrometry, SIMS VII, John Wiley and Sons, New York, 769-772, 1990.
55. "Oxidative and Enzymatic Degradation of Biomer™ Fractions, B.J. Tyler and B.D. Ratner, ACS Polym. Preprints, Vol. 31, 224-225, 1990.
56. "Surface Modification of Intraocular Lenses: Is There Greater Biocompatibility?" B.D. Ratner and N.B. Mateo, Ophthalmol. Clin. N. Am., 4, 277-293, 1991.
57. "Surface Analysis, Self-Assembly, and Selective Activity in a New Generation of Biomaterials," B.D. Ratner, T. Boland, G.R. Llanos, K.B. Lewis, and D.G. Castner, ACS Polymeric Mats. Science and Engineering, 66(1), 220-221, 1992.
58. "Polymer Analysis: Combined Techniques," B.D. Ratner, G.P. Lopez, A. Chilkoti. In: Secondary Ion Mass Spectrometry, SIMS VIII, (eds: Benninghoven, A; Janssen, KTF; Tumpner, J; Werner, HW), John Wiley and Sons, Chichester, UK, 791-798, 1992.
59. "Developing Multivariate Statistical Models of the Surface Chemistry of Organic Plasma Deposited Films Based on the Static SIMS Spectra of Model Homopolymers," A. Chilkoti, B.D. Ratner, David Briggs, in Secondary Ion Mass Spectrometry SIMS VIII, A. Benninghoven, K.T.F. Janssen, J. Tumpner, H.W. Werner, eds. , John Wiley and Sons, Chichester, UK, pp. 815-818, 1992.
60. "Chemical Alteration of Biomer™ as a Result of Oxidative Degradation," B.J. Tyler and B.D. Ratner, in Degradation Phenomena on Polymeric Biomaterials, H. Planck, M. Dauner, M. Renardy, Springer-Verlag, Berlin, pp. 9-23, 1992.
61. "Plasma Deposition for Biomedical Applications: A Brief Review," B.D. Ratner, J. Biomed. Sci., Polymer. Edn., 4 (1), 3-11, 1992.
62. "Contemporary Methods for Characterizing Complex Biomaterial Surfaces," B.D. Ratner, A. Chilkoti, and D.G. Castner, Clinical Materials, 11, 25-36, 1992.
63. "New Ideas in Biomaterials Science: A Path to Engineered Biomaterials," B.D. Ratner, J. Biomed. Mater. Res., 27, 837-850, 1993.
64. "Analysis of Biomedical Polymer Surfaces: Polyurethanes and Plasma-Deposited Thin Films," B.D. Ratner, B.J. Tyler, and A. Chilkoti, Clinical Materials, 13, 71-84, 1993.
65. "The Blood Compatibility Catastrophe," B.D. Ratner, J. Biomed. Mater. Res., 27, 283-287, 1993.
66. "Effect of Polyol Type on the Surface Structure of Sulfonate-Containing Polyurethanes," J.H. Silver, K.B. Lewis, B.D. Ratner, S.L. Cooper, ACS Polymer Preprints, Vol. 34, 56-57, 1993.
67. "Biocompatibility: The Convolution Path to a Working Definition," B.D. Ratner, Trends in Polym. Sci., 2(12), 402-403, 1994.

68. "Surface Modification of Polymers for Ophthalmologic Applications: A Review of Chemical, Biological and Surface Analytical Challenges," B.D. Ratner, Proceedings of the 1st Internet Symposium on Biomaterials in Ophthalmology, 53-55, 1995.
69. "Blood-Materials Interactions: A Perspective," B.D. Ratner, Abstracts of the 15th Annual Cardiothoracic Surgery Symposium, San Diego, February 23-26, 1995, pp 160-163. 1995.
70. "Enhanced Protein Binding on a Surface Plasmon Resonance Sensor Using a Plasma Deposited Functionalization Film", M.N. Mar, B.D. Ratner, K.S. Johnston, S.S. Yee, SPIE/BiOS Proceedings of An International Symposium on Biomedical Optics, 2388B, San Jose, California, February 4-10 1995.
71. "Surface Modification of Polymers for Biomedical Applications: Chemical, Biological and Surface Analytical Challenges," B.D. Ratner, ACS Polymer Preprints, Vol. 36, 53-54, 1995.
72. "Characterization of RF Plasma-Deposited Oligo(glyme) Films by XPS and SSIMS," E. Johnston, B.D. Ratner, ACS Polymer Preprints, Vol. 36, 87-88, 1995.
73. "Deposition of Fluorocarbon Films by Remote RF Glow Discharge," D.G. Castner, P. Favia, B.D. Ratner, ACS Polymer Preprints, Vol. 36, 105-106, 1995.
74. "Advances in the Analysis of Surfaces of Biomedical Interest," B.D. Ratner, Surface and Interface Analysis, Vol. 23, 521-528, 1995.
75. "Plasma Deposition of Organic Thin Films for Surface Modification," B.D. Ratner, Journal Photopolymer Science and Technology, 8, (3) 481-494, 1995.
76. "Recognition and Nanolithography with the Atomic Force Microscope," T. Boland, E.E. Johnston, B.D. Ratner, ACS Polymer Preprints, Vol. 37, 2, 1996.
77. "Infection Resistant Biomaterials Releasing Antibiotics into the Interfacial Zone," C. Kwok, S. Hendricks, C. Wan, J.D. Bryers, B.D. Ratner, T.A. Horbett, Proceed. Intern. Symp. Control. Rel. Bioact. Mater., 23, Controlled Release Society, Inc., 230-231, 1996.
78. "Blood Compatible Biomaterials Releasing Hirudin into the Interfacial Zone," D-D. Kim, M.M. Takeno, B.D. Ratner, T.A. Horbett, Proceed. Intern. Symp. Control. Rel. Bioact. Mater., 23, Controlled Release Society, Inc., 741-742, 1996.
79. "Ultrathin Films (by Plasma Deposition)," B.D. Ratner, The Polymeric Materials Encyclopedia, Vol. 11, 8444-8451 1st ed., CRC Press, Inc., 1996.
80. "Biosurfaces: A Communications Link Between Solids and Cells, B.D. Ratner, in Secondary Ion Mass Spectrometry SIMS X Proceedings, John Wiley and Sons, Chichester, UK, 11-20, 1996.
81. "Surface Analysis for Biomaterials and Biological Systems," B.D. Ratner, D.G. Castner, Monograph of American Vacuum Society, 524-529. 1996.
82. "Engineering Biomaterials that Exhibit Recognition and Specificity," B.D. Ratner, T. Boland, E.E. Johnston, and C.D. Tidwell, in "Thin Films and Surfaces for Bioactivity and Biomedical Applications," Materials Research Society MRS Proceedings, Vol. 414, pp195-201, C.M. Cotell, A.E. Meyer, S.M. Gorbalkin, G.L. Grobe III, eds., 1996.
83. "Surface Characterization of Polystyrene Cell Culture Substrates," A.M. Belu, D. Leach-Scampavia, B.D. Ratner, ACS Polymer Preprints, Vol. 37, 1, 307-308, 1996.
84. "Quantitative TOF-SIMS Studies of Cross-Linked Poly(Methyl Methacrylate) Using Multivariate Statistical Methods," A.M. Belu, V.H. Perez-Luna, B.D. Ratner, ACS Polymer Preprints, Vol. 37, 1, 841-842, 1996.
85. "TOF-SIMS Studies of Adsorbed Protein Films," B.D. Ratner, C.D. Tidwell, D.G. Castner, S. Golledge, ACS Polymer Preprints, Vol. 37, 1, 843-844, 1996.

86. "Self-Assembled Monolayer Growth of 16-Mercapto-1-Hexanol on Gold," S. Pan, A. Belu, M. Mar, B.D. Ratner, ACS Polymer Preprints, Vol. 38 (1), 932-933, 1997.
87. "Surface Patterning of Plasma Deposited Fluoropolymer Films By Atomic Force Microscopy," M.D. Garrison, and B.D. Ratner, ACS Polymer Preprints, Vol. 38 (1), 989-990, 1997.
88. "Infractions Between Pseudomonas Aeruginosa and Plasma-Deposited PEO-Like Thin Films During Initial Attachment and Growth," E.E. Johnston, J.D. Bryers, B.D. Ratner, ACS Polymer Preprints, Vol. 38 (1), 1016-1017, 1997.
89. "Tutorial: An Introduction to the Deposition of Polymeric Thin Films Using Plasmas," B.D. Ratner, ACS Polymer Preprints, Vol. 38 (1), 1021-1022, 1997.
90. "Hydration Induced Changes in Plasma Deposited Fluorocarbon Films," S. Sarma, D.G. Castner, B.D. Ratner, ACS Polymer Preprints, Vol. 38 (1), 1041-1042, 1997.
91. "Inflection-Resistant Biomaterials Releasing Antibiotics Through A Plasma-Deposited Thin Film," C.S.K. Kwok, B.D. Ratner, T.A. Horbett, ACS Polymer Preprints, Vol. 38 (1), 1077-1078, 1997.
92. "RF Plasma Deposited PEO-Like Surfaces that Inhibit Pseudomonas Aeruginosa Accumulation," E.E. Johnston, B.D. Ratner, and J.D. Bryers, Plasma Processing of Polymers, 465-476, 1997.
93. "Radio Frequency Glow Discharge (RFGD) Imprinting of E. coli and Nanogold Colloids," H. Shi, M. Garrison, B.D. Ratner, ACS Polymeric Materials Science & Engineering Preprints, Vol. 77 (2), 396-397, 1997.
94. "Molecular Design Strategies for Biomaterials that Heal," B.D. Ratner, Macromol. Symp. Vol. 130, 327-335, 1998.
95. "Recognition and Nanolithography with the Atomic Force Microscope, Scanning Probe Microscopy of Polymers," T. Boland, E.E. Johnston, A. Huber, and B.D. Ratner, eds, B.D. Ratner and V. Tsukruk, ACS Symposium Series 694, Washington, D.C., 342-350, 1998.
96. ISACB Essay, B.D. Ratner, International Society for Applied Cardiovascular Biology (ISACB) Circulator, Spring/Summer, 11-12, 1998.
97. "Ophthalmologic Biocompatibility: Anachronism or Oxymoron?" Guest Editorial, B.D. Ratner, J. Cataract Refract. Surg. Vol. 24, 288-290, 1998.
98. "Template-Nanostructured Protein Recognition Surfaces Based on Plasma Deposition," B.D. Ratner and H. Shi, International Forum on New Frontiers in Functional Organic Nanomaterials, 1998.
99. "Recognition templates for biomaterials with engineered bioreactivity," H. Shi, B.D. Ratner, Current Opinion in Solid State & Materials Science, 4, 395-402, 1999.
100. "Characterization of Delivery Systems, Surface Analysis and Controlled Release Systems," B. D. Ratner, C. Kwok, The Encyclopedia of Controlled Drug Delivery, (E. Mathiowitz, editor), Elsevier, 261-269 Amsterdam, 1999.
101. "Protein Contact Printing for a Surface Plasmon Resonance Biosensor with On-chip Referencing," H. Lu, J. Homola, C.T. Campbell, G. G. Nenninger, S.S. Yee, B.D. Ratner, Sensors and Actuators B, in press, 2000.
102. "Blood Compatibility – A Perspective," B. D. Ratner, Journal of Biomaterials Science, Polymer Edition, Special Edition: Blood Compatibility at the Close of the 20<sup>th</sup> Century, 11 (9), 1106-1119, 2000.
103. "Chemical and Contact Mechanical Characterization of Thin Plasma Deposited Hexafluoropropylene Films," R. Luginbuehl, M.D. Garrison, R.M. Overney, L. Weiss, H. Schieferdecker, S. Hild and B.D. Ratner, Fluorinated Surfaces, Coatings, and Films, ACS Symposium Series, No. 787, D.G. Castner and D.W. Grainer, eds., American Chemical Society, 187-202 2001.

104. "Nanostructures, Microscale Technologies and Plasma Deposited Films," B.D. Ratner, Plasma and Polymers, Vol 6, No. 3, 191-193, 2001.
105. "Protein Patterning with Programmable Surface Chemistry Chips," Y. Wang, X. Cheng, Y. Hanein, B. D. Ratner, and K. F. Bohringer, Sixth International Conference on Miniaturized Chemical and Biochemical Analysis Systems (Micro TAS 2002), vol. 1, 482-484, 2002.
106. "Storage and Translational Issues in Reparative Medicine: Breakout Session Summary," J.D. Kocsis, M. Toner, D.K. Anderson, K. Brockbank, L. Germain, R.C. Lee, B.D. Ratner, Ann N Y Acad. Sci., Jun, 961:276-8, 2002.
107. "Selective Attachment of Multiple Cell Types on Thermally Responsive Polymer," Y. Wang, X. Cheng, Y. Hanein, A. Shastry, D. D. Denton, B. D. Ratner, K. F. Bohringer, The 12<sup>th</sup> International Conference on Solid-State Sensors and Actuators (Transducers03), Boston, June 6-12, 2003.
108. "Bioinspired Implant Materials Befuddle Bacteria," J.D. Bryers, B.D. Ratner, ASM News, vol. 70(5), 232-237, 2004.
109. "Biomaterials with tightly controlled pore size that promote vascular in-growth," A.J. Marshall, C.A. Irvin, T. Barker, E.H. Sage, K.D. Hauch and B.D. Ratner, ACS Polymer Preprints, Vol. 45, No. 2, 100-101, 2004.
110. "Poly(vinyl alcohol)-Amino Acid Hydrogels Fabricated into Tissue Engineering Scaffolds by Colloidal Gas Aphron Technology," E. Donaldson, J. Cuy, P. Nair, B.D. Ratner, Macromolecular Symposia, 2005, In Press.
111. "Engineering Surface Micro-structure to Control Fouling and Hysteresis in Droplet Based Microfluidic Bioanalytical Systems," A. Shastry, S. Goyal, A. Epilepsia, M. J. Case, S. Abbasi, B. D. Ratner, K. F. Bohringer, Technical Digest of the 2006 Solid-State Sensor and Actuator Workshop, Transducer Research Foundation, Cleveland, 2006.
112. "Biomaterials Approaches to Combating Oral Biofilms and Dental Disease," J.D. Bryers, B.D. Ratner, BMC Oral Health 2006, 6(Suppl 1):S15, 15 June 2006. Open access proceedings: <http://www.biomedcentral.com/content/pdf/1472-6831-6-S1-S15.pdf>.
113. "Engineering Organs: Heart and Esophagus," B. D. Ratner, Chemical Engineering Progress, Dec, Vol. 103, No. 12, S6-10, 2007.

## **Book Chapters**

1. "Surface Grafted Polymers for Biomedical Applications," B.D. Ratner and A.S. Hoffman, in Synthetic Biomedical Polymers: Concepts and Practices, M. Szycher and W.J. Robinson, eds., Technomic Publishing Co., Westport, CT, 133-151, 1980.
2. "Surface Characterization of Hydrophilic-Hydrophobic Copolymer Model Systems. I. A Preliminary Study," B.D. Ratner and A.S. Hoffman, in Adhesion and Adsorption of Polymers, Polym. Sci. Technol. Series, Vol. 12B, L.H. Lee, ed., Plenum Press, New York, 691-706, 1980.
3. "Biomedical Applications of Hydrogels: Review and Critical Appraisal," B.D. Ratner, in Biocompatibility of Clinical Implant Materials, Vol. II, D.F. Williams, ed., CRC Press, Boca Raton, FL, 145-175, 1981.
4. "Guidelines for Blood-Material Interactions - Devices and Technology Branch, Division of Heart and Vascular Diseases, National Heart, Lung and Blood Institute," NIH Publication No. 85-2185, revised July, 1985, U.S. Department of Health and Human Services, L.V. McIntire, V.P. Addonizio, D.L. Coleman, S.G. Eskin, L.A. Harker, J.L. Kardos, B.D. Ratner, F.J. Schoen, M.V. Sefton and F.A. Pitlick.
5. "The Study of Interfacial Proteins and Biomolecules by X-ray Photoelectron Spectroscopy," R.W. Paynter and B.D. Ratner, in Surface and Interfacial Aspects of Biomedical Polymers, Vol. 2, J.D. Andrade, ed., Plenum Press, New York, 189-216, 1985.
6. "Graft Copolymer and Block Copolymer Surfaces," B.D. Ratner, in Surface and Interfacial Aspects of Biomedical Polymers, Vol. 1, J.D. Andrade, ed., Plenum Press, New York, 373-394, 1985.
7. "Electron Spectroscopy for Chemical Analysis: Applications in the Biomedical Sciences," B.D. Ratner and B.J. McElroy, in Spectroscopic Methods in the Biomedical Sciences, R.M. Gendreau, ed., CRC Press, Boca Raton, FL, 107-140, 1986.
8. "Hydrogel Surfaces," B.D. Ratner, in Hydrogels in Medicine and Pharmacy, N.A. Peppas, ed., CRC Press, Boca Raton, FL, 85-94, 1986.
9. "Surface Properties of Biomaterials," B.D. Ratner, A.B. Johnston and T.J. Lenk, in Encyclopedia of Medical Devices and Instrumentation, J.G. Webster, ed., John Wiley and Sons, New York, 366-387, 1988.
10. "Static Secondary Ion Mass Spectroscopy: A New Technique for the Characterization of Biomedical Polymer Surfaces", D.G. Castner and B.D. Ratner in Surface Characterization of Biomaterials, B.D. Ratner, ed., Elsevier Press, 65-81, 1988.
11. "ESCA and Static SIMS Studies of Polyurethane Surfaces", B.D. Ratner, D. Briggs, M.J. Hearn, S.C. Yoon and P.G. Edelman, in Surface Characterization of Biomaterials, B.D. Ratner, ed., Elsevier Press, The Netherlands, 317-329, 1988.
12. "The Surface Characterization of Biomedical Materials: How Finely Can We Resolve Surface Structure?" B.D. Ratner, in The Surface Characterization of Biomedical Materials, B.D. Ratner, Ed., Elsevier Press, The Netherlands, 13-36, 1988.
13. "Polyurethane Surfaces: Solvent and Temperature Induced Structural Rearrangements," B.D. Ratner and S.C. Yoon, in Polymer Surface Dynamics, J.D. Andrade, ed., Plenum Publishing Corp., NY, 137-152, 1988.
14. "Biomedical Applications of Synthetic Polymers," B.D. Ratner, in Comprehensive Polymer Science, Vol. 7, Part 1, "Generic Polymer Systems and Applications," S.L. Aggarwal, ed., Pergamon Press, Oxford, UK, 201-247, 1989.
15. "The Surface Structure and Properties of Biomaterials," B.D. Ratner, in Concise Encyclopedia of Medical & Dental Materials, D. Williams, ed., Pergamon Press, Oxford, UK, 337-346, 1990.

16. "Plasma Deposition and Treatment for Biomaterial Applications," B.D. Ratner, A. Chilkoti, and G.P. Lopez, in Plasma Deposition, Treatment and Etching of Polymers, R. D'Agostino, ed., Academic Press, San Diego, 463-516, 1990.
17. "Biomaterials: Surface Structure and Properties," B.D. Ratner, in Encyclopedia of Materials Science and Engineering, Suppl., Vol. 2., R.W. Cahn, ed., Pergamon Press, Oxford, UK, 739-747, 1990.
18. "Glucose-Sensitive Membranes for Controlled Release of Insulin," G. Albin, T.A. Horbett and B.D. Ratner, in Pulsed and Self-Regulated Drug Delivery, J. Kost, ed., CRC Press, Boca Raton, FL, 159-185, 1990.
19. "Static SIMS Characterization of a Styrene/p-Hydroxystyrene Copolymer Series," A. Chilkoti, D.G. Castner, B.D. Ratner, and D. Briggs, in Secondary Ion Mass Spectrometry (SIMS VII), A. Benninghoven, C.A. Evans, K.D. McKeegan, H.A. Storms, H.W. Werner, Eds., John Wiley & Sons, Chichester, 769-772, 1990.
20. "Characterization of the Poly(ether ether ketone)/Copper Interface. Preliminary Electron Spectroscopy for Chemical and Analysis Studies," R.D. McElhaney, D.G. Castner, and B.D. Ratner, in Metallization of Polymers, ACS Symposium Series 440, E. Sacher, J.J. Pireau, and S.P. Kowalczyk, eds., ACS, Washington, D.C., 370-3778, 1990.
21. "Materials Considerations for Improved Cardiac Valve Prostheses," F.J. Schoen, R.J. Levy, B.D. Ratner, M.D. Lelah and G.W. Christie, in Replacement Cardiac Valves, E. Bodnar and R. Frater, eds., Pergamon Press, London, 357-381, 1991.
22. "Developing Multivariate Statistical Models of the Surface Chemistry of Organic Plasma Deposited Films Based on the Static SIMS Spectra of Model Homopolymers," A. Chilkoti, B.D. Ratner, D. Briggs, in SIMS VIII, A. Benninghoven, K.T.F. Jasnssen, J. Tumpner, H.W. Werner, eds., John Wiley and Sons, Chichester, UK, 815-818, 1992.
23. "Surface Characterization of EUROBIOMAT Reference Polymers," D.G. Castner, B.D. Ratner, and D.K. Leach-Scampavia, in The Reference Materials of the European Communities, W. Lemm, ed., Kluwer Academic Publishers, Dordrecht, 3-16, 1992.
24. "Chemical Derivatization Methods for Enhancing the Analytical Capabilities of X-ray Photoelectron Spectroscopy and Static Secondary Ion Mass Spectrometry," A. Chilkoti and B.D. Ratner, in Surface Characterization of Advanced Polymers, L. Sabbatini and P.G. Zamboni, eds., VCH Publishing, Weinheim, Germany, 221-256, 1993.
25. "Contact Lens Deposition and Spoilage," B.D. Ratner, T.A. Horbett and N.B. Mateo, in A Textbook of Contact Lens Practice, M. Ruben and M. Guillon, eds., Chapman and Hall, London, 1083-1098, 1994.
26. "Biomaterials Science -- An Interdisciplinary Endeavor," B.D. Ratner, in Biomaterials Science: An Introduction to Materials in Medicine, B.D. Ratner, A. Hoffman, F.J. Schoen, and J. Lemons, eds., Academic Press, San Diego, 1-8, 1996.
27. "Surface Properties of Materials--Characterization of Biomaterials Surfaces, (Chap.1, 1.3), B.D. Ratner, in Biomaterials Science: An Introduction to Materials in Medicine, B.D. Ratner, A. Hoffman, F.J. Schoen, and J. Lemons, eds., Academic Press, San Diego, 21-35, 1996.
28. "Classes of Materials Used in Medicine--Thin Films, Grafts, and Coatings," (Chap. 2.2.9), B.D. Ratner and A.S. Hoffman, in Biomaterials Science: An Introduction to Materials in Medicine, B.D. Ratner, A. Hoffman, F.J. Schoen, and J. Lemons, eds., Academic Press, San Diego, 105-115, 1996.
29. "Testing of Blood-Materials Interactions," (Chap. 5, 5.4), S.R. Hanson and B.D. Ratner, in Biomaterials Science: An Introduction to Materials in Medicine, B.D. Ratner, A. Hoffman, F.J. Schoen, and J. Lemons, eds., Academic Press, San Diego, 228-238, 1996.
30. "Correlation, Surface Chemistry and Biomaterials Science," (Chap. 9.9.7), B.D. Ratner, in Biomaterials Science: An Introduction to Materials in Medicine, B.D. Ratner, A. Hoffman, F.J. Schoen, and J. Lemons, eds., Academic Press, San Diego, 445-450, 1996.

31. "Perspectives and Possibilities in Biomaterials Science," (Chap. 11.0), B.D. Ratner, in Biomaterials Science: An Introduction to Materials in Medicine, B.D. Ratner, A. Hoffman, F.J. Schoen, and J. Lemons, eds., Academic Press, San Diego, 465-468, 1996.
32. "Surface Analysis for Biomaterials and Biological Systems," B.D. Ratner, D.G. Castner, in Surfaces, Vacuum and Their Applications. Vol. AIP Conference Proceedings 378, I. Hernandez-Calderon, R. Asomoza, eds., American Institute of Physics, Woodbury, NY, 524-529, 1996.
33. "Surfaces in Biology and Biomaterials: Description and Characterization, B.D. Ratner, S.C. Porter, in Interfacial Phenomena and Bioproducts, J.L. Brash, and P.W. Wojciechowski, eds., Marcel Dekker, Inc., New York, NY, 57-84, 1996.
34. "Surface Modification of Polymeric Biomedical Applications: Chemical, Biological, and Surface Analytical Challenges," B.D. Ratner, in Surface Modification of Polymeric Biomaterials, B.D. Ratner, D.G. Castner, eds., Plenum Press, New York, 1-9, 1997.
35. "XPS and SSIMS Characterization of Surfaces Modified by plasma Deposited Oligo(glyme Films," E. E. Johnston and B.D. Ratner, in Surface Modification of Polymeric Biomaterials, B.D. Ratner, D.G. Castner, eds., Plenum Press, New York, 35-44, 1997.
36. "Deposition of Fluorocarbon Films by Remote RF Glow Discharge," D.G. Castner, P. Favia, B.D. Ratner, in Surface Modification of Polymeric Biomaterials, B.D. Ratner, D.G. Castner, eds., Plenum Press, New York, 45-52, 1997.
37. "Surface Diagnostics of Plasma-Treated Materials," B.D. Ratner, in Plasma Treatments and Depositions of Polymers, ed. R. d'Agostino, Kluwer Academic Publishers, Dordrecht, The Netherlands, 211-220, 1997.
38. "Biomaterials Science: Overview and Opportunities with Special Reference to Organic and Polymeric Glow Discharge Plasma Treatments," B.D. Ratner, in Plasma Treatments and Depositions of Polymers, ed. R. d'Agostino, Kluwer Academic Publishers, Dordrecht, The Netherlands, 1997, 453-464, 1997.
39. "RF of Plasma Deposition of PEO-Like Films: Surface Characterization and Inhibition of Pseudomonas Aeruginosa Accumulation," E.E. Johnston, B.D. Ratner, J.D. Bryers, in Plasma Treatments and Depositions of Polymers, ed. R. d'Agostino, Kluwer Academic Publishers, Dordrecht, The Netherlands, 465-476, 1997.
40. "Electron Spectroscopy for Chemical Analysis," B.D. Ratner and D.G. Castner, in Surface Analysis - The Principal Techniques, J. C. Vickerman, ed., John Wiley and Sons, Chichester, UK, 43-98, 1997.
41. "Recognition and Nanolithography with the Atomic Force Microscope," T. Boland, E.E. Johnston, A. Huber, and B.D. Ratner, in ACS Symposium Series 694 Scanning Probe Microscopy of Polymers, B.D. Ratner, V.V. Tsukruk, eds., American Chemical Society, Washington, D.C., 342-343, 1998.
42. "Protein Adsorption: Friend or Foe?" E. Johnson and B.D. Ratner, in Immobilized Biomolecules in Analysis A Practical Approach, eds., T. Cass and F. S. Ligler, Oxford University Press, 79-94, 1998.
43. "Nanobiotechnology at the Confined Biomaterial Interface," R. Luginbuhl, R.M. Overney, and B.D. Ratner in ACS Symposium Series 781 Interfacial Properties on the Submicrometer Scale, J. Frommer and R.M. Overney, eds., American Chemical Society, 179-196, 2001.
44. "A Perspective on Titanium Biocompatibility," B.D. Ratner, in Titanium in Medicine, D.M. Brunett, P. Tengvall, M. Textor, P. Thomsen, eds., Springer Publishers, Berlin, 1-12, 2001.
45. "Biomedical Applications of Plasma-Deposited Thin Films," K.J. Kitching and B.D. Ratner, in Plasma Polymer Films, H. Biedermann, ed., Imperial College Press, 325-377, 2004.
46. "Surface Analysis of Biomaterials and Biomineralization," B.D. Ratner, in Learning From Nature How to Design New Implantable Biomaterials: From Biomineralization Fundamentals to Biomimetic Materials and

Processing Routes, NATO Advanced Study Institute Volume, eds. R.L. Reis and S. Weiner, Kluwer Publishers, 75-85, 2004.

47. "Biomaterials Science: A Multidisciplinary Endeavor," B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, in Biomaterials Science: An Introduction to Materials in Medicine, 2nd ed., B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, eds., Elsevier Academic Press, San Diego, 1-9, 2004.
48. "A History of Biomaterials," B.D. Ratner, in Biomaterials Science: An Introduction to Materials in Medicine, 2nd ed., B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, eds., Elsevier Academic Press, San Diego, 10-20, 2004.
49. "Surface Properties and Surface Characterization of Materials," B.D. Ratner, in Biomaterials Science: An Introduction to Materials in Medicine, 2nd ed., B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, eds., Elsevier Academic Press, San Diego, 40-59, 2004.
50. "Nonfouling Surfaces," B.D. Ratner and A.S. Hoffman, in Biomaterials Science: An Introduction to Materials in Medicine, 2nd ed., B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, eds., Elsevier Academic Press, San Diego, 197-201, 2004.
51. "Physicochemical Surface Modification of Materials Used in Medicine," B.D. Ratner and A.S. Hoffman, in Biomaterials Science: An Introduction to Materials in Medicine, 2nd ed., B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, eds., Elsevier Academic Press, San Diego, 201-217, 2004.
52. "Some Background Concepts," B.D. Ratner, in Biomaterials Science: An Introduction to Materials in Medicine, 2nd ed., B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, eds., Elsevier Academic Press, San Diego, 237, 2004.
53. "Introduction to Testing Biomaterials," B.D. Ratner, in Biomaterials Science: An Introduction to Materials in Medicine, 2nd ed., B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, eds., Elsevier Academic Press, San Diego, 355, 2004.
54. "Evaluation of Blood-Materials Interactions," S. R. Hanson and B.D. Ratner, in Biomaterials Science: An Introduction to Materials in Medicine, 2nd ed., B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, eds., Elsevier Academic Press, San Diego, 367-378, 2004.
55. "Degradation of Materials in the Biological Environment," B.D. Ratner, in Biomaterials Science: An Introduction to Materials in Medicine, 2nd ed., B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, eds., Elsevier Academic Press, San Diego, 411, 2004.
56. "Correlation, Surfaces and Biomaterials Science," B.D. Ratner, in Biomaterials Science: An Introduction to Materials in Medicine, 2nd ed., B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, eds., Elsevier Academic Press, San Diego, 765-769, 2004.
57. "Perspectives and Possibilities in Biomaterials Science," B.D. Ratner, F.J. Schoen, J.E. Lemons, and A.S. Hoffman, in Biomaterials Science: An Introduction to Materials in Medicine, 2nd ed., B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, eds., Elsevier Academic Press, San Diego, 805-809, 2004.
58. "Esophagus: A Tissue Engineering Challenge," B.D. Ratner, K.S. Chian, C.M. Giachelli, B.L. Beckstead, and A.C. Ritchie, in The Biomedical Engineering Handbook, 3rd ed., CRC Press, Inc., Boca Raton, 2004, In Press.
59. "Novel Biophysical Techniques for Investigating Long-Term Cell Adhesion Dynamics on Biomaterial Surfaces," Z. Feng, N. Cai, V. Chan, P.S. Mhaisalka, K.S. Chian, B.D. Ratner, and K. Liao, in Tissue Engineering (ed John P. Fisher), Advances in Experimental Medicine and Biology, Springer Publishing, NY, 585:151-65, 2006.

## **Editorial**

Journal of Biomedical Materials Research - Assistant Editor

Polymeric Biomaterials – Former Member of the Editorial Board

Biomaterials - Editorial Board

Science and Engineering of Composite Materials - Former Member of the Editorial Board

Journal of Biomaterials Science - Editorial Board

Biomaterials: Interfacial Phenomena and Applications, ACS Advances in Chemistry Series No. 199, S.L. Cooper and N.A. Peppas, eds., A.S. Hoffman and B.D. Ratner, assoc. eds., American Chemical Society, Washington, D.C., 1982.

Polymers as Biomaterials, S. Shalaby, A.S. Hoffman, B.D. Ratner and T.A. Horbett, eds., Plenum Press, New York, 1984.

Surface Characterization of Biomaterials, B.D. Ratner, ed., Elsevier Press, 1989.

International Directory of Biomaterials Education Programs 1988, B.D. Ratner, ed., Society for Biomaterials, 1988.

Progress in Biomedical Engineering Series, Elsevier Press - Former Member of the Editorial Advisory Board

Surface Analysis and Its Applications Book Series, Wiley Press - Editorial Board

Cells and Materials, Quarterly Journal - Former Member of the Editorial Board

Surface Science Spectra - Former Member of the Editorial Board

Colloids and Surfaces; B: Biointerfaces - Editorial Board

Plasmas and Polymers, B.D. Ratner, and R. D'Agostino, eds., Plenum Press, 1995-1999, Member of Editorial Board

Biomaterials: Current Opinion in Solid State & Materials Science. 1999 – Editor

Biomaterial Science: An Introduction, B.D. Ratner, lead ed., (F. Schoen, J. Lemons and A.S. Hoffman, co-eds.), Academic Press, 1996.

Surface Modification of Polymeric Biomaterials, B.D. Ratner, D.G. Castner, eds., Plenum Press, New York, 1997.

Journal of Undergraduate Research in Bioengineering – Editor

Scanning Probe Microscopy of Polymers, (ACS Symposium Series 694). Edited by B. D. Ratner and V. V. Tsukruk. New York: Oxford University Press, 1998

Biomacromolecules – Editorial Board

Journal of Biomaterials Science; Polymer Edition; Special Edition Blood Compatibility at the Close of the 20<sup>th</sup> Century – Editor, Volume 11, Number 11, 2000

Biomaterial Science: An Introduction to Materials in Medicine, 2<sup>nd</sup> Ed., B.D. Ratner, A.S. Hoffman, F.J. Schoen, J.E. Lemons, Elsevier Academic Press, 2004.

Biomedical Materials: Materials for Tissue Engineering and Regenerative Medicine - Editorial Board

Nanomedicine - Editorial Board

## Letters, Abstracts, Reports

1. "Molecular Mechanism for the Interaction of Urea with Sickled Hemoglobin," B.D. Ratner and I.F. Miller, J. Am. Med. Assoc., 225, 313, 1973.
2. "Mechanism of Urea Activity in Sickling," B.D. Ratner, Letter to Editor, JAMA, 225, 313, 1973.
3. "Radiation-Grafted Acrylamide Hydrogels for Biomedical Applications," B.D. Ratner, Transactions of the 7th International Biomaterials Symposium, Society for Biomaterials, Clemson, SC, April, 1975.
4. "Radiation-Grafted Acrylamide Hydrogels for Biomedical Applications," B.D. Ratner, 24th International Symposium on Macromolecules, Jerusalem, July, 1975.
5. "The Thrombogenicity of Radiation-Grafted Polymers as Measured by the *Vena Cava* Ring Test," A.S. Hoffman, B.D. Ratner and J.D. Whiffen, Trans. Soc. Biomat., 1, 27, 1977.
6. "Blood Compatibility-Water Content Relationships for Radiation-Grafted Hydrogels," B.D. Ratner, A.S. Hoffman, S.R. Hanson, L.A. Harker and J.D. Whiffen, Abstracts of the 17th Microsymposium on Macromolecules (Medical Polymers: Chemical Problems), Prague, Aug. 15-18, 1977, C4/1-4.
7. "*In Vivo* and *Ex Vivo* Evaluation of Biomaterials Thrombogenicity," invited discussion contribution, Abstracts of the 17th Microsymposium on Macromolecules (Medical Polymers: Chemical Problems), Prague, Aug. 15-18, 1977, C74/1.
8. "Cell Adhesion to Hydrophilic-Hydrophobic Copolymers," B.D. Ratner, S.D. Hauschka, T.A. Horbett, A.S. Hoffman and J.J. Rosen, Trans. Soc. Biomat., 2, 64, 1978.
9. "Surface Properties of Polymers Correlated with Platelet Consumption," B.D. Ratner, S.R. Hanson, R.E. Baier, L.A. Harker and A.S. Hoffman, Proceedings of the 52nd Colloid and Surface Symposium, Knoxville, TN, June 12-15, 1978, 64.
10. "*In Vitro* Modelling of the Soft Tissue Response to Biomaterial Implants," J.J. Rosen, B.D. Ratner, T.A. Horbett, M.B. Schway and A.S. Hoffman, 7th Conference and Exposition, Canadian Medical and Biological Engineering Society, Vancouver, Canada, Aug. 13-16, 1978.
11. "Comparison of *In Vitro*, *In Vivo* and *Ex Vivo* Blood Tests on a Series of Polar/Apolar Polymeric Biomaterials," A.S. Hoffman, L.A. Harker, S.D. Hanson, T.A. Horbett and B.D. Ratner, 17th Congress of the International Society of Hematology, Paris, July 23-29, 1978.
12. "Studies of Cell Adhesion to Biomaterials," J.J. Waldberger, T.A. Horbett, B.D. Ratner, J.J. Rosen and A.S. Hoffman, Transactions of the 11th International Biomaterials Symposium, Society of Biomaterials, Clemson, SC, April 28-May 1, 1979, Vol. 3, 144.
13. "Interactions of Natural and Chemically Modified Aortic Tissue Protein with Blood," A.S. Hoffman, T.A. Horbett, S. Hanson and B.D. Ratner, National Institutes of Health Report NIH-NO1-HV-4-2970-4, July, 1979.
14. "Some Unusual Effects in the Radiation Grafting of Acrylamide to Polymer Substrates," A.S. Hoffman and B.D. Ratner, Abstracts of Papers - ACS/CSJ Chemical Congress, Honolulu, HI, April 1-6, 1979, Part II, Paper #255.
15. "Surface Characterization of Hydrophilic-Hydrophobic Copolymer Model Systems," B.D. Ratner and A.S. Hoffman, Abstracts of Papers - ACS/CSJ Chemical Congress, Honolulu, HI, April 1-6, 1979, Part II, Paper #156.
16. "Surface Energy Analysis of Copolymer Biomaterials Based on Contact Angles," A.S. Hoffman, B.D. Ratner and Y.C. Ko, Abstracts of Papers - 34th N.W. Regional ACS Meeting, Richland, WA, June 13-15, 1979, Paper #5.

17. "Surface Characterization Studies on Polyetherurethanes for Biomedical Applications," B.D. Ratner, Abstracts of Papers - 34th N.W. Regional ACS Meeting, Richland, WA, June 13-15, 1979, Paper #6.
18. "In Vitro Platelet Adhesion to a Chemically Homologous Series of Copolymers," R.S. Schaffnit, T.A. Horbett, B.D. Ratner and A.S. Hoffman, Preprints of the First World Congress on Biomaterials, Baden, Austria, 2.2.1, 1980.
19. "Evaluation of Artificial Surfaces Using a Baboon Arteriovenous Shunt Model," S.R. Hanson, L.A. Harker, B.D. Ratner and A.S. Hoffman, Preprints of the First World Congress on Biomaterials, Baden, Austria, 2.2.2, 1980.
20. "The Organization of Adsorbed Protein Films: An ESCA Method of Analysis," B.D. Ratner, D. Shuttleworth, T.A. Horbett and H.R. Thomas, Preprints of the First World Congress on Biomaterials, Baden, Austria, 4.3.1, 1980.
21. "In Vivo Evaluation of Artificial Surfaces Using a Baboon Model of Artificial Thrombosis, A.S. Hoffman, S.R. Hanson, L.A. Harker, B.D. Ratner, T.A. Horbett and L.O. Reynolds, Abstracts for A.I.Ch.E. 73rd Annual Meeting, Chicago, Nov. 16-20, 1980, T-41.
22. "Adsorption of Proteins to Copolymer Contact Lens Materials from Artificial Tear Solutions," F.H. Royce, Jr., B.D. Ratner and T.A. Horbett, Abstracts for A.I.Ch.E. 73rd Annual Meeting, Chicago, Nov. 16-20, 1980, T-40.
23. "Applications of ESCA in Biomaterials Science," B.D. Ratner, Symposium on New Spectroscopic Methods for Biomedical Research, Battelle Columbus Laboratories, Oct. 20-22, 1980.
24. "Cell Adhesion Substrates Prepared by Vapor Phase Deposition of Silane Coatings," B.D. Ratner and J.J. Swalec, Proceedings of the Adhesion Society Annual Meeting, Savannah, GA, Feb. 22-25, 1981, 41-42.
25. "Poly(styrene/p-hydroxystyrene) Copolymers for Studying the Interaction of Biological Systems and Synthetic Polymers," D. Majumdar, B.D. Ratner and A.S. Hoffman, Trans. Soc. Biomat., 4, 102, 1981.
26. "Macrophage Adhesion to a Series of Hydroxyethyl Methacrylate - Ethyl Methacrylate Copolymers," T.A. Horbett, A.J. Lentz, L. Hsu, B.D. Ratner and A.S. Hoffman, Trans. Soc. Biomat., 4, 104, 1981.
27. "Correlations Between Platelet Consumption and the Surface Chemistry of Neutral Polymers in Baboon," S.R. Hanson, B.D. Ratner, A.S. Hoffman and L.A. Harker, 8th International Congress on Thrombosis and Haemostasis, Toronto, July 12-17, 1981.
28. "Cellular Interactions with Foreign Materials," T.A. Horbett, B.D. Ratner, A.S. Hoffman and S. Schwartz, Devices and Technology Branch Contractors Meeting Program, N.I.H., 104-105, 1981.
29. "Surface Thrombogenesis - Mechanisms and Prevention," A.S. Hoffman, L.A. Harker, A. Ishimaru, T.A. Horbett, B.D. Ratner, S.R. Hanson, L.O. Reynolds, N. Anderson, D. Johnson, W. Lee and M. Reidy, Devices and Technology Branch Contractors Meeting Program, N.I.H., 106, 1981.
30. "ESCA Studies of Extracted Polyurethanes and Polyurethane Extracts: Biomedical Implications," B.D. Ratner, Abstracts of the 182nd ACS National Meeting, New York, Aug. 23-28, 1981, Coll. 171.
31. "Chemical Modification of Kevlar Surfaces for Improved Adhesion to Epoxy Resin Matrices. I. Surface Characterization," T.S. Keller, A.S. Hoffman, B.D. Ratner and B.J. McElroy, Abstracts of the 182nd ACS National Meeting, New York, Aug. 23-28, 1981, Coll. 155.
32. "Surface Structure of Polyetherurethanes," B.D. Ratner, Devices and Technology Branch Contractors Meeting Program, N.I.H., 89, 1981.
33. "ESCA Studies of Polymer Surfaces for Biomedical Applications," B.D. Ratner, 2nd International Symposium on New Spectroscopic Methods for Biomedical Research, Battelle Columbus Laboratories, Columbus, Oct. 19-21, 1981.

34. "Interactions of Human Platelets with Hydroxyethyl Methacrylate (HEMA) and Ethyl Methacrylate (EMA) Hydrogels," G.A. Adams, B.D. Ratner, I.L. Stevenson, Canadian Biomaterials Society, Toronto, Oct., 1982.
35. "The *In Vivo* Interaction of Baboon Platelets with a Hydrophilic-Hydrophobic Copolymer System," A.S. Hoffman, S.R. Hanson, B.D. Ratner and L.A. Harker, Trans. Soc. Biomater., 5, 36, 1982.
36. "The Kinetics of Baboon Fibrinogen Adsorption to Polymers: *In Vitro* and *In Vivo* Studies," T.A. Horbett, C.M. Cheng, B.D. Ratner, S. Hanson and A.S. Hoffman, Trans. Soc. Biomater., 5, 89, 1982.
37. "Differential Light Scattering Detection of Microemboli Produced by Blood-Biomaterial Interactions," L.O. Reynolds, T.A. Horbett, B.D. Ratner and A.S. Hoffman, Trans. Soc. Biomater., 5, 37, 1982.
38. "Hydrophobic-Hydrophilic Copolymers as Cell Substrates: Effect on 3T3 Cell Growth Rate," T.A. Horbett, M.B. Schway and B.D. Ratner, 183rd National ACS Meeting, Las Vegas, Sept., 1982.
39. "Surface Contamination of Poly(methyl methacrylate) Intraocular Lenses and Abrasives Used to Polish Intraocular Lenses," B.D. Ratner and D.W. Meltzer, 5th U.S. Intraocular Lens Symposium, Los Angeles, April 21-23, 1982.
40. "Polyetherurethane Surfaces: Chemical and Morphological Changes Upon Extraction," B.D. Ratner, Proceedings of the IUPAC 28th Macromolecular Symposium, Amherst, July 12-16, 1982, 677.
41. "Adsorbed Protein Films Investigated by ESCA," B.D. Ratner, R.W. Paynter, T.A. Horbett and H.R. Thomas, 3rd International Symposium on New Spectroscopic Methods for Biomedical Research, Battelle Columbus Laboratories, Columbus, Oct. 18-20, 1982, 26-28.
42. H.R. Thomas, 3rd International Symposium on New Spectroscopic Methods for Biomedical Research, Battelle Columbus Laboratories, Columbus, Oct. 18-20, 1982, 29.
43. "XPS Studies of Protein Films," B.D. Ratner, R.W. Paynter, T.A. Horbett and H.R. Thomas, Pacific Conference on Chemistry and Spectroscopy, San Francisco, Oct 27-29, 1982.
44. "Surface Characterization of Biomaterials by Electron Spectroscopy for Chemical Analysis (ESCA)," B.D. Ratner, Fed. Proc., 41, 1346, 1982.
45. "Evaluation of the Blood Compatibility of Synthetic Polymers: Consensus and Significance," B.D. Ratner, Consensus Development Conference on Clinical Applications of Biomaterials, Bethesda, Nov. 1-3, 1982.
46. "Polyetherurethane Surfaces - The Importance of Molecular Weight Distribution, Bulk Chemistry and Casting Conditions," B.D. Ratner, R.W. Paynter and H.R. Thomas, International Conference on Polyurethanes in Medicine, Fellbach, W. Germany, Jan. 27-29, 1983.
47. "XPS Studies of Polymeric Materials with Biological Applications," B.D. Ratner, 5th Biennial Carl S. Marvel Symposium, Tucson, AZ, Mar. 14-15, 1983.
48. "Preferential Adsorption of Tear Proteins by Different Hydrogel Lens Materials," B.D. Ratner, T.A. Horbett and F. Royce, Jr., Bausch and Lomb 10th Annual National Research Symposium on Contact Lenses, New York, Aug. 13-14, 1983.
49. "Adsorbed Protein Films Investigated by ESCA," B.D. Ratner, R.W. Paynter, T.A. Horbett and H.R. Thomas, Trans. Soc. Biomater., 6, 120, 1983.
50. "3T3 Fibroblast Attachment to Radiation-Grafted Polytetrafluoroethylene Surfaces," A.S. Hoffman, B.D. Ratner and T.A. Horbett, Trans. Soc. Biomater., 6, 67, 1983.
51. "Polyurethane Surfaces - An XPS Study," B.D. Ratner, R.W. Paynter and H.R. Thomas, Trans. Soc. Biomater., 6, 21, 1983.

52. "Radiation-Grafted Hydrogels for Biomaterials Application: Synthesis, Structure and Composition of HEMA-EMA Graft Copolymers on LDPE Films," D. Cohn, A.S. Hoffman and B.D. Ratner, 4th European Conf. on Biomaterials, Belgium, Aug. 31 - Sept. 2, 1983.
53. "UV-Adsorbing IOLs: Note of Caution," B.D. Ratner, Letter to Editor, Ophthalmol. Times, 8, 3, 1983.
54. "Review of ACS Software: Introduction to Polymer Chemistry," B.D. Ratner, by invitation for Journal of Chemical Education, 61, A165-A167, 1984.
55. "Glucose Sensitive Membranes: Stability and Biocompatibility Studies," T.A. Horbett, J. Kost, D. Coleman and B.D. Ratner, Transactions of the 2nd World Congress on Biomaterials, 7, 341, 1984.
56. "RF Plasma-Deposited Films as Model Substrates for Studying Biointeractions," B.D. Ratner, Y. Haque, T.A. Horbett, M.B. Schway and A.S. Hoffman, Transactions of the 2nd World Congress on Biomaterials, 7, 189, 1984.
57. "Surface Modification of Small Diameter Dacron Vascular Grafts After a Tetrafluoroethylene Glow Discharge Treatment," A.S. Hoffman, A.M. Garfinkle and B.D. Ratner, Transactions of the 2nd World Congress on Biomaterials, 7, 186, 1984.
58. "Improved Patency in Small Diameter Dacron Vascular Grafts After a Tetrafluoroethylene Glow Discharge Treatment," A.S. Hoffman, A.M. Garfinkle and B.D. Ratner, Transactions of the 2nd World Congress on Biomaterials, 7, 337, 1984.
59. "Protein Adsorption to Contact Lens Materials," B.D. Ratner and T.A. Horbett, Transactions of the 2nd World Congress on Biomaterials, 7, 76, 1984.
60. "Effects of a Tetrafluoroethylene Glow Discharge on Patency of Small Diameter Dacron Vascular Grafts," A.M. Garfinkle, A.S. Hoffman, B.D. Ratner and S.R. Hanson, Abstracts for the American Society for Artificial Internal Organs, 13, 19, 1984.
61. "Polyurethane Surfaces and Interfaces: Implications for Adhesion and Bioadhesion," B.D. Ratner and A. Kaul, Abstracts for the Adhesion Society Meeting, Jacksonville, FL, Feb., 1984.
62. "Glucose Sensitive Membrane for Controlled Delivery of Insulin," T.A. Horbett and B.D. Ratner, Abstracts for the 1984 Toronto International Workshop on Insulin and Portable Delivery Systems, June 6-8, 1984.
63. "Protein Adsorption to Contact Lens Materials," B.D. Ratner and T.A. Horbett, Proceedings of the 26th Prague Meeting on Macromolecules: Polymers in Medicine and Biology, July 9-12, 1984, P5-1-P5-3.
64. "Surface and Bulk Structure of Polyetherurethanes," B.D. Ratner and A. Kaul, Abstracts for the DTB NHLBI Contractors Meeting, Rockville, MD, Dec., 1984.
65. "Toxicity of Polyetherurethane Surfaces," A. Kaul, B.D. Ratner and M.B. Schway, Trans. Soc. Biomat., 8, 193, 1985.
66. "Differential Light Scattering Technique for Detection of Microparticulates in Dense Scattering Media," L.O. Reynolds, B.D. Ratner, T.A. Horbett and A.S. Hoffman, Abstracts for the 184th National Meeting of the American Chemical Society, 1985.
67. "Insulin Transport Through Glucose Sensitive Membranes," B.D. Ratner, G. Albin and T.A. Horbett, International Symposium on New Developments in Drug Delivery Systems, Salt Lake City, UT, Feb. 27 - Mar. 1, 1985.
68. "ESCA: Biomedical Studies," B.D. Ratner, Proceedings of the 30th National Symposium of the Society for the Advancement of Materials and Process Engineering, Anaheim, CA, Mar. 19-21, 1985.

69. "Plasma-Treated Surfaces for Biomedical Applications: Compositional Analysis," D. Cohn, A.S. Hoffman, B.D. Ratner and Y. Haque, 2nd International Conference on Polymers in Medicine, Capri, Italy, June 3-7, 1985, C9.
70. "Characterization of Biomaterial Surfaces by Electron Spectroscopy for Chemical Analysis," B.D. Ratner, 2nd International Conference on Polymers in Medicine, Capri, Italy, June 3-7, 1985.
71. "Protein Adsorption Studied by Electron Spectroscopy for Chemical Analysis," B.D. Ratner, A. Bright and T.A. Horbett, 5th International Conference on Surface and Colloid Science, Potsdam, New York, June 24-28, 1985.
72. "ESCA for Biomedical Studies," B.D. Ratner, Trans. Soc. Biomat., 8, 22, 1985.
73. "Unusual Protein Adsorption to Hydrophilic/Lipophilic Methacrylate Copolymers," N. Provost, A.S. Hoffman, B.D. Ratner and T.A. Horbett, Trans. Soc. Biomat., 8, 108, 1985.
74. "Polymer Surface Structure and Blood Compatibility," B.D. Ratner, Proceedings of the 18th Conference of the Foundation for Research Conferences in Chemistry, Ohtsu City, Japan, Oct. 14-18, 1985.
75. "Surface Structure of Novel Biomedical Polyurethanes," B.D. Ratner, S.C. Yoon and R. Rahman, Abstracts for A.I.Ch.E. Meeting, Chicago, Nov. 10-14, 1985.
76. "Insulin Transport Through Glucose Sensitive Membranes for Controlled Delivery of Insulin," T.A. Horbett, G. Allan and B.D. Ratner, Abstracts for A.I.Ch.E. Meeting, Chicago, Nov. 10-14, 1985.
77. "ESCA for the Characterization of Polymers for Biomedical Applications," B.D. Ratner, Abstracts for Eastern Analytical Symposium, New York, Nov. 18-24, 1985.
78. "Synthetic Polymers Get Under the Skin," B.D. Ratner and N.B. Mateo, Industrial and Chemical News, 7, 32-33, 1986.
79. "*In Vitro* Studies of the Enzymatic Biodegradation of Polyetherurethanes," B.D. Ratner, K.W. Gladhill and T.A. Horbett, Trans. Soc. Biomat., 9, 190, 1986.
80. "ESCA Studies of Protein Film Organization on Surfaces," A.B. Johnston, B.D. Ratner, T.A. Horbett and A.P. Mackenzie, Trans. Soc. Biomat., 9, 160, 1986.
81. "Fibrinogen Adsorption from Plasma: Effects of Substrate Surface Chemistry," S.M. Slack, T.A. Horbett, and B.D. Ratner, Trans. Soc. Biomat., 10, 60, 1987.
82. "Observed Spectral Changes in Adsorbed Bovine Serum Albumin," T.J. Lenk, B.D. Ratner, and R.M. Gendreau, Trans. Soc. Biomat., 10, 41, 1987.
83. "Titanium Surfaces: ESCA, FTIR, Protein Adsorption and Cell Interaction Studies," B.D. Ratner, P. Lew, T. Lenk, and T.A. Horbett, Trans. Soc. Biomat., 10, 206, 1987.
84. "Surface Analysis of Biomedical Polymers: How Precisely Can We Resolve the Surface Structure?" B.D. Ratner, Abstracts, 61st Colloid & Surface Science Symposium, Ann Arbor, MI, June 21-24, 1987.
85. "XPS Characterization of Polymer Samples for Biomedical Applications," D.G. Castner and B.D. Ratner, 3rd National Symposium, American Vacuum Society, Anaheim, CA, November 2-6, 1987.
86. Book Review (Invited): Water and Ions in Biological Systems, (A. Pullman, V. Vassilescu, and L. Packer, eds.), B.D. Ratner, Biomaterials, 8, 506, 1987.
87. Book Review (Invited): Advances in Biomedical Polymers, (C.G. Gebelein, ed.), B.D. Ratner. For The Torch, (Society for Biomaterials) 10, 1987.
88. "SIMS for the Analysis of Polyurethane Surfaces", B.D. Ratner, M.J. Hearn, D. Briggs and S.C. Yoon, Trans. Third World Biomaterials Congress, 11, 435, 1988.

89. "Adhesion of Corneal Endothelium to RF Plasma- Deposited Coatings on PMMA IOL Disks," N.B. Mateo and B.D. Ratner, Trans.Third World Biomaterials Congress 11, 351, 1988.
90. "Surface and Bulk Compositional Differences in ABC Block Copolymers of Poly(Dimethylsiloxane), Poly(Ethylene Oxide), and Heparin," D. Grainger, J. Feijen, B.D. Ratner, D. Castner, Y.K. Sung, T. Okano, S.W. Kim, Trans. Third World Biomaterials Congress, 11, 285, 1988.
91. "Surface Characterization of Vialon Polyurethanes by X-ray Photoelectron Spectroscopy," D.G. Castner, B.D. Ratner, and A.S. Hoffman, Trans. Third World Biomaterials Congress, 11, 436, 1988.
92. "Relating the Surface Properties of Intraocular Lens Materials to Endothelial Cell Adhesion Damage," B.D. Ratner and N.B. Mateo, Abstracts of the 2nd International Cataract, Implant, Microsurgical & Refractive Keratoplasty Meeting, July 3, 1988, Nagoya, Japan.
93. "Interfacial Mobility in Polyurethanes," B.D. Ratner, P.G. Edelman, S.C. Yoon, Abstracts, 194th National Meeting, American Chemical Society, New Orleans, Aug. 30 - Sept. 4, 1988.
94. "ESCA and Static SIMS Studies on Polyurethane Surfaces," B.D. Ratner, P.G. Edelman, D.G. Castner, S.C. Yoon, D. Briggs, M. Hearn, Abstracts, 194th National Meeting, American Chemical Society, New Orleans, Aug. 30 - Sept. 4, 1988.
95. "Surface Properties of Polyurethanes with C18 Pendant Groups Attached to the Hard Segments by Two Different Routes," P.G. Edelman and B.D. Ratner, Abstracts of the 196th Annual Meeting of the American Chemical Society, Los Angeles, CA., Sept. 25-30, 1988.
96. "Effect of Monomer Type on the Surface Chemistry of RF-Plasma Deposited surfaces Prepared for Cell Culture," A. Chilkoti and B.D. Ratner, Abstracts of the 196th Annual Meeting of the American Chemical Society, Los Angeles, CA., Sept. 25-30, 1988.
97. "Shear Stress Induced Platelet Refractoriness in Blood-Biomaterial Evaluations," J.A. Chinn, T.A. Horbett, and B.D. Ratner, Abstracts of the 196th Annual Meeting of the American Chemical Society, Los Angeles, CA., Sept. 25-30, 1988.
98. "Surface and Interfacial Studies of Polyurethane Block Copolymers," B.D. Ratner, Abstracts of the 196th Annual Meeting of the American Chemical Society, Los Angeles, CA., Sept. 25-30, 1988.
99. "Variation Between Surface and Bulk Composition in Novel and Conventional Segmented Polyurethanes," B.D. Ratner, P.G. Edelman and D.G. Castner, 35th National Symposium and Topical Conference, American Vacuum Society, Oct. 3-7, 1988.
100. "Using Angle Dependent XPS Measurements to Construct Depth Profiles with Nanometer Scale Resolution: The Effects of Aperture Size and Geometry," B.J. Tyler, B.D. Ratner and D.G. Castner, Abstracts of the 35th National Symposium and Topical Conference, American Vacuum Society, Oct. 3-7, 1988.
101. "Surface Characterization of Butyl Methacrylate Polymers with XPS and Static SIMS," D.G. Castner and B.D. Ratner, Abstracts of the 35th National Symposium and Topical Conference, American Vacuum Society, Oct. 3-7, 1988.
102. "Surface Characterization of Hydrogels Prepared by Three Methods," B.D. Ratner and G.P. Lopez, Abstracts of the A.I.Ch.E. Annual Meeting, Washington, D.C., Nov. 27 - Dec. 2, 1988.
103. "Fibrinogen Adsorption to Polyurethanes," T.J. Lenk, R.J. Rapoza, K.K. Chittur, and B.D. Ratner, Abstracts of the American Institute of Chemical Engineers Annual Meeting, Washington, Nov. 27 - Dec. 2, 1988.
104. "Block Copolymers: Solutions and Interfaces," P.G. Edelman and B.D. Ratner, Abstracts of the A.I.Ch.E. Annual Meeting, Washington, D.C., Nov. 27 - Dec. 2, 1988.

105. "Surface and Bulk Structure of Polyetherurethanes," B.D. Ratner, T.A. Horbett, A.S. Hoffman, P.G. Edelman, B.J. Tyler, Abstracts of the DTB Contractors Meeting, Bethesda, MD., Dec. 7, 1988.
106. "Static SIMS: A New Tool for Studying the Surface Molecular Structure of Biomaterials," B.D. Ratner, Trans. Soc. Biomat. 12, 1989.
107. "Infrared Detection of Time-dependent Changes in Fibrinogen Adsorbed to Polyurethanes," T.J. Lenk, K.K. Chittur, B.D. Ratner, Trans. Soc. Biomat. 12, 1989.
108. "Characterization of Methacrylate Polymer Surfaces with Static Secondary Ion Mass Spectroscopy," D.G. Castner and B.D. Ratner, Trans. Soc. Biomat. 12, 1989.
109. "Acetone-N<sub>2</sub> Glow Discharge Modified Surfaces: Investigation of Surface Chemistry, Protein Adsorption, and Endothelial Cell Growth," A. Chilkoti, S.I. Ertel, B.D. Ratner, T.A. Horbett, and D. Briggs, Trans. Soc. Biomat. 12, 99, 1989.
110. "Using Solvent Precipitation, HPGPC and FTIR to Study the Heterogeneity of Two Medical Grade Polyurethanes," B.J. Tyler and B.D. Ratner, Trans. Soc. Biomat. 12, 198, 1989.
111. "Protein Adsorption to Plasma Deposited Hydrogels," G.P. Lopez, R.J. Rapoza, B.D. Ratner and T.A. Horbett, Abstracts of the ACS 63rd Colloid and Surface Science Symposium, June 18-21, 1989, Seattle, WA.
112. "Static Secondary Ion Mass Spectroscopy (SIMS) Characterization of Polymer Surfaces," D.G. Castner and B.D. Ratner, Abstracts of the ACS 63rd Colloid and Surface Science Symposium, June 18-21, 1989, Seattle, WA.
113. "Transitions in Fibrinogen Adsorbed to Polyurethanes," T.J. Lenk, R.J. Rapoza, T.A. Horbett, B.D. Ratner, Abstracts of the ACS 63rd Colloid and Surface Science Symposium, June 18-21, 1989, Seattle, WA.
114. "Hydrogen bonding in segmented polyurethanes," S.C. Yoon, Y.K. Sung and B.D. Ratner, Preprints of the IUPAC International Symposium: Molecular Design of Functional Polymers, The Polymer Society of Korea, Seoul, Korea, June 26-28, 497-498, 1989.
115. "RF-plasma Deposited Films as Cell Growth Substrates," B.D. Ratner, A. Chilkoti, S. Ertel, U.S.A.-Italy Joint Workshop on Polymers for Biomedical Applications, Bologna, Italy, Sept. 1, 1989.
116. "Effect of Reduced Substrate Temperature on Film Chemistry in Plasma Deposition of Organics, G.P. Lopez, B.D. Ratner, R.J. Rapoza and T.A. Horbett, ISPC-9, Pugnuchiuso, Italy, Sept. 4-8, 1989.
117. "Surface Characterization of a Styrene/p-hydroxystyrene Copolymer Series using XPS, Static SIMS and Chemical Derivatization Techniques," A. Chilkoti, D.G. Castner and B.D. Ratner, SIMS VII, Sept. 2-8, 1989, Monterey, CA.
118. "XPS and SSIMS Studies of Deuterium and Methyl Substituted Polystyrene," A. Chilkoti, D.G. Castner and B.D. Ratner, A.V.S. Northwest Chapter, Sept. 1989, Seattle, WA.
119. "Biomolecules and Surfaces," B.D. Ratner, D.G. Castner, T.A. Horbett, T. Lenk, K. Lewis and R. Rapoza, A.V.S. 36th National Symposium, Oct. 25-27, 1989, Boston, MA.
120. "XPS Studies of PEEK-Cu Interfaces," D.G. Castner, R.D. McElhaney and B.D. Ratner, A.V.S. 36th National Symposium, Oct. 25-27, 1989, Boston, MA.
121. "Surface Characterization of a Styrene/p-hydroxystyrene Copolymer Series Using XPS Static SIMS and Derivatization Techniques," A. Chilkoti, D.G. Castner, B.D. Ratner and D. Briggs, American Vacuum Society 36th National Symposium, Oct. 25-27, 1989, Boston, MA.
122. "Surface Analysis of Hydrated Polymer Surfaces," K.B. Lewis, B.D. Ratner and D.G. Castner, American Vacuum Society 36th National Symposium, Oct. 25-27, 1989, Boston, MA.

123. "Plasma-deposited Polymers: Surface Structure and Surface Stability," B.D. Ratner, A. Chilkoti, S.I. Ertel, and T.A. Horbett, A.I.Ch.E. Meeting, Nov. 5-10, 1989, San Francisco, CA.
124. "Effect of Surface Chemistry on Endothelial Cell Growth," S.I. Ertel, A. Chilkoti, T.A. Horbett and B.D. Ratner, A.I.Ch.E. Meeting, Nov. 5-10, 1989, San Francisco, CA.
125. "*In vitro* Enzymatic and Oxidative Degradation of Biomer™ and Pellethane Precipitation and Extraction Fractions," B.J. Tyler and B.D. Ratner, A.I.Ch.E. Meeting, Nov. 5-10, 1989, San Francisco, CA.
126. "Baboon Fibrinogen Adsorption and Platelet Adhesion to Polymeric Materials," J.A. Chinn, T.A. Horbett, and B.D. Ratner, A.I.Ch.E. Meeting, Nov. 5-10, 1989, San Francisco, CA.
127. "Preparation of Non-fouling Biomaterial Surfaces by Plasma Deposition of Poly(ethylene glycol) Oligomers and Precursors," G.P. Lopez, R.J. Rapoza, B.D. Ratner and T.A. Horbett, A.I.Ch.E. Meeting, Nov. 5-10, 1989, San Francisco, CA., 99-100.
128. "Mobility in Polyurethane Surfaces and in Plasma-deposited Surfaces," B.D. Ratner and P.G. Edelman, A.C.S. Meeting, Dec. 18-22, 1989, Honolulu, Hawaii.
129. "Static SIMS Analysis of Plasma Deposited Films Prepared from Carbonyl Precursors," B.D. Ratner and D. Briggs, A.C.S. Symposium on Polymer Surfaces, April 22-27, 1990.
130. "Cryogenic Control of Chemistry in Plasma Deposited Organic Films," G.P. Lopez, B.D. Ratner, A.C.S. Symposium on Polymer Surfaces, April 22-27, 1990.
131. "Residence Time Effects on Surface Bound Fibrinogen as Indicated by Changes in SDS Elutability, Antibody Binding, and Platelet Adhesion," J.A. Chinn, S.E. Posso, T.A. Horbett and B.D. Ratner, Trans. Soc. Biomat. **13**, 242, 1990.
132. "Surface Properties of Unique Polyurethanes," B.D. Ratner, P.G. Edelman, and D.G. Castner, Trans. Soc. Biomat. **13**, 42, 1990.
133. "Surface Characterization of Hydroxyethyl Methacrylate-Styrene Copolymers," D.G. Castner, B.D. Ratner, D. Briggs, T. Okano, D.W. Grainger, and S.W. Kim, Trans. Soc. Biomat. **13**, 43, 1990.
134. "Protein Adsorption Characteristics of Nitrogen/Acetone Radio-Frequency Glow Discharge Modified Polystyrene," R.J. Rapoza, A. Chilkoti, T.A. Horbett, and B.D. Ratner, Trans. Soc. Biomat. **13**, 74, 1990.
135. "A Detailed Infrared Spectral Analysis of Fibrinogen Adsorbed to Polyurethanes," T.J. Lenk, K.K. Chittur, and B.D. Ratner, Trans. Soc. Biomat. **13**, 79, 1990.
136. "Scanning Tunneling Microscopic Study of Fibrinogen Adsorption on Gold Surfaces," K.B. Lewis and B.D. Ratner, Trans. Soc. Biomat. **13**, 94, 1990.
137. "*In Vitro* Degradation of Biomer™: The Effects of Lot-to-Lot Variation on Biostability," B.J. Tyler and B.D. Ratner, Trans. Soc. Biomat. **13**, 133, 1990.
138. "Polyurethanes: Surface properties and blood interactions," B.D. Ratner, T.A. Horbett, S.C. Yoon, J.P. Kennedy, B. Ivan, J.A. Chinn, S.E. Posso, B.J. Tyler and C.L. Haycox, Cardiovascular Science and Technology: Basic and Applied II Meeting, Nov. 30 - Dec. 2, 1990, Louisville, KY.
139. "Fibrinogen Adsorption and Platelet Adhesion to Novel Polyurethanes," J.A. Chinn, S.E. Posso, P.G. Edelman, B.D. Ratner, and T.A. Horbett, ACS 1991 Spring Symposium, April 14-19, 1991, Atlanta, GA.
140. "The Unique Nature of RF Plasma-Deposited Films for Cell Growth," B.D. Ratner, S.I. Ertel, G.P. Lopez, and T.A. Horbett, ACS 1991 Spring Symposium, April 14-19, 1991, Atlanta, GA.
141. "Using XPS and SIMS to Investigate In Vitro Surface Oxidation of Biomer™," B.J. Tyler and B.D. Ratner, Trans. Soc. Biomat. **14**, 179, 1991.

142. "Intrinsic Cytotoxicity of Polymeric Surfaces," B.D. Ratner and S.I. Ertel, Trans. Soc. Biomat. **14**, 235, 1991.
143. "Static SIMS and XPS Analyses of Nonfouling Biomaterial Surfaces Produced by Plasma Deposition of Tetraethylene Glycol Dimethyl Ether," G.P. Lopez, B.D. Ratner and D. Briggs, Trans. Soc. Biomat. **14**, 277, 1991.
144. "Surface Restructuring of Biomedical Polymers," K.B. Lewis, B.D. Ratner, L.A. Klumb, and S.I. Ertel, Trans. Soc. Biomat. **14**, 176, 1991.
145. "Photoenhancement of Platelet Adhesion to Biomaterial Surfaces Observed with Epifluorescent Video Microscopy," C.L. Haycox, B.D. Ratner, and T.A. Horbett, Trans. Soc. Biomat. **14**, 40, 1991.
146. "Structural Elucidation of Oxygen-containing Plasma Films by Static Secondary Ion Mass Spectrometry," A. Chilkoti, B.D. Ratner, and D. Briggs, Trans. Soc. Biomat. **14**, 180, 1991.
147. "Residence Time Effects on Fibrinogen Bound to Six Polyurethanes: Changes in Anti-Fibrinogen Binding and SDS Elutability," J.A. Chinn, S.E. Posso, P.G. Edelman, T.A. Horbett and B.D. Ratner, Trans. Soc. Biomat. **14**, 95, 1991.
148. "Surface Characterization of Fluorocarbon RF Glow Discharge Films Deposited on Poly(methyl methacrylate)," D.G. Castner and B.D. Ratner, Trans. Soc. Biomat. **14**, 279, 1991.
149. "Using SIMS, XPS and Preparative Scale Chromatography to Study Chemical Reactions Involved in Oxidative Degradation of Polyurethanes," B.J. Tyler and B.D. Ratner, 4th International ITV Conference on Biomaterials, Denkendorf, Germany, September 1991.
150. "Developing Multivariate Statistical Models of the Surface Chemistry of Organic Plasma Deposited Films Based on the Static SIMS Spectra of Model Homopolymers," A. Chilkoti, B.D. Ratner, D. Briggs, SIMS VIII, Amsterdam, The Netherlands, September 1991.
151. "Polymeric Biomaterials: The Relationship Between Surface Structure and Biological Performance," D.G. Castner and B.D. Ratner, Surfaces in Biomaterials Meeting, Minneapolis, MN, October 1991.
152. "Static Secondary Ion Mass Spectrometry of Synthetic Peptides," D.S. Mantus, B.D. Ratner and J.F. Moulder, Surfaces in Biomaterials Meeting, Minneapolis, MN, October 1991.
153. "Surface Characterization of Biomaterials," B.D. Ratner, 1991 Annual Meeting of the A.I. Ch.E., Los Angeles, CA, November 1991.
154. "An Investigation of the Relationship Between Surface Chemistry and Endothelial Cell Growth on Oxygen-Containing Plasma-Deposited Films," A. Chilkoti, B.D. Ratner, A. Schmierer, S.I. Ertel and T.A. Horbett, 1991 Annual Meeting of the A.I. Ch.E., Los Angeles, CA, November 1991.
155. "The Influence of Surface and Interfacial Roughness on Angle Resolved XPS Studies," B.J. Tyler, W.D. Hunter, D.G. Castner and B.D. Ratner, 38th Annual AVS Symposium and Topical Conference, November, 1991.
156. "Assessment of X-Ray Damage to Polymers in XPS Instruments," B.D. Ratner, S.J. Caldwell and D.G. Castner, 38th Annual AVS Symposium and Topical Conference, November, 1991.
157. "NEXAFS, XPS, and Static SIMS Characterization of Fluorocarbon Polymer Films," D.G. Castner, K.B. Lewis and B.D. Ratner, 38th Annual AVS Symposium and Topical Conference, November, 1991.
158. "Static Secondary Ion Mass Spectrometry of Poly(amino acids)," D.S. Mantus, B.D. Ratner, 38th Annual AVS Symposium and Topical Conference, November, 1991.
159. "Direct Observation of Time-Dependent Ordering of 6-Mercaptopurine on Au(111)," T. Boland, K.B. Lewis and B.D. Ratner, 38th Annual AVS Symposium and Topical Conference, November, 1991.

160. "Direct Observation of the Interaction of Fibrinogen with Gold Surfaces," K.B. Lewis and B.D. Ratner, 38th Annual AVS Symposium and Topical Conference, November, 1991.
161. "Developing Multivariate Statistical Models of the Surface Chemistry of Organic Plasma Deposited Films Based on the Static SIMS Spectra of Model Homopolymers," A. Chilkoti, B.D. Ratner and D. Briggs, 38th Annual AVS Symposium and Topical Conference, November, 1991.
162. "Modification of Contact Lens Surfaces to Improve Performance," B.D. Ratner, 1991 European Symposium on Contact Lenses, October, 1991.
163. "Surface Analysis of Hydrated Sulfonated Polyurethanes Using Cold-Stage ESCA," S.L. Cooper, K.B. Lewis, B.D. Ratner and J.J. Silver, presented at the 1991 Cardiovascular Science and Technology Meeting, Chicago, IL, December 1991.
164. "Surface Modification of Intraocular Lenses: Strategies and Outcomes," B.D. Ratner, presented at the 15th Japan Ophthalmic Surgery Meeting, Kobe, Japan, January, 1992.
165. "Advances in Our Ability to Characterize Subtle Features of Surfaces Important to Adhesion," B.D. Ratner, presented at the 1992 Adhesion Society Meeting, Hilton Head, SC, February, 1992.
166. "In Vitro Evaluations of Platelet Activation in Whole Human Blood Exposed to Biomer™ and Polyethylene," C.L. Haycox and B.D. Ratner, Trans. Fourth World Biomaterials Congress, 15, 183, 1992.
167. "Characterization of Surface Structure and Orientation in Fluorocarbon Films," D.G. Castner, K.B. Lewis, D.A. Fischer, B.D. Ratner and J.L. Gland, Trans. Fourth World Biomaterials Congress 15, 194, 1992.
168. "Surface Restructuring of Hydrophilic/Hydrophobic Block Copolymers," B.D. Ratner, D.G. Castner, K.B. Lewis, M. Itoh, H. Mori and S. Nakahama, Trans. Fourth World Biomaterials Congress, 15, 38, 1992.
169. "Surface Characterization of Materials for Ophthalmology," B.D. Ratner, Trans. Fourth World Biomaterials Congress, 15, 1992.
170. "Static Secondary Ion Mass Spectrometric Studies of Protein and Lipid Surfaces," D.S. Mantus and B.D. Ratner, Trans. Fourth World Biomaterials Congress, 15, 446, 1992.
171. "Surface Characterization of Biomedical Polymers with Atomic Force Microscopy," K.B. Lewis, B.D. Ratner, T. Boland and A. Chilkoti, Trans. Fourth World Biomaterials Congress, 15, 652, 1992.
172. "The Role of Chemical Heterogeneity in Oxidative Degradation of Polyurethanes," B.J. Tyler and B.D. Ratner, Trans. Fourth World Biomaterials Congress, 15, 677, 1992.
173. "Control of Surface Composition and Structure of Biomaterials," B.D. Ratner, K. B. Lewis, G.R. Llanos, D.G. Castner, T. Boland, D. Kiaei, and A.S. Hoffman, Trans. Fourth World Biomaterials Congress, Workshop #2, 4, 1992.
174. "Dermal sheep collagen in abdominal wall defects: An evaluation with monoclonal antibodies," J.S. van der Laan, J.A. Hunt, J.M. Schadenraad, P.B. van Wachem, M.J.A. van Luyn, R.P. Bleichrodt, B.D. Ratner, P. Nieuwenhuis, and D.F. Williams, Trans. Fourth World Biomaterials Congress, 15, 131, 1992.
175. "Scanning Tunneling Microscopy and Static Secondary Ion Mass Spectrometry Studies of Adsorbed Protein Layers," D.S. Mantus, K.B. Lewis, and B.D. Ratner, American Society for Mass Spectrometry, Washington, D.C., May 31-June 5, 1992.
176. "Mass Spectrometry of Biomaterial Interfaces," D.S. Mantus and B.D. Ratner, presented at American Society for Mass Spectrometry, Washington, D.C., May 31-June 5, 1992.
177. "NEXAFS and XPS Studies of Oriented Fluorocarbon Films," D.G. Castner, B.D. Ratner and K.B. Lewis, presented at 39th National AVS Symposium & Topical Conferences, Chicago, IL, November 9-13, 1992.

178. "Static SIMS Studies on Complex Fluoropolymer Surfaces," B.D. Ratner and D.G. Castner, presented at 39th National AVS Symposium & Topical Conferences, Chicago, IL, November 9-13, 1992.
179. "Investigation of Surface Crosslinking in Polymer Gels of 2-Hydroxyethyl Methacrylate by Static Secondary Ion Mass Spectrometry," A. Chilkoti, G.P. Lopez, M.J. Hearn, D. Briggs, and B.D. Ratner, presented at 39th National AVS Symposium & Topical Conferences, Chicago, IL, November 9-13, 1992.
180. "Cells and Surfaces," B.D. Ratner, S.I. Ertel, A. Chilkoti, and S. Schmeirer, presented at Surfaces in Biomaterials Symposium, Minneapolis, MN, October 14-16, 1992.
181. "NEXAFS and XPS Characterization of Self-Assembled Fluorocarbon Films," D. Castner, K.B. Lewis, G.R. Llanos, B.D. Ratner, presented at Surfaces in Biomaterials Symposium, Minneapolis, MN, October 14-16, pp. 59-62, 1992.
182. "Exploring the Nature of Cell Growth Surfaces," B.D. Ratner, A.E. Schmierer, A. Chilkoti, E. Davison, W. Ciridon, presented at the 1992 Annual Meeting of the American Institute of Chemical Engineers.
183. "Block Copolymers Studied Using Contemporary Surface Analysis Methods," B.D. Ratner, D.G. Castner, K.B. Lewis, K. Iwasaki, and S. Nakahama, 4th SPSJ Int'l Polymer Conference (IPC 92) Yokohama, Japan, Nov. 29-Dec. 3, # 184, 1992.
184. "Exploring the Nature of Cell Growth Surfaces," B.D. Ratner, A.E. Schmierer, A. Chilkoti, E. Davison, and W. Ciridon, AIChE 1992 Annual Meeting, Miami, Florida, 1992.
185. "Fluoropolymer Surfaces: Surface Analysis and Protein Interactions," presented at The 19th Annual Meeting of the Society for Biomaterials, Birmingham, Alabama, April 28-May 2, 1993.
186. "Plasma Deposition of Organic Thin-Films--Control of Film Chemistry," B.D. Ratner, ACS Polymer Preprints, **34**, 643-644, 1993.
187. "Surface Characterization of Amphiphilic Networks," D. Park, V. Galiatsatos, B. Keszler, J.P. Kennedy, and B.D. Ratner, ACS Polym. Prepr. **34(2)**, 62-63, 1993.
188. "Effect of Polyol Type on the Surface Structure of Sulfonate-Containing Polyurethanes," Silver, J.H., K.B. Lewis, B.D. Ratner, and S.L. Cooper, ACS Polym. Prepr. **34(2)**, 56-57, 1993.
189. "Surface Characterization of Polymeric Biomaterials: A Brief Tutorial," B.D. Ratner, ACS Polym. Prepr. **34(2)**, 50-51, 1993.
190. "Static Secondary Ion Mass Spectrometric Study of Glow-Discharge-Immobilized PEO Surfactant Surfaces," M.-S. Sheu, A.S. Hoffman, B.D. Ratner, J. Feijen, ACS Polymer Preprints, **34**, 663-664, 1993.
191. "Correlating Biological Interactions with Surface Properties," V.H. Perez-Luna and B.D. Ratner, 19th Annual Meeting of the Society for Biomaterials, Birmingham, AL, 281, April 28-May 2, 1993.
192. "Reply to Drs. Bruck and Schroeder," B.D. Ratner, Letter to the Editor, J. Biomed. Mater. Res. **28**, 135-136, 1994.
193. "Endothelial Cell Activation on Biomaterials," A.E. Schmierer and B.D. Ratner, 23rd Annual Keystone Symposia Tissue Engineering, Taos, NM, Feb 20-26, 1994, Journal of Cellular Biochemistry Abstract Supplement 18C, 1994.
194. "Multi-Step Assembly of Polymeric Monolayers," D.W. Grainger, G. Mao, F. Sun, and D.G. Castner, 41st National Symposium of the American Vacuum Society and NANO 3: Third International Conference on Nanometer-Scale Science and Technology, Denver, CO, October 10-24, 1994.
195. "Extraction of Quantitative Surface Information from Static SIMS using Partial Least Squares," B.D. Ratner, V.H. Perez-Lunz, and P. Favia, 41st National Symposium of the American Vacuum Society and NANO 3:

- Third International Conference on Nanometer-Scale Science and Technology, Denver, CO, October 10-24, 1994.
196. "ToF SIMS Imaging of Self-Assembled Monolayers," D.B. Castner, P.J. McKeown, and D.W. Grainger, 41st National Symposium of the American Vacuum Society and NANO 3: Third International Conference on Nanometer-Scale Science and Technology, Denver, CO, October 10-24, 1994.
197. "SIMS Characterization of Adsorbed Protein Films," B. Hagenhoff, A. Benninghoven, D.G. Castner, and B.D. Ratner, 41st National Symposium of the American Vacuum Society and NANO 3: Third International Conference on Nanometer-Scale Science and Technology, Denver, CO, October 10-24, 1994.
198. "Surface Studies of Filled Silicone Elastomers," B.D. Ratner, D. Leach-Scampavia, W. Ciridon, C.D. Tidwell, T. Boland, and P. Yang, 41st National Symposium of the American Vacuum Society and NANO 3: Third International Conference on Nanometer-Scale Science and Technology, Denver, CO, October 10-24, 1994.
199. "Molecular Recognition between DNA Base Pairs by AFM," B.D. Ratner, and T. Boland, 41st National Symposium of the American Vacuum Society and NANO 3: Third International Conference on Nanometer-Scale Science and Technology, Denver, CO, October 10-24, 1994.
200. "Aminoacid Adsorption on Polyfunctional SAM's of Alkylthiols," K. Uvdal, S.V. Atre, D. Allara, and B.D. Ratner, 41st National Symposium of the American Vacuum Society and NANO 3: Third International Conference on Nanometer-Scale Science and Technology, Denver, CO, October 10-24, 1994.
201. "The Effect of Oligo(ethyleneoxide) Chainlength on the Protein Resistance of Plasma Deposited Thin Films." B.D. Ratner, and E.E. Johnson, 41st National Symposium of the American Vacuum Society and NANO 3: Third International Conference on Nanometer-Scale Science and Technology, Denver, CO, October 10-24, 1994.
202. "Effect of Surface Mobility on Biointeractions," B.D. Ratner, and C.D. Tidwell, 41st National Symposium of the American Vacuum Society and NANO 3: Third International Conference on Nanometer-Scale Science and Technology, Denver, CO, October 10-24, 1994.
203. "Biomaterial interfaces: Why biology?," B.D. Ratner, AVS Newsletter, July-August, 1994.
204. "Book Review: Polymeric Biomaterials," B.D. Ratner, to Biomaterials Form 16, (4), 1994.
205. "TOF-SIMS Studies of Adsorbed Protein Films on Metal and Fluoropolymer Surfaces," B.D. Ratner, D.G. Castner, C.D. Tidwell, K. Meyer, B. Hagenhoff, and A. Benninghoven, 21st Annual Meeting of the Society for Biomaterials, San Francisco, CA, March 18-March 22, 1995.
206. "Surface Properties of Tyrosine Derived Polymers and Their Effect on Cell-Polymer Interactions," V.H. Perez-Luna, B.D. Ratner, and J. Kohn, 21st Annual Meeting of the Society for Biomaterials, San Francisco, CA, March 18-March 22, 1995.
207. "Correlations Between Chemical Composition and Fibrinogen Adsorption Properties of Plasma-Deposited Fluoropolymers," P. Favia, V.H. Perez-Luna, and B.D. Ratner, 21st Annual Meeting of the Society for Biomaterials, San Francisco, CA, March 18-March 22, 1995.
208. "Molecular Recognition Using AFM Between Biotin and Streptavidin Mutants," T. Boland, A. Chikoti, P.S. Stayton, and B.D. Ratner, 21st Annual Meeting of the Society for Biomaterials, San Francisco, CA, March 18-March 22, 1995.
209. "Novel Organic-Metal Interfaces: Structures and Chemistries," B.D. Ratner, T. Boland, E. Johnston, and C. Tidwell, Material Research Society Meeting, San Francisco, CA, April 17-21, 1995.
210. "Surface Analysis and Controlled Release Systems," B.D. Ratner, 22nd International Symposium on Controlled Release of Bioactive Materials, Seattle, WA, July 30 - August 2, 1995.

211. "Platelet and Protein Interactions with Solid Surfaces," T.A. Horbett, K. Hauch, J. Grunkemeir, W. Changxiu, V. Perez-Luna, B. Ratner, and J. Chinn, Colloid and Surface Chemistry, 1995.
212. "A Novel Matrix for the Controlled Release of the Anti-Thrombotic Peptide, Echistatin," M.M. Takeno, T.A. Horbett, B.D. Ratner, to Proceed. Inter. Symp. Control. Rel. Bioact. Mater., Controlled Release Society, Inc., 1995.
213. "Order and Disorder in Polymeric and Organic Surfaces: Influence on Cell and Protein Interaction," B.D. Ratner, C.D. Tidwell, B. Tarasevich, D.L. Allara, to 1995 International Chemical Congress of Pacific Basin Societies, Honolulu, HI, December 17-22, 1995.
214. "Surface Studies of Protein Resistant Films Prepared by RF-Plasma Deposition by E. Johnston, B.D. Ratner, 42nd National Symposium American Vacuum Society, Minneapolis, MN, October 16-20, 1995.
215. "Substrates for Patterned Protein Adsorption: A Combination of Plasma Film Lithography and Self-Assembly " by T. Boland, E.E. Johnston, S. Domino, B.D. Ratner, 42nd National Symposium American Vacuum Society, Minneapolis, MN, October 16-20, 1995.
216. "Endothelial Cell Growth and Serum Protein Adsorption: Effect of Surface Chemistry as Assessed with Self-Assembled Monolayers," C.D. Tidwell, B.D. Ratner, B. Tarasevich, S. Atre, D.L. Allara, Fifth World Biomaterials Congress, Toronto Canada, May 29-June 2, 1996.
217. "Adsorbed Protein Configuration and Orientation Probed by ESCA and Time-Of-Flight SIMS," B.D. Ratner, C.D. Tidwell, K. Meyer, D.G. Castner, S. Golledge, B. Hagenhoff, A. Benninghoven, Fifth World Biomaterials Congress, Toronto Canada, May 29-June 2, 1996.
218. "Substratum Control of Antibiotic Release from Biomaterials," C. Kwok, T.A. Horbett, C. Wan, L. Shen, B.D. Ratner, Fifth World Biomaterials Congress, Toronto Canada, May 29-June 2, 1996.
219. "Residence Time Effects on Fibrinogen Bound to Six Polyurethanes: Changes in Anti-Fibrinogen Binding and SDS Elutability," J.A. Chinn, S.E. Posso, P.G. Edelman, T.A. Horbett and B.D. Ratner, Trans. Soc. Biomat. 14, 95, 1991.
220. "Surface Rearrangement of Hydrophilic/Hydrophobic Block Copolymers Containing Poly(2,3-Dihydroxypropyl Methacrylate)," D.G. Castner, B.D. Ratner, K. Senshu, A. Hirao, S. Nakahama, Fifth World Biomaterials Congress, Toronto Canada, May 29-June 2, 1996.
221. "Plasma-Deposited Glyme and Crown Ether Films Resist the Attachment of *Pseudomonas Aeruginosa*," EE. Johnston, J. Bryers, B.D. Ratner, Fifth World Biomaterials Congress, Toronto Canada, May 29-June 2, 1996.
222. "Surface Analysis of Modified Polyurethane," T. Otoy, D. Leach-Scampavia, B.D. Ratner, Fifth World Biomaterials Congress, Toronto Canada, May 29-June 2, 1996.
223. "Endothelial Cell Activation on Biomaterials: Expression of the Inflammatory Marker E-Selectin," A.E. Schmierer, T.H. Polman, B.D. Ratner, Fifth World Biomaterials Congress, Toronto Canada, May 29-June 2, 1996.
224. "Surface Characterization of Polystyrene Cell Culture Substrates," A.M. Belu, D. Leach-Scampavia, B.D. Ratner, Fifth World Biomaterials Congress, Toronto Canada, May 29-June 2, 1996.
225. "Medical Devices: Court Decision Likely to be Crushing Blow for Consumers," B.D. Ratner, The Seattle Times OPINION, July 2, 1996.
226. "The Balanced Textbook We Need," B.D. Ratner, Biomaterials Forum Open Forum, 19 (2), March-April 1997.
227. "The Effect of Fluorocarbon Surface Structure on Endothelial Cell Growth," D.G. Castner, C.D. Tidwell, B.D. Ratner, M.-W. Tsao, J.F. Rabolt, 23rd Annual Meeting of the Society for Biomaterials, New Orleans, LA, April 30-May 4, 1997.
228. "Self-Assembled Monolayer Formation and Surface Derivation of 16-Mercapto-1-Hexanol on Gold," S. Pan, A. Belu, B.D. Ratner, 23rd Annual Meeting of the Society for Biomaterials, New Orleans, LA, April 30-May 4, 1997.

229. "Synthesis of Functionalized Polyetherurethanes and Polyetherurethaneureas with Linear and Branched Chains and their use in the Modification of Surface Properties," F.I. Simonovsky, S.C. Porter, B.D. Ratner, 23rd Annual Meeting of the Society for Biomaterials, New Orleans, LA, April 30-May 4, 1997.
230. "Investigation of Cation/Polyether Complexes with Static ToF-SIMS," S.C. Porter, B.D. Ratner, 23rd Annual Meeting of the Society for Biomaterials, New Orleans, LA, April 30-May 4, 1997.
231. "Radio Frequency Glow Discharge (RFGD) Imprinting of E. coli and Nanogold Colloids," H. Shi, M. Garison, B.D. Ratner, ACS Polymeric Materials Science & Engineering Preprints, Vol. 77 (2), 396-397, 1997.
232. "RF Plasma Deposited PEO-Like Surfaces that Inhibit Pseudomonas Aeruginosa Accumulation," E.E. Johnston, B.D. Ratner, and J.D. Bryers, ACS Polymeric Materials Science and Engineering Preprints, Vol. 77 (2), 1997.
233. "Endothelial Cell Growth of Binary Composition Self-Assembled Monolayers: Effect of Surface Chemistry and the Adsorbed Protein Layer," C.D. Tidwell, A.M. Belu, B.D. Ratner, B. Tarasevich, S. Atre, D.L. Allara, 23rd Annual Meeting of the Society for Biomaterials, New Orleans, LA, April 30-May 4, 1997.
234. "Quantitative Detection of Silicone in Skin Using Electron Spectroscopy for Chemical Analysis (ESCA)," C.L. Haycox, D. Leach-Scampavia, J.E. Olerud, B.D. Ratner, to The Society for Investigative Dermatology, 1997.
235. "Controlling the Biological Response by Surface Modification," B.D. Ratner, abstract submitted to International Society for Applied Cardiovascular Biology Sixth Biennial Meeting, Wildbad Kreuth, Germany, March, 1998.
236. "Endothelial Cell Growth and Surface Characterization of RF Glow Discharge Deposited Fluorocarbon Surfaces," D.G. Castner, S. Sarm, C.D. Tidwell, B.D. Ratner, 24rd Annual Meeting of the Society for Biomaterials, 21, 524, San Diego, CA, April 22-26, 1998.
237. "Surface Analysis of Medical Grade Silicon Elastomer After Exposure to Hot Saline," N.A. Shah, B.D. Ratner, 24rd Annual Meeting of the Society for Biomaterials, 21, 130, San Diego, CA, April 22-26, 1998.
238. "Template Imprinting of Cells Proteins and Nanogold Particles," B.D. Ratner, H. Shi, 24rd Annual Meeting of the Society for Biomaterials, 21, 107, San Diego, CA, April 22-26, 1998.
239. "Characterization of Apatite and Related Calcium Phosphate Surfaces by XPS," H. Lu, C.T. Campbell, B.D. Ratner, 24rd Annual Meeting of the Society for Biomaterials, 21, 35, San Diego, CA, April 22-26, 1998.
240. "Control Release of Biomolecules that Interfere with Bacterial Adhesion," J.D. Bryers, R. Bargatze, T.A. Horbett, B.D. Ratner, 24rd Annual Meeting of the Society for Biomaterials, 21, 19, San Diego, CA, April 22-26, 1998.
241. "Porphyrin Monolayers on Gold," A.L. Bramblett, M.S. Boeckh, T.K. Sasaki, B.D. Ratner, J.W. Rogers, Jr., 24rd Annual Meeting of the Society for Biomaterials, 21, 71, San Diego, CA, April 22-26, 1998.
242. "Template Imprinted Materials for Protein Recognition," H. Shi, W.B. Tsai, B.D. Ratner, 24rd Annual Meeting of the Society for Biomaterials, 21, 250, San Diego, CA, April 22-26, 1998.
243. "Stability of oxygen Gas Plasma-Treated Silicone Rubber," K.J. Leach, D. Leach-Scampavia, B.D. Ratner, A.S. Hoffman, 24rd Annual Meeting of the Society for Biomaterials, 21, 132, San Diego, CA, April 22-26, 1998.
244. "Plasma Deposited Poly(BMA) Membranes for Controlled Release of Ciprofloxacin from Poly(urethane): Bacterial Accumulation as a Function of Materials Preparation," J.D. Bryers, S. Hendricks, C. Kwok, T.A. Horbett, B.D. Ratner, 24rd Annual Meeting of the Society for Biomaterials, 21, 347, San Diego, CA, April 22-26, 1998.
245. "Template Imprinted Nanostructural Surface for Biorecognition," H. Shi, B.D. Ratner, 20<sup>th</sup> Annual Symposium on Applied Surface Analysis, Richland, WA, June 16-19, 1998.

246. "Water-Absorbing Polyurethane/Poly(ethylene glycol) Blends: Distinctive Microstructure and Hydrophilicity," F.I. Simonovsky, B.D. Ratner, Proceedings of the American Chemical Society Division of Polymeric Materials: Science and Engineering, 79, 436-437, Boston, MA, August 23-27, 1998.
247. "Surface Chemistry and Elastic Properties of Plasma Deposited Fluoropolymers," R. Luginbuehl, M.D. Garrison, R.M. Overney, B.D. Ratner, L. Weiss, S. Hild, ACS Polymer Preprints, 39, 2, 932-933, Boston, MA, 1998.
248. "Modification of Polymer Surfaces with Self-assembled Monolayers," C.S. Kwok and B.D. Ratner, 25<sup>th</sup> Annual Meeting of the Society for Biomaterials, 22, 73, Providence RI, April 28-May 2, 1999.
249. An Irreverent Guide to Biomaterials as Materials: Auto Parts to RoboCop, B. D. Ratner, American Institute of Chemical Engineers – Materials Engineering and Sciences Division Newsletter, Vol. 30, 2, October 1999.
250. Perspective on Biomaterials, B. D. Ratner and L. Hench, eds., Biomaterials Division Current Opinion in Solid State & Materials Science, Vol. 4, 4, August 1999.
251. "Immobilization of Amino Acids and Peptide on Self-assembled Monolayers as Mimetic Integrin-binding Domains for Cell Adhesive Surfaces," S. Pan, D.G. Castner, B.D. Ratner, 25<sup>th</sup> Annual Meeting of the Society for Biomaterials, 22, 78, Providence RI, April 28-May 2, 1999.
252. "Issues in Blood Interaction at the End of the 20<sup>th</sup> Century," B. D. Ratner, 15<sup>th</sup> European Conference on Biomaterials, ESB '99, Bordeaux, France, September 10, 1999.
253. "Tissue Engineering Research in the United States," B. D. Ratner, WTEC Workshop, 95, 2000.
254. "A Surface Path to 21<sup>st</sup> Century Biocompatibility", B. D. Ratner, Surface in Biomaterials Symposium 2000, 3-8, Scottsdale, Arizona, August 31, 2000.
255. "Protein Adsorption on Mixtures of Hydroxyl- and Methyl-Terminated Alkanethiols Self-Assembled Monolayers," C.L. Martins, B.D. Ratner, and M.A. Barbosa, 17<sup>th</sup> European Conference on Biomaterials, 231, Barcelona, Spain, September 11-14, 2002.
256. "Synthesis of Polyurethanes Incorporating Long Alkyl Side-Chains With Pendant Carboxyl Group," F.I. Simonovsky, Y. Wu, T.A. Horbett, B.D. Ratner, 225<sup>th</sup> ACS National Meeting- Polymeric Materials: Science and Engineering Preprints, 88, 104-106, New Orleans, LA, March 23-27, 2003.
257. "Development and Characterization of Poly(vinyl Alcohol)-amino Acid Hydrogels for Use as Biomaterials," M.S. Boeckl, J. Perry, E.R. Leber, P. Nair and B.D. Ratner, 225<sup>th</sup> ACS National Meeting - Division of Polymer Chemistry Polymer Preprints, Vol. 44, 677-678, New Orleans, LA, March 23-27, 2003.
258. "Improving the Blood Compatibility of Polyethylene Tubing by Plasma Polymerization of Tetraglyme," K.J. Kitching, L. Cao, B.D. Ratner, T.A. Horbett, 225<sup>th</sup> ACS National Meeting- Division of Polymer Chemistry Polymer Preprints, Vol. 44, 1, 175-176, New Orleans, LA, March 23-27, 2003.
259. "Poly(Vinyl Alcohol)/Amino Acid Non-Covalent Hydrogels for Biomedical Applications," B.D. Ratner, E.R. Leber, C.A. Irvin, E.E. Donaldson, M.S. Boeckl, J. Perru, P. Nair, J. Bonadio, M. Zhang, K.D. Hauch, 225<sup>th</sup> ACS National Meeting- Division of Polymer Chemistry Polymer Preprints, Vol. 44, 1, 626-627, New Orleans, LA, March 23-27, 2003.
260. "Synthesis of a Thrombin Responsive Drug Delivery Coating for Cardiovascular Stents," K.S. Walline, K. VanBuren and B.D. Ratner, 225<sup>th</sup> ACS National Meeting- Division of Polymer Chemistry Polymer Preprints, Vol. 44, 193-194, New Orleans, LA, March 23-27, 2003.
261. "Temperature-Responsive Polymeric Surface Modifications by Plasma Polymerization: Cell and Protein Interactions," B.D. Ratner, X. Cheng, Y. Wang, Y. Hanein, K.F. Böhringer, 225<sup>th</sup> ACS National Meeting- Division of Polymer Chemistry Polymer Preprints, Vol. 44, 1, 198-199, New Orleans, LA, March 23-27, 2003.

262. "Surface Modification of Polymeric Biomaterials: A Brief Tutorial and Overview," B.D. Ratner, 225<sup>th</sup> ACS National Meeting- Division of Polymer Chemistry Polymer Preprints, Vol. 44, 1, 160, New Orleans, LA, March 23-27, 2003.
263. "Investigation of Immobilized Type-1 Collagen as an Affinity Coating to Bind Osteopontin to Poly(2-Hydroxyethyl Methacrylate)," S.M. Martin, J.L. Schwartz, C.M. Giachelli, B.D. Ratner, 225<sup>th</sup> ACS National Meeting- Division of Polymer Chemistry Polymer Preprints, Vol. 44, 1, 177-178, New Orleans, LA, March 23-27, 2003.
264. "To Tissue Engineer Heart Muscle," B.D. Ratner, M. Allan, J. Angello, P. Bornstein, K.D. Hauch, S.D. Hauschka, A.S. Hoffman, C. Murry, J. Sanders, P. Stayton, R. Vernon, K. Woodhouse, International Society for Artificial Organs (ISAO) and the American Society for Artificial Internal Organs (ASAIO), Washington D.C., USA, June, 18 - 21, 2003.
265. "Launching TESNA: The Tissue Engineering Society of North America," R.M. Nerem, B.D. Ratner, Tissue Engineering Vol. 9, 5, 869-870, Larchmont, NY, October 2003.
266. "Adaptive Surface Films for Biocompatibility," B.D. Ratner, S.M. Martin, C.M. Giachelli, A.J. Marshall, P. Bornstein and Themis Kyriakides, ACS Polym. Mater. Sci. Eng., 90, 680-681, 2004.
267. "Novel Tissue Scaffold Materials Based on Poly(vinyl alcohol) and Amino Acid Hydrogels," E.E. Donaldson, J.L. Cuy, K.D. Hauch, A. Karchin, B.D. Ratner, Transactions 7th World Biomaterials Congress, 102, Sydney, Australia, May 17-21, 2004.
268. "Progress Toward Engineered Biomaterials That Heal," B. Ratner, T. Horbett, M. Shen, C. Giachelli, S. Martin, A. Marshall, P. Bornstein, T. Kyriakides, H. Sage, P. Puolakkainen, C. Irvin, J. Sanders, Transactions 7th World Biomaterials Congress, 118, Sydney, Australia, May 17-21, 2004.
269. "Poly(vinyl alcohol)-Amino Acid Hydrogels: Potential for Use as an Implantable Electrode Coating," E.R. Leber, M.S. Boeckl, B.D. Ratner, Transactions 7th World Biomaterials Congress, 153, Sydney, Australia, May 17-21, 2004.
270. "Tailoring the Architecture of Photopolymerized Porous pHEMA Scaffolds for Cardiac Tissue Engineering," S.J. Bryant, A.J. Marshall, K.D. Hauch, B.D. Ratner, Transactions 7th World Biomaterials Congress, 182, Sydney, Australia, May 17-21, 2004.
271. "Total Plasma Protein Repellency of Glow Discharge Deposited Tetraglyme Measured with Surface Plasmon Resonance: Ultralow Protein Adsorption Surfaces for Improved Hemocompatibility," L. Cao, C.Y. Lee, D.G. Castner, B.D. Ratner, T.A. Horbett, Transactions 7th World Biomaterials Congress, 233, Sydney, Australia, May 17-21, 2004.
272. "SPARC Binding with ECM Proteins and Its Influence on Cell Adhesion," H. Wang, S. Chen, T. Barker, H. Sage, B. Ratner, S. Jiang, Transactions 7th World Biomaterials Congress, 287, Sydney, Australia, May 17-21, 2004.
273. "The Effect of Polyurethane Surface Chemistry on Fibrinogen Adsorption, Monoclonal Antibody Binding, and Platelet Adhesion," Y. Wu, F.I. Simonovsky, K.C. Brownlow, B.D. Ratner, T.A. Horbett, Transactions 7th World Biomaterials Congress, 300, Sydney, Australia, May 17-21, 2004.
274. "Past Surface Characterization and Future Surface Characterization for Biomaterials," B.D. Ratner, Transactions 7th World Biomaterials Congress, 365, Sydney, Australia, May 17-21, 2004.
275. "Surface Characterization of Extracellular Matrix upon Cell Detachment from a 'Smart Polymer,'" H.E. Canavan, X. Cheng, B.D. Ratner, D.G. Castner, Transactions 7th World Biomaterials Congress, 432, Sydney, Australia, May 17-21, 2004.
276. "Pore Size Controls Angiogenesis in Subcutaneously Implanted Porous Matrices," A.J. Marshall, T. Barker, E.H. Sage, K.D. Hauch, B.D. Ratner, Transactions 7th World Biomaterials Congress, 710, Sydney, Australia, May 17-21, 2004.

277. "Control of Osteopontin Orientation/Conformation on Surfaces for Cell Adhesion," L. Liu, S. Chen, B. Ratner, S. Jiang, Transactions 7th World Biomaterials Congress, 761, Sydney, Australia, May 17-21, 2004.
278. "Proteins on Plasma Deposited Thermo-Responsive Polymer: Adsorption and Activity Study," X. Cheng, B.D. Ratner, Transactions 7th World Biomaterials Congress, 1420, Sydney, Australia, May 17-21, 2004.
279. "An Introduction to Surface Analysis by XPS and AES," Book Review, B.D. Ratner, Journal of Controlled Release, Vol. 105, Issues 1-2, 178-179, 2005.
280. "Cross-Linking of an Esophagus Acellular Matrix Tissue-Scaffold," A. Bhrany, N. Futran, C. Lien, N. Muni, C. Irvin, B. Ratner, C. Giachelli, Otolaryngology - Head and Neck Surgery, Vol. 133, Issue 2, P109, 2005.

## **Submitted Works**

“Recognition Biosurfaces via Self-assembly and Amino Acid Immobilization: Preparation, Characterization, and *in vitro* Biological Assessment,” S. Pan, D.G. Castner and B.D. Ratner, J. Biomed. Mater. Res. 2000, Accepted pending revision.

“Fibronectin Adsorption of Radiofrequency Plasma-Deposited Films: Scatchard Analysis and Cell Growth Characteristics,” A.E. Schmierer, B.D. Ratner, M. Jozefowicz, J. Biomed. Mater. Res., 2000, Accepted pending minor revisions.

“Macrophage Secretion of IL-1 $\beta$ , TNF $\alpha$ , and IL-8 in Response to Material Micro-architecture,” A.E. Schmierer and B.D. Ratner, submitted to J. Biomed. Mater. Res., 2001.

“Multivariate Analysis of TOF-SIMS Spectra from Self-Assembled Monolayers: Thiol Chain Length and Fragmentation Pattern,” D.J. Graham and B.D. Ratner, submitted to Langmuir, 2003.

“Fabrication of highly porous biodegradable tubular scaffolds for tissue engineering,” S. Pan and B.D. Ratner, submitted to J. Biomat. Sci. Polym. Ed., 2005.

“Promoting Angiogenesis and Outwitting the Foreign Body Response: Pore Size Matters,” A.J. Marshall, C.A. Irvin, K.D. Hauch, B.D. Ratner, submitted to Science, 2005.

“A Systems Approach to the Tissue Engineering of Heart Muscle,” B.D. Ratner and C.E. Murry, submitted to Trends in Biotechnology, 2006.

“Effect of Extracellular Matrix Proteins on Adhesion Contact Dynamics of Esophageal Epithelia on Chitosan Surface,” Z. Feng, K. S. Chian, P. S. Mhaisalka1, V. Chan, B. D. Ratner, submitted to Biomaterials, 2006.

“Adhesion of MC3T3-E1 Cells to Bone Sialoprotein and Bone Osteopontin Specifically Bound to Collagen,” M. Bernards, C. Qin, B.D. Ratner, S. Jiang, submitted to J. Biomed. Mater. Res. A, 2007.

“Molecularly designed surfaces for blood deheparinization using an immobilized heparin-binding peptide,” M.C.L. Martins, S. Curtin, B.D. Ratner, submitted to J. Biomed. Mater. Res. A, 2007.

“Differentiating Calcium Carbonate Polymorphs by Surface Analysis Techniques; An XPS and TOF-SIMS Study,” M. Ni, B.D. Ratner, submitted to Surface and Interface Analysis, 2007.

“Selective Protein Adsorption Modulates Platelet Adhesion and Activation to Eligo (ethylene glycol)-terminated Self-assembled Monolayers with C18 Ligands,” I.C. Goncalves, M.C.L. Martins, M.A. Barbosa, B.D. Ratner, E. Naeemi, submitted to J. Biomed. Mater. Res. A, 2008.

## **Patents**

"Process for Radiation Grafting Hydrogels onto Organic Polymeric Substrates," B.D. Ratner (Seattle, WA), A.S. Hoffman (Seattle, WA), filed April 10, 1974, Appl. No. 05/459,734, Assignee The United States of America as represented by the United States Energy (Washington, DC), allowed February 17, 1976, U.S. Patent #3,939,049.

"Process for Radiation Grafting Hydrogels onto Organic Polymeric Substrates," B.D. Ratner (Seattle, WA), A.S. Hoffman (Seattle, WA), U.S. Dept. of Energy, submitted April 25, 1978, Canadian Patent No. 1,030,100/A/.

"Plasma Gas Discharge Treatment for Improving the Biocompatibility of Biomaterials," A.S. Hoffman (King County, WA), A. Garfinkle (King County, WA), B.D. Ratner (King County, WA), S.R. Hanson (San Diego County, CA), filed March 11, 1985, Appl. No. 06/709,990, Assignee Washington Research Foundation (Seattle, WA), allowed April 7, 1987, U.S. Patent #4,656,083.

"Radio Frequency Plasma Deposited Polymers That Enhance Cell Growth," T.A. Horbett (Seattle, WA), B.D. Ratner (Seattle, WA), J.A. Chinn (Seattle, WA), Y. Haque (Pasadena, CA), filed December 21, 1987, Appl. No. 07/136,457, Assignee The Board of Regents for the University of Washington (Seattle, WA), allowed April 24, 1990, U.S. Patent #4,919,659.

"Method of Controlling the Chemical Structure of Polymeric Films by Plasma," B.D. Ratner (Seattle, WA), G.P. Lopez, filed August 31, 1989, Appl. No. 07/402,181, Assignee The Board of Regents of the University of Washington (Seattle, WA), allowed March 26, 1991, U.S. Patent #5,002,794.

"Plasma Gas Discharge Treatment for Improving the Compatibility of Biomaterials," A.S. Hoffman (Seattle, WA), A. Garfinkle (Montreal, CA), B.D. Ratner (Seattle, WA), S.R. Hanson (Encinitas, CA), filed August 21, 1989, Appl. No. 07/398,312, Assignee Washington Research Foundation (Seattle, WA), allowed July 23, 1991, U.S. Patent #5,034,265.

"Polymeric Intraocular Lens Material Having Improved Surface Properties," B.D. Ratner (Seattle, WA), N.B. Mateo (Seattle, WA), filed October 21, 1987, Appl. No. 07/111,132, Assignee Washington Research Foundation, allowed February 25, 1992, U. S. Patent #5,091,204.

"Methods of Controlling the Chemical Structure of Polymeric Films by Plasma Deposition and Films Produced Thereby," B.D. Ratner (Seattle, WA), G. Lopez (Seattle, WA), filed March 25, 1991, Appl. No. 07/675,531, Assignee The Board of Regents of the University of Washington (Seattle, WA), allowed October 6, 1992, U.S. Patent #5,153,072.

"Surface-Modified Self-Passivating Intraocular Lenses," B.D. Ratner (Seattle, WA), C.L. Tidwell (Arnhem, NL), filed March 25, 1991, Appl. No. 07/675,600, Assignee The Board of Regents of the University of Washington (Seattle, WA), allowed December 15, 1992, U.S. Patent #5,171,267.

"Multiple-Probe Diagnostic Sensor," B.D. Ratner (Seattle, WA), J.E. Francese (Seattle, WA), filed April 15, 1992, Appl. No. 07/869,899, Assignee The Board of Regents of the University of Washington (Seattle, WA), allowed November 2, 1999, U.S. Patent #5,976,466.

"Template Imprinted Materials by RFGD Plasma Deposition," B.D. Ratner (Seattle, WA), H. Shi (Seattle, WA), filed April 15, 1999, Appl. No. 09/293,460, Assignee University of Washington (Seattle, WA), allowed October 17, 2000, U.S. Patent #6,131,580.

"Polymeric Intraocular Lens Material Having Improved Surface Properties and Intraocular Lens Construction," B.D. Ratner (Seattle, WA), N.B. Mateo (Seattle, WA), filed April 23, 1987, Appl. No. 07/041/796, Assignee Washington Research Foundation (Seattle, WA), allowed November 7, 2000, U. S. Patent #6,143,027.

"Drug delivery devices, and methods of use," C. S-K Kwok (Seattle, WA), B.D. Ratner (Seattle, WA), P.D. Mourad (Seattle, WA), L.A. Crum (Seattle, WA), filed April 25, 2001, Appl. No. 09/844,659, Assignee University of Washington (Seattle, WA), allowed September 3, 2002, U.S. Patent #6,444,217.

“Hydrogels formed by non-covalent linkages,” B.D. Ratner (Seattle, WA), P.D. Nair (Kerala, IN), M.S. Boeckl (Seattle, WA), E.R. Leber (Seattle, WA), filed January 9, 2003, Appl. No. 10/339,777, Assignee University of Washington (Seattle, WA), allowed September 27, 2005, U.S. Patent #6,949,590.

“Porous Structures Useful for Growing Living Tissue, and Methods of Manufacture,” P.D. Nair (Trivandrum, IN), B.D. Ratner (Seattle, WA), V. Vogel (Seattle, WA), R.M. Nerem (Atlanta, GA), filed December 5, 2002, Appl. No. 10/314,453, Assignee University of Washington (Seattle, WA), issued September 12, 2006, U.S. Patent #7,105,580.

“Method for hydrogen storage and delivery,” B.D. Ratner (Seattle, WA), E. Naeemi (Lynnwood, WA), filed November 23, 2004, Appl. No. 10/997,368, Assignee Asemblon, Inc. (Seattle, WA), issued March 6, 2007, U.S. Patent #7,186,396.

“Methods for photopatterning hydrogels,” S.J. Bryant (Shoreline, WA), K.D. Hauch (Lynnwood, WA), B.D. Ratner (Seattle, WA), filed February 24, 2005, Appl. No. 11/067,480, Assignee University of Washington (Seattle, WA), issued March 20, 2007, U.S. Patent #7,192,693.

“Hydrogels formed by non-covalent linkages,” B.D. Ratner (Seattle, WA), P.D. Nair (Kerala, IN), M.S. Boeckl (Seattle, WA), E.R. Leber (Seattle, WA), filed August 9, 2005, Appl. No. 11/199,613, Assignee University of Washington (Seattle, WA), a division of application No. 10/339,777 now Pat. No. 6,949,590, allowed November 27, 2007, U.S. Patent #7,300,962.

**Listed in**

Who's Who in America

Who's Who in Science and Technology

Who's Who in American Education

Who's Who in the West

American Men and Women of Science

2000 Outstanding Scientists of the 21st Century

Who's Who in Medicine and Healthcare

# Surface Chemical and Mechanical Properties of Plasma-Polymerized *N*-Isopropylacrylamide

Xuanhong Cheng,<sup>†,§</sup> Heather E. Canavan,<sup>‡,§</sup> M. Jeanette Stein,<sup>†,§</sup>  
James R. Hull,<sup>‡,§</sup> Sasha J. Kveskin,<sup>||</sup> Matthew S. Wagner,<sup>‡</sup> Gabor A. Somorjai,<sup>||</sup>  
David G. Castner,<sup>†,‡,§,£</sup> and Buddy D. Ratner<sup>\*,†,‡,§,£</sup>

University of Washington Engineered Biomaterials, National ESCA and Surface Analysis Center for Biomedical Problems, Departments of Bioengineering, and Chemical Engineering, University of Washington, Seattle, Washington, and Department of Chemistry, University of California at Berkeley and Material Science Division, Lawrence Berkeley National Laboratory, Berkeley, California 94720

Received February 16, 2005. In Final Form: May 3, 2005

Surface-immobilized poly(*N*-isopropyl acrylamide) (pNIPAM) is currently used for a wide variety of biosensor and biomaterial applications. A thorough characterization of the surface properties of pNIPAM thin films will benefit those applications. In this work, we present analysis of a plasma-polymerized NIPAM (ppNIPAM) coating by multiple surface analytical techniques, including time-of-flight secondary-ion mass spectrometry (ToF-SIMS), contact angle measurement, atomic force microscopy (AFM), and sum frequency generation (SFG) vibrational spectroscopy. ToF-SIMS data show that the plasma-deposited NIPAM polymer on the substrate is cross-linked with a good retention of the monomer integrity. Contact angle results confirm the thermoresponsive nature of the film as observed by a change of surface wettability as a function of temperature. Topographic and force–distance curve measurements by AFM further demonstrate that the grafted film shrinks or swells depending on the temperature of the aqueous environment. A clear transition of the elastic modulus is observed at 31–32 °C. The change of the surface wettability and mechanical properties vs temperature are attributed to different conformations taken by the polymer, which is reflected on the outmost surface as distinct side chain groups orienting outward at different temperatures as measured by SFG. The results suggest that a ppNIPAM thin film on a substrate experiences similar mechanical and chemical changes to pNIPAM bulk polymers in solution. The SFG result provides evidence supporting the current theory of the lower critical solution temperature (LCST) behavior of pNIPAM.

## Introduction

Poly(*N*-isopropyl acrylamide) (pNIPAM) has been studied extensively for decades for its reversible phase transition behavior: the swollen polymer matrix in an aqueous solution collapses as the temperature is increased above the lower critical solution temperature (LCST). This transition around physiological temperature has recently found numerous applications<sup>1</sup> including drug release,<sup>2,3</sup> chromatography for bioseparation,<sup>4–7</sup> biosensors,<sup>8,9</sup> cata-

lytic reaction control,<sup>10,11</sup> gene delivery,<sup>12,13</sup> protein folding,<sup>14</sup> and microactuators.<sup>15,16</sup> When immobilized onto a flat substrate, the LCST behavior of pNIPAM leads to a temperature-controlled wettability change on the surface and has been used for control of protein adsorption<sup>17,18</sup> and cell adhesion.<sup>19–22</sup> The recent work by Okano and colleagues to recover cell sheets from pNIPAM-grafted surfaces<sup>23,24</sup> brings exciting applications of the grafted polymer to 2-D and 3-D tissue engineering.

\* Author to whom correspondence should be addressed. Buddy D. Ratner, Director, University of Washington Engineered Biomaterials, Department of Bioengineering, Box 351720, University of Washington, Seattle, WA 98195-1720. E-mail: ratner@uweb.engr.washington.edu. Tel: (206) 685-1005. Fax: (206) 616-9763.

<sup>†</sup> University of Washington Engineered Biomaterials.

<sup>‡</sup> National ESCA and Surface Analysis Center for Biomedical Problems.

<sup>§</sup> Department of Bioengineering, University of Washington.

<sup>£</sup> Department of Chemical Engineering, University of Washington.

<sup>||</sup> University of California at Berkeley and Lawrence Berkeley National Laboratory.

(1) Roy, I.; Gupta, M. N. *Chem. Biol.* **2003**, *10*, 1161–1171.

(2) Coughlan, D. C.; Quilty, F. P.; Corrigan, O. I. *J. Controlled Release* **2004**, *98*, 97–114.

(3) Kost, J.; Langer, R. *Adv. Drug Delivery Rev.* **2001**, *46*, 125–148.

(4) Kikuchi, A.; Okano, T. *Macromol. Symp.* **2004**, *207*, 217–227.

(5) Kobayashi, J.; Kikuchi, A.; Sakai, K.; Okano, T. *Anal. Chem.* **2003**, *75*, 3244–3249.

(6) Kobayashi, J.; Kikuchi, A.; Sakai, K.; Okano, T. *Anal. Chem.* **2001**, *73*, 2027–2033.

(7) Fong, R. B.; Ding, Z. L.; Hoffman, A. S.; Stayton, P. S. *Biotechnol. Bioeng.* **2002**, *79*, 271–276.

(8) Malmstadt, N.; Yager, P.; Hoffman, A. S.; Stayton, P. S. *Anal. Chem.* **2003**, *75*, 2943–2949.

(9) Zhu, Q. Z.; Yang, H. H.; Li, D. H.; Chen, Q. Y.; Xu, J. G. *Analyst* **2000**, *125*, 2260–2263.

(10) Nagayama, H.; Maeda, Y.; Shimasaki, C.; Kitano, H. *Macromol. Chem. Phys.* **1995**, *196*, 611–620.

(11) Stayton, P. S.; Shimboji, T.; Long, C.; Chilkoti, A.; Chen, G.; Harris, J. M.; Hoffman, A. S. *Nature* **1995**, *378*, 472–474.

(12) Twaites, B. R.; Alarcon, C. D.; Cunliffe, D.; Lavigne, M.; Pennadam, S.; Smith, J. R.; Gorecki, D. C.; Alexander, C. *J. Controlled Release* **2004**, *97*, 551–566.

(13) Kurisawa, M.; Yokoyama, M.; Okano, T. *J. Controlled Release* **2000**, *68*, 1–8.

(14) Chen, Y. J.; Huang, L. W.; Chiu, H. C.; Lin, S. C. *Enzyme Microb. Technol.* **2003**, *32*, 120–130.

(15) Luo, Q. Z.; Mutlu, S.; Gianchandani, Y. B.; Svec, F.; Frechet, J. M. J. *Electrophoresis* **2003**, *24*, 3694–3702.

(16) Harmon, M. E.; Tang, M.; Frank, C. W. *Polymer* **2003**, *44*, 4547–4556.

(17) Huber, D. L.; Manginell, R. P.; Samara, M. A.; Kim, B. I.; Bunker, B. C. *Science* **2003**, *301*, 352–354.

(18) Grabstain, V.; Bianco-Peled, H. *Biotechnol. Prog.* **2003**, *19*, 1728–1733.

(19) Ista, L. K.; Mendez, S.; Perez-Luna, V. H.; Lopez, G. P. *Langmuir* **2001**, *17*, 2552–2555.

(20) Ratner, B. D.; Cheng, X.; Wang, Y. B.; Hanein, Y.; Bohringer, K. *Abstr. Pap. Am. Chem. Soc.* **2003**, *225*, U582–U582.

(21) Liu, H. C.; Ito, Y. *J. Biomed. Mater. Res. Part A* **2003**, *67A*, 1424–1429.

(22) Canavan, H. E.; Cheng, X.; Graham, D. J.; Ratner, B. D.; Castner, D. G. *Langmuir* **2005**, *21*, 1949–1955.

Despite the great interest in thermoresponsive polymer coatings based on pNIPAM, characterization of pNIPAM properties such as chemical,<sup>25,26</sup> thermal,<sup>27,28</sup> structural,<sup>29–31</sup> mechanical,<sup>32,33</sup> and optical properties<sup>34–36</sup> have mostly been performed with bulk polymer in an aqueous solution. Recent studies have examined the physical and chemical properties of immobilized pNIPAM using various techniques such as infrared (IR) spectroscopy, contact angle, secondary-ion mass spectrometry (SIMS), and ellipsometry.<sup>19,37–40</sup> However, a comprehensive study of the grafted pNIPAM thin film—including its mechanical properties and surface transition details—has yet to be undertaken and will enable further surface applications of pNIPAM.

In this paper, we studied a pNIPAM-grafted surface with multiple complementary surface analytical techniques. The pNIPAM thin film is produced using plasma polymerization (ppNIPAM),<sup>41</sup> which is a one-step, solvent free, vapor-phase technique to produce conformal, sterile, tightly adhering, and ultrathin coatings. Previously, we demonstrated that ppNIPAM stimulates different cell responses depending on the surface temperature and explored its application for proteomic and cellomic chips.<sup>42,43</sup> Here, we characterized the mechanical and chemical properties of the thin film to better understand the behavior of the polymer itself. We used time-of-flight secondary-ion mass spectrometry (ToF-SIMS) and principal component analysis (PCA) of the ToF-SIMS data to compare the surface chemistry of ppNIPAM to conventionally synthesized pNIPAM by free-radical polymerization. The temperature-induced wettability change of the polymer coating was studied by contact angle measurements. To correlate the surface wettability with the polymer mechanical properties, atomic force microscopy (AFM) was applied to study the topography and modulus of the thin film under ambient conditions in water.<sup>44,45</sup>

(23) Tsuda, Y.; Kikuchi, A.; Yamato, M.; Sakurai, Y.; Umez, M.; Okano, T. *J. Biomed. Mater. Res. Part A* **2004**, *69A*, 70–78.

(24) Shimizu, T.; Yamato, M.; Isoi, Y.; Akutsu, T.; Setomaru, T.; Abe, K.; Kikuchi, A.; Umez, M.; Okano, T. *Circ.* **2002**, *90*, E40–E48.

(25) Maeda, Y.; Higuchi, T.; Ikeda, I. *Langmuir* **2001**, *17*, 7535–7539.

(26) Katsumoto, Y.; Tanaka, T.; Sato, H.; Ozaki, Y. *J. Phys. Chem. A* **2002**, *106*, 3429–3435.

(27) Boutris, C.; Chatzi, E. G.; Kiparissides, C. *Polymer* **1997**, *38*, 2567–2570.

(28) Cai, W. S.; Gan, L. H.; Tam, K. C. *Colloid Polym. Sci.* **2001**, *279*, 793–799.

(29) Reichelt, R.; Schmidt, T.; Kuckling, D.; Arndt, K. F. *Macromol. Symp.* **2004**, *210*, 501–511.

(30) Chern, J. M.; Lee, W. F.; Hsieh, M. Y. *J. Appl. Polym. Sci.* **2004**, *92*, 3651–3658.

(31) Tam, K. C.; Wu, X. Y.; Pelton, R. H. *Polymer* **1992**, *33*, 436–438.

(32) Hirotsu, S. *J. Chem. Phys.* **1991**, *94*, 3949–3957.

(33) Shibayama, M.; Morimoto, M.; Nomura, S. *Macromolecules* **1994**, *27*, 5060–5066.

(34) Suzuki, Y.; Nozaki, K.; Yamamoto, T.; Itoh, K.; Nishio, I. *J. Chem. Phys.* **1992**, *97*, 3808–3812.

(35) Takeoka, Y.; Watanabe, M. *Adv. Mater.* **2003**, *15*, 199–201.

(36) Reese, C. E.; Mikhonin, A. V.; Kamenjicki, M.; Tikhonov, A.; Asher, S. A. *J. Am. Chem. Soc.* **2004**, *126*, 1493–1496.

(37) Bergbreiter, D. E.; Tao, G. L.; Franchina, J. G.; Sussman, L. *Macromolecules* **2001**, *34*, 3018–3023.

(38) Bohanon, T.; Elender, G.; Knoll, W.; Koberle, P.; Lee, J. S.; Offenhausser, A.; Ringsdorf, H.; Sackmann, E.; Simon, J.; Tovar, G.; Winnik, F. M. *J. Biomater. Sci.-Polym. Ed.* **1996**, *8*, 19–39.

(39) Akiyama, Y.; Kikuchi, A.; Yamato, M.; Okano, T. *Langmuir* **2004**, *20*, 5506–5511.

(40) Takei, Y. G.; Aoki, T.; Sanui, K.; Ogata, N.; Sakurai, Y.; Okano, T. *Macromolecules* **1994**, *27*, 6163–6166.

(41) Pan, Y. V.; Wesley, R. A.; Luginbuhl, R.; Denton, D. D.; Ratner, B. D. *Biomacromolecules* **2001**, *2*, 32–36.

(42) Wang, Y. B.; Cheng, X.; Hanein, Y.; Shastry, A.; Denton, D. D.; Ratner, B. D.; Bohringer, K. F. *The 12th International Conference on Solid-State Sensors and Actuators (Transducers'03)*; Boston, MA, 2003.

(43) Cheng, X.; Wang, Y. B.; Hanein, Y.; Bohringer, K. F.; Ratner, B. D. *J. Biomed. Mater. Res. Part A* **2004**, *70A*, 159–168.

(44) Sheiko, S. S. *Adv. Polym. Sci.* **2000**, *151*, 61–174.

Finally, we used sum frequency generation (SFG) vibrational microscopy to probe the species of the surface functional groups. Our study demonstrates that temperature affects the wettability, mechanical properties, and conformation of the ppNIPAM thin film. These observations are consistent with those previously reported for bulk pNIPAM in solution.

## Experimental Methods

**Substrate Preparation.** Silicon wafers were obtained from Silicon Valley Microelectronics (San Jose, CA) and diced into 1 cm × 1 cm squares. Calcium fluoride (CaF<sub>2</sub>) crystals were purchased from International Scientific Products (Irvington, NY). The wafers and CaF<sub>2</sub> samples were cleaned by sonication in methylene chloride, acetone, methanol, and 18 mΩ deionized (DI) water (Millipore, Billerica, MA) twice each for 10 min. The wafers and CaF<sub>2</sub> crystals were then subjected to a 30 min UV/ozone oxidation treatment to remove trace organic contaminants before further use.

**Plasma Polymerization.** Plasma polymerization of NIPAM was carried out in a custom-built reactor using the protocol described earlier.<sup>41</sup> In brief, the powered electrode is connected to a 13.56 MHz radio frequency power source and a manual impedance matching network. The deposition process included an 80 W methane plasma deposition followed by NIPAM plasma deposition with stepwise decreasing powers from 80 to 1 W for 30 min with a processing pressure of 100 mTorr. The ppNIPAM-grafted surfaces were rinsed three times with cold, deionized water to remove un-cross-linked molecules before use.

**Preparation for Film Thickness Measurement.** To measure ppNIPAM film thickness, a mask was applied on the center of a silicon chip to block deposition in a small region on the substrate.<sup>46</sup> The mask solution was prepared by dissolving poly(lactic acid) (PLA) (average MW 75 000–120 000, Fisher Scientific, Fairlawn, NJ) in acetone to make a 10% (w/v) solution. Five microliters of this solution was pipetted onto silicon samples and air-dried for a minimum of 5 min immediately preceding plasma deposition. After plasma deposition, the PLA mask was carefully removed using tweezers and the film edge was imaged by AFM.

**Preparation of pNIPAM by Free Radical Polymerization.** The control bulk pNIPAM was synthesized by free-radical polymerization using protocols adapted from a previous publication by Schild et al.<sup>47</sup> and was generously donated by Thomas Robey of the Bioengineering Department at the University of Washington. The reaction was carried out in benzene using azobisisobutyronitrile (AIBN, C<sub>8</sub>H<sub>12</sub>N<sub>4</sub>) as the free-radical initiator to obtain the polymer. One gram of polymer was dissolved in 6 mL of deionized water at room temperature to make a pNIPAM solution. Twenty microliters of solution was pipetted on a piece of silicon (8 mm × 8 mm) and spin-cast at 4000 rpm for 20 s to form the control surface for the ToF-SIMS study.

**ToF-SIMS and Principal Component Analysis (PCA).** ToF-SIMS data acquisition was performed using a PHI Model 7200 Physical Electronics instrument (PHI, Eden Prairie, MN) equipped with an 8 keV Cs<sup>+</sup> primary ion source, a reflectron time-of-flight mass analyzer, a chevron-type multichannel plate (MCP), a time-to-digital converter (TDC), and a pulsed electron flood gun for charge neutralization. Both positive and negative secondary ion mass spectra were collected over a mass range from  $m/z = 0$  to 400 and analyzed with PHI Tofpak software. As both the positive- and negative-ion mass spectra showed similar trends, only positive-ion ToF-SIMS spectra were presented in this study. The area of analysis for each spectrum was 100 μm × 100 μm, and the total ion dose used to acquire each spectrum was less than  $2 \times 10^{12}$  ions/cm<sup>2</sup>. The mass resolution of the secondary ion peaks in the positive-ion spectra was typically between 4000 and 6000. Positive-ion spectra were calibrated using CH<sub>3</sub><sup>+</sup>, C<sub>2</sub>H<sub>3</sub><sup>+</sup>, C<sub>3</sub>H<sub>5</sub><sup>+</sup>, and C<sub>7</sub>H<sub>7</sub><sup>+</sup> peaks before further analysis.

(45) Reich, Z.; Kapon, R.; Nevo, R.; Pilpel, Y.; Zmora, S.; Scolnik, Y. *Biotechnol. Adv.* **2001**, *19*, 451–485.

(46) Hartley, P. G.; Thissen, H.; Vaithianathan, T.; Griesser, H. J. *Plasma Polym.* **2000**, *5*, 47–60.

(47) Schild, H. G.; Tirrell, D. A. *Langmuir* **1991**, *7*, 665–671.

Three replicates were prepared for each sample type, with three spectra acquired from different locations on each replicate.

ToF-SIMS spectra from different sample types (ppNIPAM or pNIPAM) were compared using principal component analysis (PCA), which captures the linear combination of peaks that describe the majority of variation in a dataset (the principle components, PCs). Although a detailed description of PCA is not warranted here, the interested reader is referred to a more complete discussion of PCA by Jackson<sup>48</sup> or Wold.<sup>49</sup> A "complete" peak set using all of the peaks with intensities >3 times the background in the 0–400 *m/z* region was generated from all of the spectra. The peaks were then normalized to the total ion intensity to account for fluctuations in secondary-ion yield between different spectra, and all the datasets were mean-centered. PCA was then used to analyze the positive ToF-SIMS spectra, and was performed using PLS Toolbox v. 2.0 (Eigenvector Research, Manson, WA) for MATLAB (MathWorks, Inc., Natick, MA).

From this input, an output of both "scores" and "loadings" plots were obtained to compare the main differences of the samples and contribution of the chemistries to the difference. The scores describe the relationship or spread of the samples. They represent the amount of the PC in each sample and are the projection of the samples onto the PC axes. Loadings plots describe which variables are responsible for the differences seen within the dataset.

**Contact Angle Measurement.** Surface wettability was evaluated by a captive air bubble method. This was done by measuring static contact angles of an air bubble in contact with the samples submerged in pure water using a contact angle goniometer (Ramé-Hart, Mountain Lakes, NJ). The samples were allowed to equilibrate for at least an hour in the water bath at the appropriate temperature before any measurements were taken.

**AFM Measurements.** All AFM measurements were performed using a PicoScan microscope (Molecular Imaging (MI), Phoenix, AZ) on ppNIPAM deposited onto silicon chips. Samples were hydrated in DI water for an hour and then quickly transferred to a Teflon cell containing DI water for measurement. The cell was mounted on a MI thermal stage controlled by a temperature controller (Model 321, Lake Shore Cryotronics, Westerville, OH), and data were collected in the range of 25–37 °C. The samples were allowed to equilibrate for at least half an hour at each temperature before the measurements were taken.

Topography images were obtained in the acoustic AC mode using rectangular silicon cantilevers with integrated sharp tips, having resonance frequencies in the range of 260–410 kHz (PPP-NCH type, Nanosensors, Neuchatel, Switzerland). The boundary between the plasma polymer coated and uncoated regions were aligned directly below the AFM tip using an add-on CCD camera. The images were analyzed using ImageJ software (<http://rsb.info.nih.gov/ij/>) to get height histograms, average step height, and roughness information.

The force displacement curves were taken with standard V-shaped silicon nitride cantilevers (Nanoprobe AFM tips, Type NP-S, Digital Instruments, Santa Barbara, CA). The tip spring constant was 0.06 N/m according to the manufacturer's specifications. The tip radius was measured to be 50–60 nm by scanning an Ultrasharp calibration grating that contains an array of sharp tips (TGT01 model, Silicon-MDT, Moscow, Russia). These blunt-tip cantilevers were selected to satisfy conditions for elastic mechanical contact.<sup>50</sup> Five to 10 force displacement curves were acquired at randomly selected regions at each temperature using an approach–retract frequency of 0.5 Hz.

To calibrate the detector signal (in volts), measurements of the force displacement curves were taken on a reference surface, which is assumed to have infinitely high stiffness and no deformation from pressing. In our study, a piece of clean silicon wafer was used as the reference surface, whose modulus is 160 GPa and several orders of magnitude higher than the polymer.

The measured force–displacement curves were converted to plots relating indentation depth vs loading force according to previously described methods.<sup>51</sup> The indentation of the cantilever under a given load was fit to the Hertz model for indentation of a sphere on an elastic solid and used to calculate the elastic modulus of the surface thin film.<sup>51,52</sup> The indentation depth was controlled to no greater than 20% of the film thickness to minimize the influence of the solid support.<sup>50,53,54</sup> To exclude the possibility of polymer plastic deformation, tens of force displacement curves on the same location were recorded and identical curves were obtained, indicating full recovery of surfaces for each indentation cycle.

**SFG Measurements.** Surface vibrational spectra were obtained by sum frequency generation (SFG) vibrational spectroscopy to identify the functional groups present at the outermost surface. Details of the technique can be found in several recent papers.<sup>55–57</sup> The specific laser system used for our study was described by Kim et al.<sup>58</sup> Briefly, surface vibrational spectra of ppNIPAM deposited onto CaF<sub>2</sub> crystals were collected by overlapping visible and tunable infrared laser pulses on the polymer surface and measuring the induced sum-frequency signal. The visible laser pulse ( $\omega_{\text{vis}}$ ) of 532 nm light was generated by frequency-doubling the 1064 nm fundamental output from a passive-active mode-locked Nd:YAG laser (Leopard, Continuum, Santa Clara, CA) using an optical parametric generation/optical parametric amplification (OPG/OPA) stage (Laservision, Bellevue, WA). The untreated radiation has a pulse width of 20 ps and a 20 Hz repetition rate. Using the fundamental radiation to pump the stage crystals, the infrared laser pulse ( $\omega_{\text{ir}}$ ) is generated from the OPG/OPA stage and is tunable from 2000 to 4000 cm<sup>−1</sup>. The sum frequency output signal ( $\omega_{\text{sum}} = \omega_{\text{vis}} + \omega_{\text{ir}}$ ) was collected by a gated integrator and photon counting system. In this study, the spectra were collected using an S<sub>sum</sub>S<sub>vis</sub>DIR polarization combination. The SFG spectra in air were taken by aligning the polymer face of the sample toward the light source with the angle of incident light set at 45° with respect to the surface normal. For studies in water, the polymer film was immersed in pure water and the incident light was projected through the crystal to the polymer film. Light reflected from the solid–liquid interface was collected after traveling twice through the crystal. The incident light angle and polarization were the same as those used for the air spectra. The collected spectra cover the CH-stretch region from 2800 to 3050 cm<sup>−1</sup> in 5 cm<sup>−1</sup> increments. For a given condition, SFG measurements were repeated on at least three different samples with 1–3 spots probed on each sample. For each sample spot, 4–5 scans were performed with 100 shots/data point to increase the signal-to-noise ratio. The collected data were averaged to produce the final spectra presented here.

## Results and Discussions

**ToF-SIMS Analysis of Surface Chemistry.** Previously, we presented an ESCA analysis on ppNIPAM indicating that its surface chemical composition is close to that predicted by the monomer's stoichiometry.<sup>41</sup> To better assess whether the monomer structure is retained after plasma deposition, ToF-SIMS is used as a complementary technique, as it yields information regarding molecular species at interfaces. A representative ToF-SIMS positive ion spectrum of ppNIPAM in the range

(51) Chizhik, S. A.; Huang, Z.; Gorbunov, V. V.; Myshkin, N. K.; Tsukruk, V. V. *Langmuir* **1998**, *14*, 2606–2609.

(52) Tsukruk, V. V.; Huang, Z.; Chizhik, S. A.; Gorbunov, V. V. *J. Mater. Sci.* **1998**, *33*, 4905–4909.

(53) Harmon, M. E.; Kuckling, D.; Pareek, P.; Frank, C. W. *Langmuir* **2003**, *19*, 10947–10956.

(54) Domke, J.; Radmacher, M. *Langmuir* **1998**, *14*, 3320–3325.

(55) Chen, Z.; Shen, Y. R.; Somorjai, G. A. *Annu. Rev. Phys. Chem.* **2002**, *53*, 437–465.

(56) Miranda, P. B.; Shen, Y. R. *J. Phys. Chem. B* **1999**, *103*, 3292–3307.

(57) Opdahl, A.; Hoffer, S.; Mailhot, B.; Somorjai, G. *Chem. Rec.* **2001**, *1*, 101–122.

(58) Kim, J.; Koffas, T. S.; Lawrence, C. C.; Somorjai, G. A. *Langmuir* **2004**, *20*, 4640–4646.

(48) Jackson, J. E. *J. Qual. Technol.* **1980**, *12*, 201–213.


(49) Wold, S.; Esbensen, K.; Geladi, P. *Chemom. Intell. Lab. Syst.* **1987**, *2*, 37–52.

(50) Tsukruk, V. V.; Sidorenko, A.; Gorbunov, V. V.; Chizhik, S. A. *Langmuir* **2001**, *17*, 6715–6719.

from  $m/z = 0$  to 200 is shown in Figure 1a, as very few peaks of interest are beyond this range. The molecular fragment of the NIPAM monomer ( $C_6H_{12}NO^+$ ) is clearly evident at  $m/z = 114.093$ . Fragments at  $m/z = 43.055$  and  $58.065$  are indicative of the monomer fragments  $C_3H_7^+$  and  $C_3H_8N^+$ , respectively. The ToF-SIMS spectra of pNIPAM by free-radical polymerization also contain these peaks. Observation of the monomer molecular fragments supports the hypothesis that at least some of the monomer units remain intact on the surface following plasma deposition.

We next compare the surface chemistry of ppNIPAM to that of conventionally synthesized pNIPAM. ESCA analysis reveals the similarity of ppNIPAM to pNIPAM in both the elemental composition and chemical bonding (data not shown). However, a direct comparison of ppNIPAM and pNIPAM SIMS spectra is difficult, as SIMS spectra from each type contain hundreds of peaks in the 0–400  $m/z$  range. Principal component analysis (PCA) is used to aid in the interpretation of spectra by identifying related variables and focusing on the differences between spectra.<sup>48,49</sup> Figure 1b shows a scores plot of principal component 1 (PC1), which captures 97% of the variance in the data, vs the spectrum number. Examination of Figure 1b shows that ppNIPAM and pNIPAM samples are distinctly grouped from each other: ppNIPAM samples cluster above the  $x$  axis, and pNIPAM samples cluster below the  $x$  axis. To appreciate the reason for these differences, we must inspect the loadings plot for PC 1.

Figure 1c represents the loadings from PC1. Peaks are shown only in the mass range from  $m/z = 0$  to 200, as few peaks of interest are observed beyond this range. Each of the positive peaks in the PC1 loadings plot corresponds to samples in the scores plot with positive scores. Of key interest in the loadings plot is the absence of molecular fragments arising from the intact NIPAM moiety in the negative loadings corresponding to conventional pNIPAM. This indicates that the differences between ppNIPAM and pNIPAM surfaces are not due to the absence of monomer units. Instead, when comparing the PC1 loadings plot to the PC1 scores, we find that separation of ppNIPAM from pNIPAM is due to peaks loaded positively with ppNIPAM, including 74.062 ( $C_3H_8NO^+$ ), 97.080 ( $C_5H_9N_2^+$ ), and 156.144 ( $C_9H_{18}NO^+$ ). These peaks are likely produced by cross-linking or other reactions occurring during the plasma deposition process as they do not contain the monomer structure. This is expected considering the numerous reactive species created in the energetic plasma process.<sup>59</sup> The fact that hydrocarbon peaks at 27.024 ( $C_2H_3^+$ ) and 43.055 ( $C_3H_7^+$ ) loaded negatively with pNIPAM indicate the cross-linking may be occurring through the side-chain propyl groups. Therefore, a comparison of the positive-ion spectra of the two surfaces indicates that the NIPAM monomer units are immobilized onto the substrate in the plasma film with high retention of the monomer structure despite the concern of significant monomer fragmentation in the plasma state.<sup>59</sup> Two hypotheses may explain the maintenance of the monomer integrity: (1) low RF power (as used in our process) reduces monomer fragmentation in plasmas<sup>59</sup> and (2) condensation of polymerizable molecules (e.g., molecules with unsaturated backbones) in conjunction with plasma deposition



**Figure 1.** (a) Characteristic ToF-SIMS positive-ion spectrum acquired on a ppNIPAM surface. Important peaks corresponding to the monomer fragments are labeled. The theoretical linear polymer structure is shown in the inset. ToF-SIMS spectra of ppNIPAM and conventional pNIPAM prepared by free-radical polymerization were subjected to principal component analysis (PCA) to compare their chemistry. The PCA results of positive ion spectra are presented as scores (b) and loadings (c) plots. The differences between the two surfaces are likely produced from cross-linking in the plasma film, as both films show evidence of significant retention of the NIPAM monomer structure.

(59) *Plasma deposition, treatment, and etching of polymers*; d'Agostino, R., Ed.; Academic Press: Boston, 1990.

(60) Lopez, G. P.; Ratner, B. D. *Langmuir* **1991**, *7*, 766–773.

(61) Lopez, G. P.; Chilkoti, A.; Briggs, D.; Ratner, B. D. *J. Polym. Sci. Pol. Chem.* **1992**, *30*, 2427–2441.

(62) Lopez, G. P.; Ratner, B. D. *J. Polym. Sci. Pol. Chem.* **1992**, *30*, 2415–2425.

**Table 1. Advancing Contact Angles on ppNIPAM-Coated Silicon and Bare Silicon Measured by Trapped Air Bubbles in Water<sup>a</sup>**

	ppNIPAM	silicon
20 °C	34° ± 1.0°	41° ± 0.6°
40 °C	40° ± 0.5°	40° ± 0.6°

<sup>a</sup> A significant difference is noticed on ppNIPAM when measurements are taken at the two temperatures but not on the control silicon substrate.

onto the surface helps with the formation of predictable chemical functionalities that resemble the monomer.<sup>60–62</sup> That the monomer structure is retained suggests that the phase transition properties of the ppNIPAM thin film will be retained as well. However, as both ESCA and ToF-SIMS are ultrahigh vacuum techniques, they cannot probe the phase transition behavior in situ. Thus, we employ several other techniques in the rest of the paper to directly study the structure and behavior of ppNIPAM films below and above the LCST in water.

#### Change in Surface Wettability by Contact Angles.

To directly evaluate the wettability of the ppNIPAM film, a captive air bubble contact angle of the ppNIPAM film surface was measured in water. A summary of the advancing contact angles measured on ppNIPAM-coated silicon and bare silicon is found in Table 1. The contact angles on ppNIPAM change from 34 ± 1.0° at 20 °C to 40 ± 0.5° at 45 °C ( $n \geq 11$ ), which are comparable with measurements by Akiyama et al. using a silane-grafted pNIPAM thin film.<sup>39</sup> Similar measurements taken on untreated bare silicon show no statistical change in the surface contact angles over the same temperature range (41 ± 0.6° at 20 °C to 40 ± 0.6° at 45 °C). The significantly lower contact angle at room temperature on ppNIPAM indicates that the plasma film becomes more hydrated when the temperature is below the LCST. Thus, the surface wettability change with temperature confirms the thermoresponsive behavior of ppNIPAM film, as expected from the intact monomer structure observed in ToF-SIMS.

**Surface Topography by AFM.** Bulk pNIPAM polymer demonstrates a transition in volume and modulus through its LCST.<sup>32,33</sup> To test whether this is also the case with the plasma-deposited thermoresponsive film, we studied the surface topographic and mechanical properties of ppNIPAM using AFM. Figure 2 shows the surface topography of a ppNIPAM film imaged in water by AFM at 25 and 37 °C. The surface is fairly smooth at 37 °C with a root-mean-square (RMS) roughness of 3.5 ± 0.5 nm over a 5 μm × 5 μm scan area. When the same size image is taken at 25 °C, the RMS roughness increases to 5.3 ± 1.1 nm. It has been previously observed that, when ppNIPAM hydrates at room temperature, it creates nanocavities on the surface<sup>63</sup> that probably account for the slight increase in surface roughness observed in the swollen state. This may suggest an inhomogeneous cross-link density over the surface at a nanometer scale causing some areas to swell less than others.

To determine the film thickness in water at different temperatures, ppNIPAM steps are created by plasma deposition over a partially masked sample and then removing the mask afterward. Two characteristic AFM images of the same area across a ppNIPAM step with the height histograms and section analysis are shown in Figure 3a and d. The height histograms obtained for each image give two characteristic peaks corresponding to the

substrate and coating heights (gray areas in Figure 3b and e). By subtracting the lower peak value from the upper, the film thickness is obtained. To accurately estimate the peak location in the histogram, a Gaussian model is used to fit each peak in the histograms (black curves in Figure 3b and e). The distances between the two peaks are 73.7 and 63.7 nm at 25 and 37 °C, respectively, indicating a 10 nm decrease in film thickness above the LCST compared to below the LCST. The section analysis on individual scan lines (Figure 3c and f) in the two images confirms the values obtained from the histograms. The broadening of the height histogram at 25 °C (Figure 3b) also indicates higher roughness and scattering of the height distribution. Identical histogram analyses were performed on four samples of different deposition batches and three spots on each sample. The results are summarized in Figure 3g. Although the thickness of deposited polymer varies from batch to batch, decreased film thickness is observed in all the samples and areas tested as temperature increases from below to above the LCST, with the error bars in Figure 3g resulting from variations in film thickness on individual samples at each temperature. The batch-to-batch variation of the film thickness at the same temperature may arise from variation in the plasma polymerization process.

Recently, Akiyama et al. reported that temperature-controlled cell adhesion and detachment from pNIPAM surface is dependent on the thickness of the thermoresponsive film.<sup>39</sup> However, in our cell culture study, no obvious difference was observed on different batches of coatings.<sup>43</sup> This suggests that the variation in film thickness we observed arises mainly from the thickness variations in the underlying adhesion-promoting layer formed during the high-power deposition, not thickness variations in the top functional ppNIPAM coating.

**Mechanical Property by Force Displacement Curves.** Since the ppNIPAM film thickness/volume changes with temperature, it is expected that the polymer mechanical properties also vary.<sup>32</sup> Atomic force microscopy has been shown as a unique tool to probe the micro-mechanical properties of thin-film coatings.<sup>64–67</sup> Figure 4a shows sample AFM force vs distance curves obtained on bare silicon at room temperature and on ppNIPAM surface at 25 and 37 °C in pure water. In this figure, the cantilever deflection is presented as a function of the  $z$  piezo displacement. It is clearly seen that the cantilever deflects less for the same  $z$  piezo movement at 25 °C than at 37 °C, indicating the polymer is softer and more swollen at 25 °C.

To quantitatively compare the thin-film mechanical properties, the force-displacement data (Figure 4a) are converted to plots relating the indentation depth as a function of the loading force (squares and circles in Figure 4b). The elastic moduli are obtained from best fitting to the indentation vs load data using the Hertz model (thin solid lines in Figure 4b). The parameters used are  $R = 53$  nm and  $\nu = 0.5$  assuming elastic deformation. The spring constant is 0.06 N/m taken from the manufacturer's specifications. For easier comparison of the fitted curve and experimental data, the same plot is shown in the log-log presentation in Figure 4c. It is observed that the experimental data are described satisfactorily using a simple Hertz model for the force displacement measure-


(64) Munz, M.; Cappella, B.; Sturm, H.; Geuss, M.; Schulz, E. *Filler-Reinf. Elastomers Scanning Force Microscopy* **2003**, 164, 87–210.

(65) Janicijevic, A.; Ristic, D.; Wyman, C. J. *Microsc.-Oxf.* **2003**, 212, 264–272.

(66) Jandt, K. D. *Mater. Sci. Eng. R-Rep.* **1998**, 21, 221–295.

(67) Baker, S. P. *Thin Solid Films* **1997**, 308, 289–296.

(63) Matzelle, T. R.; Ivanov, D. A.; Landwehr, D.; Heinrich, L. A.; Herkt-Bruns, C.; Reichelt, R.; Kruse, N. *J. Phys. Chem. B* **2002**, 106, 2861–2866.



**Figure 2.** AFM images of ppNIPAM in water at 25 (a) and 37 °C (b) acquired in the acoustic AC mode. The surfaces are fairly smooth in both cases with a slightly higher root-mean-square roughness at 25 than at 37 °C. Notice the two images have different  $z$  scales.

ment taken at 37 °C (solid squares in Figure 4b and c). However, at 25 °C, the fitted curve deviates from the experimental measurement when the indentation depth goes beyond 12–13 nm. As the Hertz model assumes that the two contacting surfaces have homogeneous elastic properties in the  $z$  direction, this deviation is likely due to the substrate effect that the simple Hertz model cannot explain, as reported by Domke and Radmacher.<sup>54</sup> Using the optimal fitting parameters, the elastic moduli are calculated to be 185.2 kPa at 25 °C and 1.592 MPa at 37 °C for the two curves shown in Figure 4a. Thus, the local stiffness of ppNIPAM is more than 8 times higher in the collapsed state at 37 °C than in the swollen state at 25 °C.

In an aqueous environment, bulk polymer chains of pNIPAM are believed to adopt a random coil configuration below the LCST and a more compact globular configuration above the LCST. This conformational transition accounts for changes in both polymer volume and mechanical properties.<sup>33</sup> The AFM study in our work demonstrates that the ppNIPAM thin film is still able to transition between the collapsed and swollen state as the temperature is changed. However, when comparing the mechanical characteristics of the ppNIPAM thin film produced in our system with those of the pNIPAM gel synthesized by free-radical polymerization in the bulk state, some obvious differences are noticed. Matzelle et al. recently reported a swelling ratio of eight and elastic moduli of 2.8 and 183 kPa at 25 and 35 °C, respectively for a lightly cross-linked pNIPAM gel (100:1 monomer-to-cross-linker molar ratio) cast onto mica.<sup>63</sup> The surface-immobilized ppNIPAM, however, has a higher moduli (185 kPa and 1.592 MPa) and lower swelling ratio (<1). This would seem to support our conclusion from PCA analysis of the ToF-SIMS data that the ppNIPAM film is more cross-linked, as cross-links have been shown to restrict the magnitude of the swelling ratio and reinforce the polymer mechanical properties.<sup>32,33,68,69</sup> Nevertheless, the moduli below and above the LCST obtained by us still fall in the soft hydrogel range of kilopascals to a few megapascals.<sup>70</sup>

To determine at which temperature the transition in surface stiffness happens, force–distance curve measurements were taken at 1 °C increments from 24 to 37 °C.

Five to 10 randomly selected spots were probed at each temperature with the average elastic moduli summarized in Figure 4d. The surface stiffness increases significantly around 31–32 °C, close to the transition temperature measured by Pan et al. using an AFM modulation measurement.<sup>41</sup> To confirm that the stiffness transition behavior is reversible, the surface was cooled to 25 °C again and the measured modulus is shown as an open square in Figure 4d. It is clearly observed that the film rehydrates and swells after cooling to below its LCST. The relatively larger deviation for measurements taken above the transition temperature may arise from reduced sensitivity to modulus differences in the range of the higher modulus above the LCST.


**Surface Group Rearrangement by SFG.** To determine whether the surface chemistry of ppNIPAM films changes in situ at different temperatures, we next analyzed the ppNIPAM film with SFG vibrational spectroscopy. SFG selection rules allow the detection of chemical species that are ordered and lack inversion symmetry, thus allowing the top few atomic layers of the polymer surface to be probed directly.<sup>55–57,71</sup> Figure 5 shows characteristic SFG spectra for the CH stretching region taken in water at room temperature and 37 °C. For comparison, the spectrum of ppNIPAM in air at room temperature is plotted in the same figure. As water absorption tends to attenuate the signal, the spectra in water are multiplied by a factor of 4. Figure 5a shows the spectrum of fully dehydrated ppNIPAM film in air where two peaks are predominant and centered at 2875 and 2940  $\text{cm}^{-1}$ . These two peaks are assigned as the  $\text{CH}_3(\text{s})$  stretch and Fermi resonance between the  $\text{CH}_3$  stretching and bending modes. There are also three shoulder peaks measured at approximately 2855, 2925, and 2960  $\text{cm}^{-1}$ , which are assigned as the  $\text{CH}_2(\text{s})$ ,  $\text{CH}_2(\text{a})$ , and  $\text{CH}_3(\text{a})$  stretches. The strong  $\text{CH}_3$  stretch peak indicates the presence of ordered isopropyl groups tilting toward the surface normal from the polymer side chain in the dehydrated state. The  $\text{CH}_2$  stretch in the spectrum may arise from the backbone or from random cross-linking induced by the plasma-deposition process. This is expected given that SFG spectra provide averaged chemical information over a 1  $\text{mm}^2$  spot size. When the spectrum is acquired in water at 37 °C, a broad peak is observed between 2900 and 2980  $\text{cm}^{-1}$ , which is associated with the  $\text{CH}_2(\text{a})$  stretch,  $\text{CH}_3$  Fermi resonance, and  $\text{CH}_3(\text{a})$  stretch peaks. This suggests organization of the hydro-

(68) Senff, H.; Richtering, W. *Colloid Polym. Sci.* **2000**, 278, 830–840.

(69) Takahashi, K.; Takigawa, T.; Masuda, T. *J. Chem. Phys.* **2004**, 120, 2972–2979.

(70) Kim, S. H.; Opdahl, A.; Marmo, C.; Somorjai, G. A. *Biomaterials* **2002**, 23, 1657–1666.


(71) Chen, Z.; Ward, R.; Tian, Y.; Eppler, A. S.; Shen, Y. R.; Somorjai, G. A. *J. Phys. Chem. B* **1999**, 103, 2935–2942.




**Figure 3.** AFM images of a ppNIPAM step on a silicon surface at 25 (a) and 37 °C (d). The corresponding height histograms (gray area) at 25 (b) and 37 °C (e) show two main heights, representing the substrate and plasma polymer surfaces, respectively. Each of the peaks is fitted to a Gaussian model (black curve), and the centers of the peaks are denoted by the triangular cursors. The step heights are obtained by subtracting the lower cursor position from the upper, giving a plasma polymer thickness of 73.7 nm at 25 °C and 63.7 nm at 37 °C for the scanned region. Section analyses on individual scan lines in each image are shown in (c) for 25 °C and (f) for 37 °C, which yields step heights of 74.2 and 63.1 nm, respectively. Film thickness measured on four different samples and three spots on each samples is summarized in (g) using the histogram analysis. The gray bar and white bar are film thicknesses measured at 25 and 37 °C, respectively, and a thicker film is observed for all measurements at 25 °C.

phobic isopropyl side chain to the aqueous environment above the LCST. In contrast, we find no evidence of these peaks at room temperature. This indicates disordering of

the hydrophobic isopropyl groups away from the surface normal, either orienting to the interior of the polymer or in the plane of the surface. It has been hypothesized that,



**Figure 4.** (a) Force-displacement curves by AFM on ppNIPAM coatings in pure water at 25 (bottom line) and 37 °C (middle line) and on silicon (top line). The same z piezo displacement results in a smaller cantilever deflection on the ppNIPAM surface in comparison to the hard silicon surfaces because of elastic indentation. The plasma-polymerized NIPAM surface appears to be stiffer at 37 °C than at 25 °C, as there is less deflection from the same z piezo movement. (b) Plot of indentation vs loading force obtained on ppNIPAM at 25 (open circles) and 37 °C (solid squares). Each data set has been modeled by the Hertz theory for a sphere indenting a flat surface (solid lines). The optimal fitting parameters from the Hertz theory are used to calculate Young's modulus at each temperature. The corresponding log-log presentation of (b) is given in (c) for easier comparison of the measured data with the theoretical fittings. To determine the transition temperature, Young's modulus of ppNIPAM are calculated from force displacement curves acquired at 25–37 °C with a 1 °C temperature increment. The results are demonstrated in (d) with 5–10 replicates for each data point. A clear transition in the surface modulus is noticed at around 31–32 °C. The open square at 25 °C shows recovery of the film to the swollen state after cooling the sample down from 37 to 25 °C.



**Figure 5.** SFG spectra of ppNIPAM in (a) air at room temperature, (b) pure water at 37 °C, and (c) pure water at room temperature (25 °C). The spectra obtained in water are enhanced by a multiple of 4 to counteract the low signal intensity in the water measurements brought on by the absorption of the IR signal by water. The lines are guides to the eyes, and the peak assignments are labeled in the figure.

below the LCST, the amide groups will extend into the aqueous environment to participate in hydrogen bonding, although we are not able to directly observe this as the characteristic peaks are not detected in this region.

The results from our SFG characterization of ppNIPAM films in situ above and below the LCST support the hypothesis that ppNIPAM films retain the behavior characteristic of their conventionally formed counterparts. The structural rearrangement of the ppNIPAM polymer side chain provides evidence to support the currently proposed mechanism of LCST behavior of thermoresponsive polymers.<sup>33,72</sup> It has been proposed that, below the LCST, well-hydrated pNIPAM chains take a random-coil configuration in an aqueous environment, with amide groups forming hydrogen bonds with water, but a more-compact globular configuration and an increased hydrophobic interaction accompanied by a sudden dehydration above its LCST. Associated with the polymer conformational changes, we directly observe the reorientation of the surface chemical functionalities using SFG. In the dehydrated state, the polymer surface orients the hydrophobic group outward to maximize hydrogen bonding underneath the surface.<sup>70,73</sup> In the aqueous environment at room temperature, on the other hand, the hydrophobic isopropyl groups appear to bend inward to allow hydrogen bonding of the polar amide groups with water to lower surface energy. Above the LCST in water, the surface rearranges to resemble the one in air due to an entropy-driven process to free the bound water molecules and reform intramolecular hydrogen bonds under the surface.<sup>1,72,74</sup> This exposure of surface chemical functionalities of different polarities may also help to explain the change of surface contact angles as a function of temperature. This preliminary examination of the C–H stretch region shows promising results in that we detect rearrangement of the isopropyl groups, although more studies of the amide

(72) Lin, S. Y.; Chen, K. S.; Liang, R. C. *Polymer* **1999**, *40*, 2619–2624.

(73) Chen, Q.; Zhang, D.; Somorjai, G.; Bertozzi, C. R. *J. Am. Chem. Soc.* **1999**, *121*, 446–447.

(74) Bruscolini, P.; Casetti, L. *Phys. Rev. E* **2001**, *64*, Art. No. 051805, Part 1.

group transition and water structure on ppNIPAM are needed to provide a more complete picture of the mechanism behind LCST behavior.

### Conclusion

We report in this paper characterization of a plasma-deposited NIPAM thin film using multiple, complementary techniques. The ppNIPAM film is found to resemble the conventional bulk polymer in surface wettability, structural, and elasticity transition through the LCST near 31–32 °C. The surface wettability, as well as polymer thickness, decreases while the film elastic modulus increases when water temperature goes from 25 to 35 °C. However, the magnitude of moduli and swelling ratio differs between ppNIPAM and pNIPAM. This may arise from cross-linking in the plasma polymer, as suggested by the ToF-SIMS spectra. Associated with the wettability and mechanical property transition, reorientation of the side-chain groups is directly probed by SFG measurements. Disappearance of the features attributed to methyl groups at room temperature suggests different hydrogen bonding and water structure at the surfaces. The value of SFG to observe transitions in polymers at the nanometer scale is confirmed in this study. Direct molecular mea-

surement of subtle but significant surface changes as a function of temperature in a NIPAM polymer were made for the first time here. Future experiments will further investigate this hypothesis by detecting signals in the hydroxyl and amide stretch region to further understand the orientation of those groups.

**Acknowledgment.** This research was supported by NSF-Engineering Research Center program Grant No. ERC-9529161 to the University of Washington Engineered Biomaterials group (UWEB) and NIBIB Grant No. EB-002027 to the National ESCA and Surface Analysis Center for Biomedical Problems (NESAC/BIO). The SFG study was supported by the Director, Office of Science, Office of Basic Energy Sciences, Divisions of Materials Science and Chemical Science of the U.S. Department of Energy under Contract No. DE-AC03-76SF00098. J.R.H. was supported by an NIH Biomaterials grant (GM-065098). The authors thank Rosnita Talib and Sally McArthur at the Department of Engineering Materials at University of Sheffield, as well as Winston Ciridon and Dr. Vickie Pan for expertise.

LA050417O